Article

A comparative study of hydroxyapatite coating produced with Plasma Electrolytic Oxidation and Hydrothermal Treatment on titanium alloys: Ti6Al4V and Ti6Al7Nb for dental implants

Elinor Nahum*, Svetlana Lugovskoy

Department of Chemical Engineering, Ariel University, Ariel 40700, Israel; svetlanalu@ariel.ac.il

* Correspondence: elinorna@ariel.ac.il

Abstract: Titanium and Titanium alloys are considered perfect materials for applications in a human body, such as artificial joints and dental implants. Ti6Al4V is a very common alloy used for dental implants, owing to its good mechanical properties and corrosion resistance. Nevertheless, because of uncertainties regarding the toxicity of vanadium and its influence on the human body, other titanium alloys containing no vanadium and retaining suitable properties are used. The aim of this study is to compare two viable titanium alloys, Ti6Al4V and Ti6Al7Nb, and to attain on their surface hydroxyapatite (HA) coating improving the osseointegration, as it simulates a human bone. In this work Ti6Al4V and Ti6Al7Nb were oxidized in a water solution of calcium acetate ($\text{Ca}(\text{CH}_3\text{COO})_2$) and calcium glycerophosphate ($\text{Ca}(\text{PO}_4\text{CH}(\text{CH}_2\text{OH})_2$) by Plasma Electrolytic Oxidation (PEO) for 20 minutes and then were hydrothermally treated (HTT) in water (pH=7) and in KOH solution (pH=11) for 2 hours at 200°C in a pressurized reactor. The surface morphologies, elemental composition and phase components were characterized by Scanning Electron Microscopy, Energy Dispersive Spectroscopy and X-Ray Diffraction, respectively. The surface roughness was measured by Atomic Force Microscope (AFM) and thickness measurements were made by SEM and thickness gauge. Also, corrosion tests were made to evaluate the corrosion behavior of the two alloys.

Keywords: Ti6Al4V; Ti6Al7Nb; Plasma electrolytic oxidation (PEO); hydrothermal treatment (HTT); Hydroxyapatite (HA)

1. Introduction

Titanium and Titanium alloys are considered perfect engineering materials for applications inside a human body, such as artificial joints, prostheses for blood vessels and dental implants. These alloys have the necessary properties for implant materials, such as low Young modulus, good fatigue strength and excellent corrosion resistance even in aggressive physiological environments. In addition, the corrosion products of titanium and its alloys are harmless for living tissues and the use of them as bio-medical materials has been increasing significantly in last few decades [1,2]. A layer containing mainly Titania (TiO_2) is formed spontaneously or by electrochemical procedures on the surface of titanium and titanium alloys. This layer is responsible for the distinctive characteristics of implants materials and thereby is considered to favor their adaptation to living tissues [3]. The most common titanium alloys used for medical applications are commercial pure titanium (also known as CP-Ti) and Ti6Al4V. CP-Ti cannot be used for medical applications that required high stress durability such as orthopedic prosthesis. It also has poorer mechanical properties than those of other titanium alloys. In the contrary to CP-Ti, Ti6Al4V is an alloy having good corrosion resistance and good mechanical properties, but there are some uncertainties concerning the influence of vanadium, which is considered to be toxic to human body and might be released from the implant due to corrosion and wear processes [4,5]. For that reason, it became necessary to use a vanadium free alloy

with suitable properties such as Ti6Al7Nb [6]. Titanium is a reactive metal which can be easily oxidized when exposed to air or water, producing a thin layer of TiO₂. This oxide layer is considered to be passive and chemically stable, it also has the capability of insulate the metal implant from the corrosion environment [7]. The combination of passive oxide layers and the smooth surfaces of an untreated metal makes titanium and titanium alloys to be bio-inert yet lacking bio-functionality, and therefore to be poorly integrated with bone [8]. To overcome these disadvantages, it is required to modify the surface of the implants. In this study, the surface modification was made by using plasma electrolyte oxidation which is a simple technique for producing hard and rough coating with micro-pores [9]. Using that technique, the insertion into the coating of such elements as calcium and phosphorous may be performed by just adding them to the electrolyte in a suitable form. The presence of these elements in the coating improves the biological compatibility of the implant to the living body [10]. In addition, the coating produced with this technique has good adhesion to the metal even if the implant geometry is complex such as screw shaped implants [11,12].

2. Materials and Methods

2.1 Samples preparation, PEO process and hydrothermal treatment

Ti6Al4V samples of 40mm x 20mm x 1mm size and Ti6Al7Nb samples of 40mm x 20mm x 3mm size were used as substrates in this study. The samples were grounded by 150, 360, 600, 1000 grid SiC papers. Subsequently, the samples were cleaned in distilled water and acetone in an ultrasonic cleaner for 5 minutes. The PEO treatment was performed in an electrolyte containing 0.25M calcium acetate and 0.06M calcium glycerophosphate in distilled water at current density of 4A/dm² for 20 minutes. The PEO station was operated in AC mode with a water-cooled stainless-steel container, which served as the counter electrode, equipped with a stirring system. After the completion of the PEO process the samples were washed with distilled water and dried under air. After that, the samples of both alloys were hydrothermally treated in distilled water and in a KOH solution separately at 200°C in a pressurized reactor for 2 hours.

2.2 Characterization of the coating

The surface morphology and elemental composition were characterized by scanning microscope electron (SEM) TESCAN MAIA3 TriglavTM equipped with AZtec Oxford energy dispersive spectroscopy (EDS) analyser. X-Ray diffraction (XRD) Rigaku, SmartLab X-RAY DIFRACTOMETER using Cu-K α radiation ($\lambda=1.54\text{\AA}$) between 15° and 65° angles with a step size 0.02°, was used to characterized the phases components of substrates and coating. Thickness of the coatings was measured by using ElektroPhysik MiniTest 730 thickness gauge based on eddy current principle. The average thickness was taken from ten measurements and the standard deviation was calculated by the device. Focused ion beam technique (FIB) FEI Helios NanoLabTM 600 DualBeam was used to both characterize the morphology of coating and measure the coating thickness by exposing a cross sectional area. Surface roughness of the samples was evaluated with atomic force microscope (AFM) Bruker Dimension FastScan with ScanAsystTM using contact mode.

2.3 Electrochemical characterization

The corrosion resistance was determined by electrochemical methods: linear polarization (LPR) and Tafel slopes analyses using a three electrodes corrosion cell in a single chamber, where Ag/AgCl electrode functioned as a reference electrode, the sample functioned as the working electrode and a platinum wire as a counter electrode. The processes were operated by an IVIUMnSTAT potentiostat. In order to simulate the physiological conditions of a human body, all corrosion tests were made in a Hanks' solution and a simulated saliva solution, whose chemical compositions are given in Table 1. The pH of the electrolytes was 7 approximately and the temperature was maintained at 36.5°C.

Table 1. Chemical composition of Hank's and simulated saliva solutions

Hanks' solution [13]		Saliva solution [14]	
Reagent	Composition [g/l]	Reagent	Composition [g/l]
CaCl ₂ ·2H ₂ O	0.185	MgCl ₂ ·6H ₂ O	0.059
MgSO ₄	0.09767	KCl	0.625
KCl	0.4	KH ₂ PO ₄	0.326
KH ₂ PO ₄	0.06	K ₂ HPO ₄	0.804
NaHCO ₃	0.35	CaCl ₂ ·2H ₂ O	0.166
NaCl	8.0	C ₃ H ₈ O ₃	2.00
Na ₂ HPO ₄	0.04788	Sodium Carboxymethyl	10.0
		Cellulose	
Glucose	1.0		

3. Results and Discussion

3.1. Scanning electron microscope (SEM)

The surface morphology of the PEO coating of both titanium alloys is shown in Figure 1. This Figure shows typical microstructure of oxide coating produced after PEO process and characterized by micro pores scattered randomly across the surface. Both alloys have similar morphology after this process.

Figure 1. SEM micrograph of the sample's surface after PEO: (a) Ti6Al4V; (b) Ti6Al7Nb

The surface morphologies were examined after hydrothermal treatment in distilled water (pH=7) and a KOH solution (pH=11), as is shown in Figure 2. After the hydrothermal treatment in distilled water, Ti6Al4V demonstrates a different morphology than Ti6Al7Nb. After that treatment Ti6Al4V surface is characterized by grainy HA crystals on the surface and needle-like HA crystals inside the pores (Figure 2a). On the other hand, the surface of Ti6Al7Nb is mainly characterized by plate-shaped HA crystals localized inside the pores and also needle-like HA crystals localized both inside the pores and also on the surface (Figure 2b). For both cases the crystals are distributed uniformly on the surface.

Likewise, after hydrothermal treatment of both alloys in a KOH solution demonstrate different morphologies. For Ti6Al4V the surface is characterized by an ununiform plate-shaped HA crystals inside the pores and an approximately smooth surface outside the pores with no crystals at all

(Figure 2c). In contrast to that, Ti6Al7Nb surface is characterized by an ununiform plate-shaped HA crystals inside the pores and a uniform mixture of grainy and needle-like crystals on the surface (Figure 2d).

(a)

(b)

(c)

(d)

Figure 2. Surface morphologies of coatings after hydrothermal treatment: (a) Ti6Al4V pH=7; (b) Ti6Al7Nb pH=7; (c) Ti6Al4V pH=11; (d) Ti6Al7Nb pH=11

The surface morphologies were examined also by SEM images of the alloys after exposing a cross sectional area by FIB. Example for these images is shown in Figure 3.

Figure 3. Surface morphologies of coatings after hydrothermal treatment, pH=7: (a) Ti6Al4V; (b) Ti6Al7Nb

3.2 Energy dispersive spectroscopy (EDS)

The elemental composition (%atomic) obtained by EDS spectra is given in Table 2.

Table 2. Elemental composition (EDS) of coating after PEO and hydrothermal treatments

Treatment	Titanium alloy	Ti	Al	Nb/V	O	Ca	P	C
PEO	Ti6Al4V	15.1	1.6	0.6	63.3	8.6	5.7	5.2
	Ti6Al7Nb	11.0	1.3	0.4	58.4	7.5	4.6	16.9
HTT pH=7	Ti6Al4V	15.8	1.9	0.4	65.4	7.6	4.6	4.3
	Ti6Al7Nb	17.6	2.1	0.6	69.8	5.2	4.7	-
HTT pH=11	Ti6Al4V	15.5	1.6	0.4	59.9	11.6	5.8	7.7
	Ti6Al7Nb	14.5	2.1	0.6	65.3	6.1	5.1	6.4

Table 2 shows that the coating contains mainly titanium and oxygen as it is a film of titanium oxide. there also are some additional elements like aluminum and vanadium or niobium, which are originated from the substrates, and calcium, phosphorus and carbon originated from the electrolyte.

3.3 X-Ray diffraction (XRD)

Figure 4 shows XRD spectra of the surface film for substrates and different treatments. It can be seen that for both alloys there is no presence of HA after PEO but it does appear after both kinds of the hydrothermal treatments. additionally, an amorphous phase is present after PEO for both alloys, but not after the hydrothermal treatments. The phase compositions are summarized in Table 3.

Figure 4. XRD spectra acquired from the coatings: (a) Ti-6Al-4V and (b) Ti-6Al-7Nb

Table 3. Phase composition of coating after PEO and hydrothermal treatments

Treatment	Ti6Al7Nb	Ti6Al4V
PEO	TiO ₂ - rutile, anatase	TiO ₂ - rutile, anatase
	Amorphous phase	Ca ₃ (PO ₄) ₂
		Amorphous phase
HTT pH=7	TiO ₂ -anatase	TiO ₂ - rutile, anatase
	HA	HA
HTT pH=11	TiO ₂ -anatase	TiO ₂ - rutile, anatase
	HA	HA

3.4 Coating thickness measurements

The thickness of the coating on samples was determined by two different methods (Table 4): by using a thickness gauge and by using a scanning electron microscope after exposing a cross sectional area by FIB. The measurements using both thickness gauge and SEM reveal a higher thickness for the coating of Ti6Al4V than that of Ti6Al7Nb, but also a higher standard deviation for the coating of Ti6Al4V which shows ununiform thickness for Ti6Al4V and a thin uniform coating for Ti6Al7Nb.

Table 4. Thickness of the coatings on titanium alloys

Titanium alloy	Treatment	Method	
		Average coating thickness by SEM [μm]	Average coating thickness by thickness gauge [μm]
Ti6Al4V	PEO	6.36±1.23	9.35±1.01
	HTT pH=7	8.49±1.02	8.84±1.12
	HTT pH=11	7.01±0.93	9.52±1.15
Ti6Al7Nb	PEO	2.75±0.36	2.84±0.28
	HTT pH=7	3.17±0.11	2.45±0.17
	HTT pH=11	3.00±0.63	2.65±0.43

3.5 Roughness measurements by AFM

3D AFM images of Ti6Al4V and Ti6Al7Nb after PEO and hydrothermal treatments are shown in Figure 5. The values of average roughness (R_a) are listed in Table 5. R_a values are higher for Ti6Al7Nb for all treatments and these results support AFM and SEM images, which exhibit a developed surface with plate-shaped HA crystals inside pores and grainy crystals on the surface.

Figure 5. 3D AFM images: (a) Ti6Al4V after PEO; (b) Ti6Al4V after HTT pH=7; (c) Ti6Al4V after HTT pH=11; (d) Ti6Al7Nb after PEO; (e) Ti6Al7Nb after HTT pH=7; (f) Ti6Al7Nb after HTT pH=11

Table 5. R_a values for Ti6Al4V and Ti6Al7Nb surface after PEO and hydrothermal treatments

Titanium alloy	Treatment	R_a [nm]
Ti6Al4V	PEO	83.1
	HTT pH=7	115.7
	HTT pH=11	55.4
Ti6Al7Nb	PEO	232.7
	HTT pH=7	175.3
	HTT pH=11	234.7

3.6 Electrochemical characterization

Polarization curves were measured between $\pm 250\text{mV}$ at the scan rate of 1mV/s and linear polarization measurements (LPR) were performed in a range of $\pm 10\text{mV}$ at the scan rate of 0.5mV/s . Corrosion parameters such as J_{corr} - current density; I_{corr} -corrosion current and R_p - corrosion resistance were evaluated (Table 6). It can be seen from Table 6 that the corrosion currents are significantly small and the corrosion resistance is significantly high, as it is known for titanium alloys and titanium oxide. Furthermore, passivation is observed for Ti6Al7Nb in both solutions.

Table 6. Corrosion parameters for Ti6Al4V and Ti6Al7Nb in Hanks' and saliva solution

Titanium alloy and treatment	Solution	LPR			Tafel		
		Parameters	J_{corr} [A/cm ²]	I_{corr} [A]	R_p [Ω]	J_{corr} [A/cm ²]	I_{corr} [A]
Ti6Al4V PEO	Hanks'		$3.76 \cdot 10^{-7}$	$3.58 \cdot 10^{-7}$	$1.57 \cdot 10^5$	$2.31 \cdot 10^{-7}$	$2.19 \cdot 10^{-7}$
	Saliva		$2.91 \cdot 10^{-8}$	$2.76 \cdot 10^{-8}$	$8.71 \cdot 10^4$	$2.63 \cdot 10^{-8}$	$2.50 \cdot 10^{-8}$
Ti6Al7Nb PEO	Hanks'		$2.66 \cdot 10^{-6}$	$2.53 \cdot 10^{-6}$	$2.27 \cdot 10^4$	$1.32 \cdot 10^{-6}$	$1.26 \cdot 10^{-6}$
	Saliva		-	-	$1.43 \cdot 10^6$	passivation	
Ti6Al4V HTT pH=7	Hanks'		$5.16 \cdot 10^{-7}$	$4.90 \cdot 10^{-7}$	$7.95 \cdot 10^4$	$2.83 \cdot 10^{-7}$	$2.69 \cdot 10^{-7}$
	Saliva		$2.06 \cdot 10^{-7}$	$1.96 \cdot 10^{-7}$	$1.96 \cdot 10^5$	$1.02 \cdot 10^{-7}$	$9.68 \cdot 10^{-8}$
Ti6Al7Nb HTT pH=11	Hanks'		-	-	$1.48 \cdot 10^5$	passivation	
	Saliva		-	-	$4.76 \cdot 10^5$	passivation	
Ti6Al4V HTT pH=7	Hanks'		$1.38 \cdot 10^{-6}$	$1.31 \cdot 10^{-6}$	$3.62 \cdot 10^4$	$1.23 \cdot 10^{-6}$	$1.17 \cdot 10^{-6}$
	Saliva		$2.44 \cdot 10^{-7}$	$2.32 \cdot 10^{-7}$	$1.92 \cdot 10^5$	$1.30 \cdot 10^{-7}$	$1.24 \cdot 10^{-7}$
Ti6Al7Nb HTT pH=11	Hanks'		-	-	$1.15 \cdot 10^6$	passivation	
	Saliva		-	-	$1.22 \cdot 10^6$	passivation	

5. Conclusions

Ti6Al4V and Ti6Al7Nb alloys were characterized in terms of surface morphologies, elemental and phases composition, coating thickness, roughness and corrosion behavior after treated by PEO and hydrothermally.

- Hydroxyapatite-containing surfaces can be attained by the two-stage procedure, PEO and HTT, for both alloys.
- Using the same parameters, different coating thicknesses are attained for the two competing alloys. For Ti6Al4V the thickness is not even as compared to Ti6Al7Nb.
- The most developed surface with plate-shaped HA crystals was obtained for Ti6Al7Nb after HTT in distilled water.
- The surface roughness increased after PEO for both alloys, although the roughness of Ti6Al7Nb is higher.
- Corrosion tests showed passivation for all samples of Ti6Al7Nb after were treated hydrothermally on both solutions.
- According to the results of this study, the Ti6Al7Nb alloy may be preferred over Ti6Al4V, thereby avoiding the use of vanadium toxicity.

References

1. Srimaneepong, V.; Yoneyama, T.; Kobayashi, E.; Doi, H.; Hanawa, T. Comparative study on torsional strength, ductility and fracture characteristics of laser-welded $\alpha + \beta$ Ti-6Al-7Nb alloy, CP Titanium and Co-Cr alloy dental castings. *Dent. Mater.* **2008**, *24*, 839-845, DOI: 10.1016/j.dental.2007.10.002.
2. Lugovskoy, A.; Lugovskoy, S. Production of hydroxyapatite layers on the plasma electrolytically oxidized surface of titanium alloys. *Mater. Sci. Eng.* **2014**, *C. 43*, 527-532, DOI:10.1016/j.msec.2014.07.030.
3. Pan, J.; Thierry, D.; Leygraf, C. Electrochemical impedance spectroscopy study of the passive oxide film on titanium for implant application. *Electrochim Acta* **1996**, *41*, 1143-53.
4. Okazaki, Y.; Ito, Y.; Kyo, K.; Tateishi, T. Corrosion resistance and corrosion fatigue strength of new titanium alloys for medical implants without V and Al, *Mater. Sci. Eng.* **1996**, *A. 213*, 138-147, DOI:10.1016/0921-5093(96)10247-1.

5. Elias, C.N.; Fernandes, D.J.; Resende, C.R.S.; Roestel, J. Mechanical properties, surface morphology and stability of a modified commercially pure high strength titanium alloy for dental implants. *Dent. Mater.* **2015**, *31*, e1–e13, DOI:10.1016/j.dental.2014.10.002.
6. Tamilselvi, S.; Raman, V.; Rajendran, N.; Corrosion behaviour of Ti-6Al-7Nb and Ti-6Al-4V ELI alloys in the simulated body fluid solution by electrochemical impedance spectroscopy. *Electrochim. Acta.* **2006**, *52*, 839–846, DOI:10.1016/j.electacta.2006.06.018.
7. Rajapakse, R.M.G.; Wijesinghe, W.P.S.L. Preparation of bone-implants by coating hydroxyapatite nanoparticles on self-formed titanium dioxide thin-layers on titanium metal surfaces. *Mater. Sci. Eng.* **2016**, *C. 63*, 172–184, DOI:10.1016/j.msec.2016.02.053.
8. Adeleke, S.A.; Sopyan, I.; Bushroa, A.R. Hydroxyapatite Layer Formation on Titanium Alloys Surface Using Micro-Arc Oxidation. *ARPJ. Eng. Appl. Sci.* **2015**, *10*, 10101–10108.
9. Ibrahim, M.Z.; Sarhan, A.A.D.; Yusuf, F.; Hamdi, M. Biomedical materials and techniques to improve the tribological, mechanical and biomedical properties of orthopedic implants – A review article. *J. Alloys Compd* **2017**, *714*, 636–667, DOI:10.1016/j.jallcom.2017.04.231.
10. Kossenko, A.; Lugovskoy, S.; Astashina, N.; Lugovskoy, A.; Zinigrad, M. Effect of Time on the Formation of Hydroxyapatite in PEO Process with Hydrothermal Treatment of the Ti – 6Al – 4V Alloy. *Glas. Phys. Chem.* **2013**, *39*, 639–642, DOI:10.1134/S1087659613060072.
11. Esen, Z.; Öcal, E.B. Surface characteristics and in-vitro behavior of chemically treated bulk Ti6Al7Nb alloys. *Surf. Coatings Technol.* **2017**, *309*, 829–839, DOI:10.1016/j.surfcoat.2016.10.078.
12. Zhu, X.; Chen, J.; Scheideler, L.; Reichl, R.; Geis-Gerstorfer, J. Effects of topography and composition of titanium surface oxides on osteoblast responses. *Biomaterials* **2004**, *25*, 4087–4103, DOI:10.1016/j.biomaterials.2003.11.011.
13. SIGMA-ALDRICH. Available online: <https://www.sigmaaldrich.com/content/dam/sigma-aldrich/docs/Sigma/Formulation/d5796for.pdf>.
14. PICKERING LABORATORIES. Available online: <https://www.pickeringlabs.com/wp-content/uploads/sds/SDS%2017000305%20Artificial%20Saliva%20for%20Medical%20and%20Dental%20Research.pdf>