

1 *Data Descriptor*

2 **Waste to Carbon: Preliminary Research on** 3 **Mushroom Spent Compost Torrefaction**

4 **Ewa Syguła**¹, **Jacek A. Koziel**², and **Andrzej Białowiec**^{1,2*}

5 ¹ Faculty of Life Sciences and Technology, Institute of Agricultural Engineering, Wrocław University of
6 Environmental and Life Sciences, 37/41 Chelmońskiego Str., 51-630 Wrocław, Poland;
7 ewwwrock7@gmail.com, andrzej.bialowiec@upwr.edu.pl

8 ² Department of Agricultural and Biosystems Engineering, Iowa State University, Ames, IA 50011, USA,
9 koziel@iastate.edu, andrzejb@iastate.edu

10 * Correspondence: andrzej.bialowiec@upwr.edu.pl; Tel.: +48-71-320-5973;

11 Received: date Accepted: date; Published: date

12 **Abstract:** Mushroom production in Poland is an important and dynamically developing element of
13 diverse agriculture. Mushroom spent compost (MSC) is major waste generated during production,
14 i.e., MSC: mushrooms is ~5:1. To date, the main use of MSC is soil application as organic fertilizer.
15 To date, several methods of MSC treatment have been researched and developed including
16 production of compost, bioethanol, biogas, enzyme lactase, xylo-saccharides, and hydrogen.
17 Torrefaction may be considered a novel approach for biomass valorization. Thus, we are pioneering
18 the potential use of MSC valorization via torrefaction. We explored valorizing the waste biomass of
19 MSC via thermal treatment – torrefaction ('roasting') to produce biochar with improved fuel
20 properties. Here for the first time, we examined and summarized the MSC torrefaction
21 thermogravimetric analyses, fuel properties data of raw biomass of MSC and biochars generated
22 from MSC via torrefaction. The effects of torrefaction temperature (200~300 °C), process time (20~60
23 min), on fuel properties of the resulting biochars were summarized. The dataset contains results of
24 thermogravimetric analysis (TGA) as well as proximate analyses of MSC and generated biochars.
25 The presented data are useful in determining MSC torrefaction reaction kinetics, activation energy
26 and to further techno-economical modeling of the feasibility of MSC valorization via torrefaction.
27 MSC torrefaction could be exploited as part of valorization resulting from a synergy between an
28 intensive mushroom production with the efficient production of high-quality renewable fuel.

29 **Dataset:** This dataset is available in the supplementary file 'Data_MSC_torrefaction.xlsx.zip'.

30 **Dataset License:** CC-BY

31 **Keywords:** mushrooms; mushroom spent compost; renewable energy; biochar; biomass
32 valorization; torrefaction; fuel properties; proximate analysis; carbon sequestration
33

34 1. Summary

35 Poland is the largest grower of mushrooms in Europe and the third in the world. The production
36 of mushrooms in Poland is growing rapidly and has become an important branch of regional
37 agriculture. The production of mushrooms increased from 196 thousand Mg·year⁻¹ to 325
38 thousand Mg·year⁻¹ from 2006 to 2018, which currently accounts for ~24% of the total production in
39 European Union [1,2]. One of the residual wastes generated during the cultivation is mushroom
40 spent compost (MSC, low nutrient substrate), which accounts as 5:1 MSC: mushrooms (kg·kg⁻¹)
41 [3]. This waste amounts to ~5,527 thousand Mg·year⁻¹ of MSC [1]. It is estimated that the MSC [4]
42 generation may reach up to 1.3 million tons per year in Poland by year 2018 [1]. MSC is classified
43 according to European Waste Classification, as an industrial waste (02 01 99 code), which belongs to

44 the group of wastes from agriculture, horticulture, hydroponics, fisheries, forestry, hunting and food
45 processing [5].

46 Potential MSC waste treatment methods result from its properties. For example, a white
47 mushroom (*Agaricus bisporus*) is grown on a soil consisting mainly straw and chickens' manure.
48 Poultry manure also contains gypsum, urea, peat, coconut, and soy proteins [6]. The production cycle
49 of mushrooms on this bedding takes 6 to 8 weeks, during which, three harvests of mushrooms may
50 be obtained. After this period, the MSC cannot be regenerated and used again for production. It is a
51 waste which requires to be treated [7].

52 To date, several methods of managing of MSC have been developed and used. Those methods
53 were aimed to obtain compost [7], bioethanol [8], biogas [9], enzyme lactase [4], xylo-saccharides [10],
54 or hydrogen [11]. Torrefaction may be considered a novel approach for biomass valorization [12].
55 Thus, we are pioneering the potential use of MSC valorization via torrefaction.

56 Torrefaction is sometimes called a 'low temperature pyrolysis' in the range of 200-300 °C [13].
57 The process residence time depends on many factors, such as the moisture or volatile content, as well
58 as the type of reactor or substrate [14]. The residence time usually does not exceed 60 min. The
59 products of torrefaction are: solid biochar and gas 'torgas'. Torgas consists non-flammable and
60 flammable gases such as water vapor, CO₂, CO, CH₄ and H₂ [15]. The ratio of flammable to non-
61 flammable gases depends on process and substrate parameters [13]. Thus, torgas is a less attractive
62 product of torrefaction compared with biochar [16,17]. The solid product of the torrefaction – biochar,
63 could be considered as a renewable source of energy according to Polish law if its calorific value is
64 >21 MJ·kg⁻¹ d.m. and the feedstock originates from solid biomass and biowaste [18].

65 During the torrefaction process the loss of mass as well the loss of chemical energy from raw
66 material is observed. However, the degree of mass loss is higher (30-40%) than the energy loss (10%).
67 and the energy densification in solid fuels (biochars) occurs [13]. To date, research has been carried
68 out on the torrefaction of the following wastes: parts of industrial and municipal wastes [19, 20],
69 sewage sludge derived from wastewater treatment [21]. Also, the brewers' spent grain [22], oxytree
70 biomass [23] straw, woodchips, olives waste, Virginia mallow have already been torrefied [24].

71 To date, the torrefaction of MSC has not been attempted yet. This dataset includes the novel
72 results of properties including thermogravimetric analyses (TGA), proximate properties of MSC and
73 generated biochars. The presented data are useful in determining the MSC torrefaction reaction
74 kinetics and to further the techno-economical modeling of the feasibility of MSC valorization via
75 torrefaction, including a comparison with other torrefied types of biomass and waste.

76 2. Data Description

77 2.1. The properties of raw MSC

78 The raw biomass of MSC was characterized for moisture content, volatile solids (VS) and ash
79 content, and higher heating value (HHV) (Table 1).
80

81 Table 1. The properties of raw MSC

Parameter	Unit	Mean ± Standard Deviation
Moisture	%	65.32 ± 0.05
VS	% d.m.	71.60 ± 2.31
Ash	% d.m.	28.40 ± 2.31
HHV	MJ·kg ⁻¹ d.m.	13.79 ± 0.50

82
83 The obtained data are presented in the Supplementary Material file "MSC torrefaction data.xlsx"
84 in six sheets summarizing properties of raw and torrefied MSC (biochars):

- 85 • Read me (guide)
- 86 • MSC Moisture (2nd sheet)
- 87 • Higher Heating Value (3rd sheet)
- 88 • Volatile Solids (4th sheet)

- 89 • Ash (5th sheet)
90 • TGA (6th sheet).
91 The first “Read me” sheet is a guide on how to read the data with short information about each
92 type of treatment.

93 3. Methods

94 The samples of MSC originated from mushroom farm in Gogołowo, Poland. Before the
95 experiment, MSC samples were dried for 24 h in a WAMED laboratory dryer, model KBC-65W
96 (Warsaw, Poland) at 105 °C. Then, dry MSC sample was ground through a 0.1 mm screen and the
97 laboratory knife mill TESTCHEM, model LMN-100 (Pszów, Poland).
98

99 3.1. The MSC torrefaction and biochar generation

100

101 The MSC torrefaction was carried out according to procedure described by Świechowski et al.
102 [23] in a muffle furnace (Snol 8.1/1100, Utena, Lithuania). CO₂ was used as an inert gas with a flow of
103 10 dm³·h⁻¹. The process was carried out at the setpoint temperatures of 200 °C to 300 °C with intervals
104 of 20 °C and 20, 40, and 60 min retention time. The samples were heated from 20 °C to the torrefaction
105 setpoint temperature at a 50 °C·min⁻¹ heating rate. The dry mass of the samples used for the tests was
106 10 g (± 0.5 g). The biochars were removed from the muffle furnace when the interior temperature was
107 lower than 200 °C. The approximate times of cooling from 300 °C, 280 °C, 260 °C, 240 °C, and 220 °C
108 to 200 °C were 38, 33, 29, 23, and 13.5 min, respectively. The approximate cooling time from 300 °C
109 to room temperature (~20 °C) was around 6 h. Analyses of three replicates were carried out.
110

111

112 3.2. MSC torrefaction - thermogravimetric analysis

113

114 The thermogravimetric analysis (TGA) of the MSC torrefaction process was conducted
115 according to the protocol described elsewhere [21]. Briefly, to ensure that the inert atmosphere was
116 maintained, the CO₂ gas was introduced from the bottom of the reactor at a rate of 0.6 mL·min⁻¹. The
117 investigated MSC sample was placed in the cuvette and introduced inside the reactor. The cuvette
118 was integrated with the electronic balance with 0.01 g resolution to enable the measurement of the
119 mass loss during the torrefaction process. The parameters of the torrefaction process were registered
120 by a PC and exported to a file. Approximately 2.25 g of dried MSC samples were placed in the reactor
121 and heated at constant temperatures of 200, 220, 240, 260, 280, and 300 °C for up to 1 h. Temperature
122 range and intervals were typical for torrefaction temperatures [26] and based on the methodology
123 described by Bialowiec et al. [19].
124

125

126 3.3. Proximate Analysis of raw MSC and biochars generated

127

128 Raw and torrefied MSC samples were tested in three replicates for:

129

- 130 • Moisture content, determined in accordance with [27], by means of the laboratory dryer
131 (WAMED, model KBC-65W, Warsaw, Poland).
- 132 • Volatile solids, determined in accordance with [28], by means of the SNOL 8.1/1100 muffle
133 furnace (Utena, Lithuania).
- 134 • The ash content, determined in accordance with [29], by means of the SNOL 8.1/1100 muffle
135 furnace (Utena, Lithuania).
- 136 • High heating value (HHV), determined in accordance with [30], by means of the IKA C2000
137 Basic calorimeter.

138 4. User Notes

139 The dataset represents a novel work on the MSC biomass torrefaction. The dataset consists of
140 results of raw MSC and biochars produced from MSC, i.e., fuel properties in relation to torrefaction

138 temperature and residence time in the reactor. The torrefaction TGA analyses results were given for
139 MSC biomass. These data can be used for calculating MSC torrefaction kinetics and activation energy
140 and can also be used to propose mathematical models describing the influence of torrefaction,
141 temperature, and residence time on fuel properties. The presented data may serve as reference values
142 for comparative analyses with other types of biomass and waste and renewable fuels from
143 agriculture.

144 **Supplementary Materials:** The following are available online at www.mdpi.com/xxx/s1, File S1:
145 Data_MSC_torrefaction.xlsx.zip.

146 **Author Contributions:** Conceptualization, A.B.; methodology, A.B., E.S.; software, E.S.; validation, E.S., A.B.,
147 and J.K.; formal analysis, E.S.; investigation, E.S.; resources, E.S., A.B., and J.K.; data curation, E.S., A.B.;
148 writing—original draft preparation, E.S., A.B.; writing—review and editing, E.S., A.B. and J.K.; supervision, A.B.
149 and J.K.; project administration, A.B.; funding acquisition, A.B., and J.K.

150 **Funding:** The authors would like to thank the Fulbright Foundation for funding the project titled “Research on
151 pollutants emission from Carbonized Refuse-Derived Fuel into the environment,” completed at the Iowa State
152 University. In addition, this paper preparation was partially supported by the Iowa Agriculture and Home
153 Economics Experiment Station, Ames, Iowa. Project no. IOW05556 (Future Challenges in Animal Production
154 Systems: Seeking Solutions through Focused Facilitation) sponsored by Hatch Act and State of Iowa funds.

155 **Conflicts of Interest.** The authors declare no conflict of interest. The funders had no role in the design of the
156 study; in the collection, analyses, or interpretation of data; in the writing of the manuscript; or in the decision to
157 publish the results.

158 References

- 159 1. Czop, M.; Kłapcia, E. Termiczne przekształcanie jako sposób zagospodarowania podłoża pieczarkowego
160 po zakończonym cyklu produkcyjnym ‘*Thermal transformation as a way of developing a mushroom substrate*
161 *after a completed production cycle*’. *Inżynieria i Ochrona Środowiska* **2016**, *19*(1), 67-80.
- 162 2. Kurczewski, R. Odpady organiczne, czyli resztki z pańskiego stołu ‘*Organic waste, or leftovers from your*
163 *table*’. Available online: [https://sozosfera.pl/ochrona-przyrody/odpady-organiczne-czyli-resztki-](https://sozosfera.pl/ochrona-przyrody/odpady-organiczne-czyli-resztki-panskiego-stolu/)
164 [panskiego-stolu/](https://sozosfera.pl/ochrona-przyrody/odpady-organiczne-czyli-resztki-panskiego-stolu/) (accessed on 01 June 2019)
- 165 3. Finney, K.N.; Ryu, C.; Sharifi, V.N.; Swithenbank J. The reuse of spent mushroom compost and coal tailings
166 for energy recovery: Comparison of thermal treatment technologies. *Bioresource Technology* **2009**, *100*, 310–
167 315.
- 168 4. Singha, A.; Bajara, S.; Bishnoia, N.R.; Singhb N. Laccase production by *Aspergillus heteromorphus* using
169 distillery spent wash and lignocellulosic biomass. *Journal of Hazardous Materials* **2010**, *176*, 1079–1082.
- 170 5. Commission regulation (EU) 2015/2002 of 10 November 2015 amending Annexes IC and V to Regulation
171 (EC) No 1013/2006 of the European Parliament and of the Council on shipments of waste (Text with EEA
172 relevance).
- 173 6. Becher, M. Skład chemiczny podłoża po uprawie pieczarki jako odpadowego materiału organicznego
174 ‘*Chemical composition of the substrate after cultivation of the mushroom as waste organic material*’. *Ekonomia i*
175 *Środowisko* **2013**, *4*(47), 207-213.
- 176 7. Kalembsa, D.; Becher, M.; Bik, B.; Makolewski A. Właściwości materii organicznej podłoża po uprawie
177 pieczarki ‘*Properties of the organic matter of the substrate after growing the mushrooms*’. *Acta Agrophysica* **2012**,
178 *19*(4), 713-723.
- 179 8. Kapu, N.U.S.; Manning, M.; Hurley, T.B.; Voigt, J.; Cosgrove, D.J.; Romaine, C.P. Surfactant-assisted
180 pretreatment and enzymatic hydrolysis of spent mushroom compost for the production of sugars.
181 *Bioresource Technology* **2012**, *114*, 399–405.
- 182 9. Bisaria, R.; Vasudevan, P.; Bisaria, V.S. Utilization of spent agro-residues from mushroom cultivation for
183 biogas production. *Applied Microbiology and Biotechnology* **1990**, *33*(5), 607–609.
- 184 10. Sato, N.; Shinji, K.; Mizuno, M.; Nozaki, K.; Suzuki, M.; Makishima, S.; Shiroish, M.; Onoda, T.; Takahashi,
185 F.; Kanda, T.; Amano Y. Improvement in the productivity of xylooligosaccharides from waste medium after
186 mushroom cultivation by hydrothermal treatment with suitable pretreatment. *Bioresource Technology* **2010**,
187 *101*, 6006–6011.

- 188 11. Ya-Chieh, L.; Shu-Yii, W.; Chen-Yeon, C.; Hsin-Chieh, H. Hydrogen production from mushroom farm
189 waste with a two-step acid hydrolysis process. *International Journal of Hydrogen Energy* **2011**, *36*, 14245 -
190 14251.
- 191 12. Phanphanich, M.; Mani, S. Impact of torrefaction on the grindability and fuel characteristics of forest
192 biomass. *Bioresour. Technol.* **2011**, *102*, 1246–1253, doi:10.1016/j.biortech.2010.08.028.
- 193 13. Kopczyński, M.; Zuwała, J. Biomasa toryfikowana - nowe paliwo dla energetyki 'Torrefied biomass - a new
194 fuel for the power industry'. *CHEMIK* **2013**, *67(6)*, 540-551.
- 195 14. Bajpai, P. Pretreatment of Lignocellulosic Biomass for Biofuel Production. SpringerBriefs in Green
196 Chemistry for Sustainability, Springer, Singapore, 2016, XI, 87, ISBN 978-981-10-0687-6, doi: 10.1007/978-
197 981-10-0687-6.
- 198 15. Basu, P. Biomass Gasification, pyrolysis and torrefaction: practical design and theory. Third Edition,
199 Elsevier, Halifax, Canada **2013**, 44-139.
- 200 16. Kordylewski, W.; Tatarek, A. Wybrane właściwości toryfikatów z krajowych i importowanych biomas
201 'Selected properties of tbiochars from domestic and imported biomass'. *Archiwum Spalania* **2012**, *12*, 3.
- 202 17. Jakubiak, M.; Kordylewski, W.; Torfikacja biomasy 'Biomass torrefaction'. *Polski Instytut Spalania*, **2010**, *10*,
203 11-25.
- 204 18. The Directive of Parliament of the Republic of Poland on Renewable Energy Sources. *Journal of Law from*
205 *the 2018 year*, item 2389.
- 206 19. Białowiec, A.; Pulka, J.; Gołaszewski, J.; Manczarski, P.; Stępień, P. The RDF torrefaction: An effect of
207 temperature on characterization of the product - Carbonized Derived Fuel. *Waste Manag.* **2017**, *70*, 91–100,
208 doi:10.1016/j.wasman.2017.09.02
- 209 20. Białowiec, A.; Micuda, M.; Koziel, J.A. Waste to Carbon: Densification of Torrefied Refuse-Derived
210 Fuel. *Energies* **2018**, *11*, 3233.
- 211 21. Pulka, J.; Manczarski, P.; Koziel, J.A.; Białowiec, A. Torrefaction of Sewage Sludge: Kinetics and Fuel
212 Properties of Biochars. *Energies* **2019**, *12*, 565.
- 213 22. Dudek, M.; Świechowski, K.; Manczarski, P.; Koziel, J.A.; Białowiec, A. The Effect of Biochar Addition on
214 the Biogas Production Kinetics from the Anaerobic Digestion of Brewers' Spent Grain. *Energies* **2019**, *12*,
215 1518.
- 216 23. Świechowski, K.; Liszewski, M.; Bąbelewski, P.; Koziel, J.A.; Białowiec, A. Fuel Properties of Torrefied
217 Biomass from Pruning of Oxytree. *Data* **2019**, *4*, 55.
- 218 24. Zuwała, J.; Kopczyński, M.; Kazalski, K. Koncepcja systemu uwierzytelniania biomasy toryfikowanej w
219 perspektywie wykorzystania paliwa na cele energetyczne 'The concept of a biomass authentication
220 system in the perspective of using fuel for energy purposes'. *Polityka energetyczna* **2015**, *18(4)*, 89–100.
- 221 25. Pulka, J.; Manczarski, P.; Koziel, J.A. Torrefaction of Sewage Sludge : Kinetics and Fuel Properties of
222 Biochars. *Energies* **2019**, *12*, 565, doi:10.3390/en12030565
- 223 26. Bergman, P.C.A.; Kiel, J.H.A. Torrefaction for biomass upgrading. In Proceedings of the 14th European
224 Biomass Conference & Exhibition, Paris, France, 17–21 October 2005.
- 225 27. Polish Committee for Standardization. PN-EN 14346:2011 Standard. Waste characteristics. Calculation of
226 Dry Mass on the Basis of Dry Residue or Water Content. Available online:
227 [https://infostore.saiglobal.com/en-au/Standards/PN-EN-14346-2011-
228 932471_SAIG_PKN_PKN_2197939/](https://infostore.saiglobal.com/en-au/Standards/PN-EN-14346-2011-932471_SAIG_PKN_PKN_2197939/) (accessed on 01 June 2019).
- 229 28. Polish Committee for Standardization. PN-EN 15169:2011 Standard. Waste characteristics. Determination
230 of Organic Matter Content for Waste, Slurry and Sludge. Available online: [http://sklep.pkn.pl/pn-en-
231 15169-2011p.html](http://sklep.pkn.pl/pn-en-15169-2011p.html) (accessed on 01 June 2019).
- 232 29. Polish Committee for Standardization. PN-Z-15008-04:1993 Standard. Municipal solid waste. Analysis of
233 combustible and non-combustible content. Available online: <http://sklep.pkn.pl/pn-z-15008-04-1993p.html>
234 (accessed on 01 June 2019).
- 235 30. Polish Committee for Standardization. PN-G-04513:1981 Standard. Solid fuels. Determination of the higher
236 heating value and the lower heating value. Available online: <http://sklep.pkn.pl/pn-g-04513-1981p.html>
237 (accessed on 01 June 2019).