

Article

Metal-Insulator Transition in Three-Dimensional Semiconductors

Klaus Ziegler¹ ¹ Institut für Physik, Universität Augsburg, D-86135 Augsburg, Germany

Abstract: We use a random gap model to describe a metal-insulator transition in three-dimensional semiconductors due to doping and find a conventional phase transition, where the effective scattering rate is the order parameter. Spontaneous symmetry breaking results in metallic behavior, whereas the insulating regime is characterized by the absence of spontaneous symmetry breaking. The transition is continuous for the average conductivity with critical exponent equal to 1. Away from the critical point the exponent is roughly 0.6, which may explain experimental observations of a crossover of the exponent from 1 to 0.5 by going away from the critical point.

Keywords: particle-hole symmetry, metal-insulator transition, random gap model

1. Introduction

The particle-hole symmetry plays a crucial role in solid state physics. In particular in semi- as well as in superconductor physics [1], this symmetry appears due to the existence of two separate bands. Recent theoretical studies of three-dimensional Weyl materials has renewed interest in the disordered driven metal-insulator transition [2–26]. It was shown recently that Anderson localization can be prevented even in the strong disorder regime when particle-hole symmetry is present [27,28]. This can be understood by the simple picture that particle-hole pairs can be created by an infinitesimal excitation energy.

Undoped semiconductors have a small gap between the valence and the conduction band, typically of the order of 0.2...1.2 eV [1]. This gap is strongly affected by doping, which allows us to engineer a variety of useful technological applications. In particular, sufficiently strong doping closes the gap such that a metallic phase appears. A classical example for this type of metal-insulator transition is doped silicon, where typical dopants are phosphorus (Si:P) or boron (Si:B) [29–33]. Disorder plays a crucial role in these materials due to the inhomogeneous distribution of the dopants. This suggested that Anderson localization must play a crucial role in these systems, where the quantum states would undergo a transition from extended to localized states for increasing disorder. This transition should be reflected in the transport properties, where extended states lead to a metal and localized states to an insulator at vanishing temperatures.

Measurements of the conductivity $\sigma(N)$ as a function of doping concentration N in Si:P at low temperatures has indeed revealed a critical behavior. Above a critical concentration N_c a power law was found

$$\sigma(N) \sim \sigma_0(N/N_c - 1)^\mu \quad (N \geq N_c)$$

and a vanishing conductivity for $N \leq N_c$. The exponent μ was determined as $\mu \approx 0.5$ for some experiments [29–32], whereas a crossover from $\mu \approx 0.5$ at some distance from the critical point to $\mu \approx 1$ in a vicinity very close to N_c was observed in other experiments [32,33].

Although the picture of an Anderson transition is quite appealing, an alternative description can be provided by a random gap model. The idea is that the dopants create energy levels inside

the semiconductor gap. These levels are associated with states that can overlap with the states in the semiconductor bands and eventually fill the semiconductor gap by forming extended states. The effect can be described by a random distribution of local gaps. Then the locally filled gaps can be distributed over the entire system and form eventually, after sufficient doping, a conducting “network”. This is associated with a second-order phase transition which will be described in this article. The transition is distinguished from the Anderson transition by the fact that the metallic phase appears at strong disorder (i.e. high dopant concentration) and the insulating phase at weak disorder. This does not rule out an Anderson transition if we increase the disorder inside the metallic regime. However, in realistic systems it is more likely to see the transition caused by the random gap than the more sophisticated Anderson transition for $N \gg N_c$.

In the following, we will discuss and analyze the insulator-metal transition due to random gap closing in a three-dimensional system. This will be based on a two-band model with particle-hole symmetry. The latter is essential for the existence of metallic states in the presence of strong disorder.

2. Model and symmetries

We consider a two-band model with a symmetric Hamiltonian. This can be expressed in terms of Pauli matrices σ_j ($j = 0, \dots, 3$). A simple case is

$$H = h_1\sigma_1 + h_3\sigma_3 \quad (1)$$

with symmetric matrices h_1, h_3 in three-dimensional (real) space. To be more specific, we can choose the Fourier components $h_1 = k/\sqrt{2m}$ with $k \equiv \sqrt{k_1^2 + k_2^2 + k_3^2}$. For a uniform gap Δ implies $h_3 = \Delta/2$ we obtain two bands with the dispersion $E_{\mathbf{k}} = \pm\sqrt{k^2/2m + \Delta^2/4}$. Subsequently we will consider a random gap h_3 with mean values $\Delta/2$ to describe the effect of an inhomogeneous distribution of dopants and rescale $k/\sqrt{2m} \rightarrow k$.

The one-particle Hamiltonian H is invariant under an Abelian chiral transformation:

$$e^{\alpha\sigma_2} H e^{\alpha\sigma_2} = H. \quad (2)$$

In order to reveal the relevant symmetry for transport in this system, we construct the two-body Hamiltonian

$$\hat{H} = \begin{pmatrix} H & 0 \\ 0 & H \end{pmatrix}, \quad (3)$$

where the upper block H acts on bosons and the lower block H on fermions. The reason for introducing this two-body Hamiltonian is that we can transform the distribution of the random Hamiltonian H into a distribution of the Green's function $\hat{G}(z) = (\hat{H} - z)^{-1}$ [34,35], which is often called a supersymmetric representation of the Green's function.

Next we introduce the transformation matrix

$$\hat{U} = \begin{pmatrix} 0 & \varphi\sigma_2 \\ \varphi'\sigma_2 & 0 \end{pmatrix} \quad (4)$$

and obtain the anti-commutator relation

$$\{\hat{H}, \hat{U}\}_+ = 0. \quad (5)$$

This implies the non-Abelian chiral symmetry

$$e^{\hat{U}} \hat{H} e^{\hat{U}} = \hat{H}, \quad (6)$$

55 which is an extension of the Abelian symmetry (2). The Green's function $\hat{G}(z)$ does not obey this
 56 symmetry for $z \neq 0$. Therefore, z plays here the role of a symmetry-breaking field. An interesting limit
 57 is $z \rightarrow 0$, which we will study in the next section.

Now we consider the case of a random gap with mean $\langle h_{3,r} \rangle = \Delta/2$ and variance $\langle h_{3,r} h_{3,r'} \rangle - \Delta^2/4 = g\delta_{r,r'}$ and its effect on the average conductivity at frequency ω . The conductivity is obtained from the Kubo formula as [35,36]

$$\sigma_{kk} = -\frac{e^2}{2h} \omega^2 \lim_{\epsilon \rightarrow 0} \text{Re} \left\{ \sum_{\mathbf{r}} r_k^2 \text{Tr}_2 [\langle G_{0\mathbf{r}}(\omega/2 + i\epsilon) G_{\mathbf{r}0}(-\omega/2 - i\epsilon) \rangle] \right\}, \quad G(z) = (H - z)^{-1}. \quad (7)$$

58 In particular, we are interested in the DC limit $\omega \rightarrow 0$. This limit restores the chiral symmetry of \hat{H} in
 59 (6) for the Green's functions. However, the symmetry can be spontaneously broken now. Since it is a
 60 continuous symmetry, this creates a massless mode, which represents fluctuations on arbitrarily large
 61 length scales.

62 Here it should be noticed that $\sigma_2(H+z)^{-1}\sigma_2 = -(H-z)^{-1}$. This has the consequence that the
 63 product in (7) reads $G_{0\mathbf{r}}(z)G_{\mathbf{r}0}(-z) = (H-z)_{0\mathbf{r}}^{-1}(H+z)_{\mathbf{r}0}^{-1} = -(H-z)_{0\mathbf{r}}^{-1}\sigma_2(H-z)_{\mathbf{r}0}^{-1}\sigma_2$ such that
 64 elements of $\hat{G}(\omega/2 + i\epsilon)$ are sufficient to express the conductivity.

A common approximation for the average two-particle Greens function is the factorization of the average

$$\langle G_{0\mathbf{r}}(\omega/2 + i\epsilon) G_{\mathbf{r}0}(-\omega/2 - i\epsilon) \rangle \approx \langle G_{0\mathbf{r}}(\omega/2 + i\epsilon) \rangle \langle G_{\mathbf{r}0}(-\omega/2 - i\epsilon) \rangle \quad (8)$$

65 and a subsequent self-consistent Born approximation for the two factors. There are corrections though,
 66 which might be divergent [35,36]. The reason is that the expression on the left-hand side decays like a
 67 power law with distance r while the expression on the right-hand side decays exponentially. The power
 68 law is a consequence of the massless mode associated with the spontaneously broken non-Abelian
 69 symmetry. This problem will be discussed and solved in Sect. 4.

70 3. Self-consistent approximation

We start with the self-consistent Born approximation of the average one-particle Green's function

$$\langle G(z) \rangle \approx G_0(z + i\eta), \quad G_0(z) = (\langle H \rangle - z)^{-1}, \quad (9)$$

where the self-energy η is a scattering rate, which is determined by the self-consistent equation $i\eta = G_{0,0}(z + i\eta)$ [37]. This reads in our case with momentum cut-off λ

$$i\eta = \gamma(z + i\eta) \left[\lambda - \frac{\alpha}{2} \log \left(\frac{\alpha + \lambda}{\alpha - \lambda} \right) \right] \quad (\gamma = g/2\pi^2, \quad \alpha = \sqrt{(z + i\eta)^2 - \Delta^2/4})$$

and for $z = 0$ this simplifies to the relation $\eta = \eta I$ with

$$I = \gamma [\lambda - \beta \arctan(\lambda/\beta)], \quad \beta = \sqrt{\eta^2 + \Delta^2/4}.$$

In this case there are two solutions of the self-consistent equation, namely $\eta = 0$ and $\eta \neq 0$ with

$$\gamma = \frac{1}{\lambda - \beta \arctan(\lambda/\beta)}. \quad (10)$$

A nonzero η reflects spontaneous symmetry breaking with respect to (6). Such a solution exists for (10) only at sufficiently large γ . Moreover, η vanishes continuously as we reduce γ . Then there is a phase boundary which separates the symmetric and the symmetry-broken regime:

$$\gamma(\Delta) = \frac{2}{2\lambda - \Delta \arctan(2\lambda/\Delta)} \quad (11)$$




Figure 1. Phase diagram of the metal-insulator transition of the three-dimensional random gap model from Eq. (11), where disorder is the parameter γ and the average gap is Δ .

which is plotted in Fig. 1. The average density of states then reads

$$\begin{aligned} \rho(E) &= \frac{1}{2\pi} \lim_{\epsilon \rightarrow 0} \text{Im} \{ \text{Tr}_2 [\langle G_{\mathbf{r}\mathbf{r}}(E + i\epsilon) \rangle] \} \approx \frac{1}{2\pi} \lim_{\epsilon \rightarrow 0} \text{Im} \{ \text{Tr}_2 G_{0,0}(E + i\epsilon + i\eta) \} \\ &= \frac{1}{\pi} \text{Im} \left\{ (E + i\eta) \left[\lambda - \frac{\alpha}{2} \log \left(\frac{\alpha + \lambda}{\alpha - \lambda} \right) \right] \right\}, \quad \alpha = \sqrt{(E + i\eta)^2 - \Delta^2/4}. \end{aligned} \quad (12)$$

71 As a qualitative picture the average density of states is plotted for a fixed η in Fig. 2.

72 4. Scaling relation of the average two-particle Green's function

Using the factorization of the averaged product of Green's functions in Eq. (8), the conductivity in Eq. (7) is approximated as [36]

$$\omega^2 \sum_{\mathbf{r}} r_k^2 \text{Tr}_2 [\langle G_{0\mathbf{r}}(y) G_{\mathbf{r}0}(-y) \rangle] \approx \omega^2 \sum_{\mathbf{r}} r_k^2 \text{Tr}_2 [\langle G_{0\mathbf{r}}(y) \rangle \langle G_{\mathbf{r}0}(-y) \rangle] \quad (y = \omega/2 + i\epsilon), \quad (13)$$

where the constant prefactor $e^2/2h$ has been omitted here. This can be combined with the self-consistent Born approximation in Eq. (9) to obtain

$$\omega^2 \sum_{\mathbf{r}} r_k^2 \text{Tr}_2 [\langle G_{0\mathbf{r}}(y) \rangle \langle G_{\mathbf{r}0}(-y) \rangle] \approx \omega^2 \sum_{\mathbf{r}} r_k^2 \text{Tr}_2 [G_{0,\mathbf{r}}(y + i\eta) G_{0,-\mathbf{r}}(-y - i\eta)]. \quad (14)$$

For the expression (7) this approximation leads to the Boltzmann (or Drude) conductivity, which reads in our specific case

$$\sigma_{kk} \approx \frac{e^2}{2h} \frac{\omega^2}{\pi^2} \int_0^\lambda \frac{\Delta^2/4 - z^2}{(\Delta^2/4 - z^2 + k^2)^3} k^2 dk \quad (z = \omega/2 + i\eta). \quad (15)$$

73 Thus the conductivity vanishes in the DC limit $\omega \rightarrow 0$ for $\eta > 0$. The reason is that the self-consistent
74 Born approximation creates the Green's function $G_{0,\mathbf{r}}(y + i\eta)$, which decays exponentially on the scale
75 $1/\eta$. Consequently, the sum over the real space coordinates on the right-hand side of Eq. (14) is finite.

A more careful inspection indicates that the averaged product of Green's function on the left-hand side of Eq. (13) decays according to a power law as a consequence of the massless fluctuations around




Figure 2. Average density of states of the three-dimensional random gap model for fixed $\eta = 0.04$ and average gap $\Delta = 0.4$ (full curve) and $\Delta = 0.8$ (dashed curve).

the spontaneous symmetry breaking solution $\eta \neq 0$ [34]. We can perform the integration with respect to these fluctuations and obtain the diffusion propagator [35]

$$\text{Tr}_2 [\langle G_{0\mathbf{r}}(y)G_{\mathbf{r}0}(-y) \rangle] \approx \frac{\eta - iy}{4} \int \frac{e^{i\mathbf{q}\cdot\mathbf{r}}}{-iy + Dq^2} d^3q \quad (16)$$

with diffusion coefficient

$$D = \frac{\eta - iy}{2} \sum_{\mathbf{r}} r_k^2 \text{Tr}_2 [G_{0,\mathbf{r}}(y + i\eta)G_{0,-\mathbf{r}}(-y - i\eta)] . \quad (17)$$

After summing over the real space coordinates we obtain the expression

$$\omega^2 \sum_{\mathbf{r}} r_k^2 \text{Tr}_2 [\langle G_{0\mathbf{r}}(y)G_{\mathbf{r}0}(-y) \rangle] = \omega^2 f(\eta/y) \sum_{\mathbf{r}} r_k^2 \text{Tr}_2 [G_{0,\mathbf{r}}(y + i\eta)G_{0,-\mathbf{r}}(-y - i\eta)] , \quad (18)$$

where the coefficient on the right-hand side is a result of the strong massless fluctuations, which didn't exist in the approximation given by Eq. (14). It depends on the ratio of the order parameter of spontaneous symmetry breaking η and the symmetry-breaking field y :

$$f(\eta/y) = (1 + i\eta/y)^2 . \quad (19)$$

76 This coefficient indicates that the correlations of the Green's function fluctuations are negligible only
 77 for $f(\eta/y) \approx 1$. This is the case in the absence of symmetry breaking, where $\eta = 0$ and $f(0) = 1$. This
 78 justifies the approximation by Eq. (14) in the insulating regime. On the other hand, in the presence
 79 of spontaneous symmetry breaking (i.e., for $\eta > 0$) the coefficient diverges for $\omega \rightarrow 0$ and gives
 80 $\omega^2 f(\eta/y) \rightarrow -1$ in the limits $\epsilon \rightarrow 0$ and then $\omega \rightarrow 0$.

The diffusion coefficient in Eq. (17) is easy to calculate and reads

$$\sum_{\mathbf{r}} r_k^2 \text{Tr}_2 [G_{0,\mathbf{r}}(y + i\eta)G_{0,-\mathbf{r}}(-y - i\eta)] = \frac{1}{4\pi} \frac{1}{\sqrt{\Delta^2/4 + (\eta - iy)^2}} , \quad (20)$$




Figure 3. Conductivity as a function of disorder for an average gap $\Delta = 0.004$ (red curve), $\Delta = 0.04$ (green curve) and $\Delta = 0.4$ (blue curve). There is a metal-insulator transition at $\gamma \approx 1$, at $\gamma \approx 1.03$ and at $\gamma \approx 1.37$, respectively.

which together with the scaling relation (18) gives for the conductivity of Eq. (7) in the DC limit $\omega \rightarrow 0$

$$\sigma_{kk} = \frac{e^2}{4\pi h} \frac{\eta^2}{\sqrt{\Delta^2/4 + \eta^2}}. \quad (21)$$

81 The solution η of the self-consistent Eq. (10) is inserted into σ_{kk} and the conductivity is plotted as a
 82 function of disorder strength γ in Fig. 3. The conductivity vanishes linearly with decreasing disorder
 83 strength (i.e. with decreasing doping concentration). To illustrate the crossover to a power law with
 84 exponent 0.6, the calculated conductivity and the power-law fit are plotted together in Fig. 4.

85 5. Discussion and conclusions

86 Our result for the DC conductivity in Eq. (21), together with the solution of the order parameter η
 87 in Eq. (10), provides a simple description of a metal-insulator transition in doped three-dimensional
 88 semiconductors. The metal-insulator transition is characterized by the scattering rate η that vanishes
 89 in the insulating regime. Such a behavior is not an Anderson transition, since the latter would have a
 90 scattering rate $\eta \neq 0$ on both sides of the transition [38]. Even more important is the change of the
 91 coefficient $f(\eta/y)$: It is always 1 in the insulating regime and infinite in the metallic regime. This
 92 quantity describes the correlations of the Green's function fluctuations in the relation (18).

93 There is a linear behavior near the metal-insulator transition and a crossover to a non-critical
 94 power law, as depicted in Fig. 4. For the linear part the slope of the conductivity is quite robust with
 95 respect to the average gap Δ (cf. Fig. 3). Away from the transition point a negative curvature appears
 96 though, which can be fitted by a power law with exponent $\mu \approx 0.6$ (cf. Fig. 4). The change of exponents
 97 can be related to the discussion in Refs. [33,39] about a crossover of exponents in Si:P from $\mu \approx 1$
 98 very close to the critical point N_c to $\mu \approx 0.5$ further away from N_c . Rosenbaum et al. have found that
 99 the conductivity close to the critical point varies from sample to sample [32]. This indicates strong
 100 conductivity fluctuations, which may also exist in our random gap model, as indicated by the strong
 101 fluctuations of the Green's functions due to the large values of $f(\eta/y)$.

102 As mentioned in the Introduction, a related metal-insulator transition in three-dimensional Weyl
 103 fermionic systems has attracted considerable attention recently [2–26]. Formally, this transition is
 104 very similar, although the underlying Hamiltonian is that of Weyl fermions rather than our simple
 105 semi-conductor Hamiltonian in Eq. (1). This difference leads to the creation of two distinct insulating




Figure 4. This plot demonstrates the crossover in the critical regime of the conductivity (green curve) through the fitting (red) curve $0.47(\gamma - \gamma_c)^{0.6}$. The latter fits the conductivity very well away from the critical point γ_c for $\Delta = 0.01$.

106 phases, characterized by the Hall conductivity $\sigma_{xy} = \mp e^2/2h$ in the lower part of the phase diagram in
 107 Fig. 1 for Weyl fermions. But the role of the particle-hole symmetry, the existence of a massless mode
 108 due to spontaneous breaking of this symmetry and the role of diffusion in the metallic phase are the
 109 same in both type of models [26–28]. This indicates that metal-insulator transitions in systems with
 110 particle-hole symmetry are based on the same type of mechanism.

111 ACKNOWLEDGMENT

112 This work was supported by a grant of the Julian Schwinger Foundation.

113 References

- 114 1. N.W. Ashcroft and N.D. Mermin, *Solid State Physics* (Saunders College 1976)
- 115 2. E. Fradkin, Phys. Rev. B **33**, 3263 (1986).
- 116 3. E. Fradkin, Phys. Rev. B **33**, 3257 (1986).
- 117 4. X. Wan, A. M. Turner, A. Vishwanath, and S. Y. Savrasov, Phys. Rev. B **83**, 205101 (2011).
- 118 5. J. Smith, S. Banerjee, V. Pardo, and W.E. Pickett, Phys. Rev. Lett. **106**, 056401 (2011).
- 119 6. A.A. Burkov and L. Balents, Phys. Rev. Lett. **107**, 127205 (2011).
- 120 7. A.A. Burkov, M.D. Hook, and L. Balents, Phys. Rev. B **84**, 235126 (2011).
- 121 8. G. Xu, H. Weng, Z. Wang, X. Dai, and Z. Fang, Phys. Rev. Lett. **107**, 186806 (2011).
- 122 9. W. Witczak-Krempa and Y.B. Kim, Phys. Rev. B **85**, 045124 (2012).
- 123 10. S.M. Young, S. Zaheer, J.C.Y. Teo, C.L. Kane, E.J. Mele, and A.M. Rappe, Phys. Rev. Lett. **108**, 140405 (2012).
- 124 11. P. Hosur, S.A. Parameswaran, and A. Vishwanath, Phys. Rev. Lett. **108**, 046602 (2012).
- 125 12. Z. Wang, Y. Sun, X.-Q. Chen, C. Franchini, G. Xu, H. Weng, X. Dai, and Z. Fang, Phys. Rev. B **85**, 195320
 126 (2012).
- 127 13. B. Singh, A. Sharma, H. Lin, M.Z. Hasan, R. Prasad, and A. Bansil, Phys. Rev. B **86**, 115208 (2012).
- 128 14. G.Y. Cho, arXiv:1110.1939 (2012).
- 129 15. G.B. Halász and L. Balents, Phys. Rev. B **85**, 035103 (2012).
- 130 16. R. Nandkishore, D. A. Huse, and S. Sondhi, arXiv:1307.3252 (2013).
- 131 17. C.-X. Liu, P. Ye, and X.-L. Qi, Phys. Rev. B **87**, 235306 (2013).
- 132 18. R. R. Biswas and S. Ryu, Phys. Rev. B **89**, 014205 (2014).
- 133 19. K. Kobayashi, T. Ohtsuki, and K.-I. Imura, Phys. Rev. Lett. **110**, 236803 (2013).
- 134 20. Z. Huang, T. Das, A.V. Balatsky and D.P. Arovas, Phys. Rev. B **87**, 155123 (2013).

- 135 21. K. Kobayashi, T. Ohtsuki, K.-I. Imura, and I. F. Herbut, Phys. Rev. Lett. **112**, 016402 (2014).
- 136 22. Y. Ominato and M. Koshino, Phys. Rev. B **89**, 054202 (2014).
- 137 23. B. Roy and S. Das Sarma. Rev. B **90**, 241112(R) (2014).
- 138 24. B. Sbierski, G. Pohl, E.J. Bergholtz and P.W. Brouwer, Phys. Rev. Lett. **113**, 026602 (2014).
- 139 25. S.V. Syzranov, V. Gurarie, L. Radzihovsky, Phys. Rev. Lett. **114**, 166601 (2015).
- 140 26. K. Ziegler, Eur. Phys. J. B **89**, 268 (2016).
- 141 27. K. Ziegler, J. Phys. A: Math. Theor. **48**, 055102 (2015).
- 142 28. K. Ziegler, J. Phys. A: Math. Theor. **52**, 455101 (2019).
- 143 29. T.F. Rosenbaum, K. Andres, G.A. Thomas and R.N. Bhatt, Phys. Rev. Lett. **45**, 1723 (1980).
- 144 30. T.F. Rosenbaum, R.F. Milligan, M.A. Paalanen, G.A. Thomas, R.N. Bhatt and W. Lin, Phys. Rev. B **27**, 7509
145 (1983).
- 146 31. A. Roy and M.P. Sarachik, Phys. Rev. B **37**, 5531 (1988).
- 147 32. T.F. Rosenbaum, G.A. Thomas and M.A. Paalanen, 1994 Phys. Rev. Lett. **72**, 2121 (1994).
- 148 33. H. v. Löhneysen, Phil. Trans. R. Soc. Lond. A **356**, 139 (1998).
- 149 34. K. Ziegler, Phys. Rev. B **55**, 10661 (1997); Phys. Rev. Lett. **80**, 3113 (1998).
- 150 35. K. Ziegler, Phys. Rev. Lett. **102**, 126802 (2009); Phys. Rev. B **79**, 195424 (2009).
- 151 36. B.L. Altshuler and B.D. Simons, in *Mesoscopic quantum physics*, eds. E. Akkermans et al. (North-Holland
152 1995).
- 153 37. A. Altland, and B.D. Simons, *Condensed Matter Field Theory* (Cambridge University Press 2010).
- 154 38. L. Schäfer and F. Wegner, Z. Phys. B **38**, 113 (1980).
- 155 39. H. Stupp, M. Hornung, M. Lakner, O. Madel, and H. v. Löhneysen, Phys. Rev. Lett. **71**, 2634 (1993).