

Review

Not peer-reviewed version

Ceramic-on-Metal Bearing in Total Hip Arthroplasty—Was It So Bad? A Narrative Review and a Critical Analysis of the Literature

[Michela Saracco](#)^{*}, Vincenzo Ciriello, [Antonio Spinarelli](#), [Giuseppe Solarino](#), Remo Goderecci, [Giandomenico Logroscino](#)

Posted Date: 9 October 2023

doi: 10.20944/preprints202310.0480.v1

Keywords: ceramic-on- metal; hip replacement; hard-on-hard bearings



Preprints.org is a free multidiscipline platform providing preprint service that is dedicated to making early versions of research outputs permanently available and citable. Preprints posted at Preprints.org appear in Web of Science, Crossref, Google Scholar, Scilit, Europe PMC.

Copyright: This is an open access article distributed under the Creative Commons Attribution License which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Narrative Review

Ceramic-on-Metal Bearing in Total Hip Arthroplasty—Was It So Bad? A Narrative Review and a Critical Analysis of the Literature

Michela Saracco ^{1,*}, Vincenzo Ciriello ², Antonio Spinarelli ³, Giuseppe Solarino ³, Remo Goderecci ⁴ and Giandomenico Logroscino ⁴

¹ Department of Orthopaedics, ASL Napoli 2 Nord, Naples, Italy; michelasaracco@gmail.com

² Department of Surgery, Orthopaedic and Trauma Unit, S. Croce e Carle Hospital, Cuneo, Italy; vincenzo.ciriello83@live.com

³ Department of Translational biomedicine and neuroscience, School of Medicine, University of Bari Aldo Moro, AOU Consorziale 'Policlinico', Bari, Italy; antoniospinarelli@gmail.com; giuseppe.solarino@uniba.it

⁴ Department of Life, Health and Environmental Sciences, Orthopaedic Unit - University of L'Aquila, Italy; g.logroscino@gmail.com

* Correspondence: michelasaracco@gmail.com; Tel.: +39-3388679796

Abstract: Hip replacement has significantly improved the quality of life of patients with symptomatic hip osteoarthritis. Metal-on-metal (MoM) bearings have been used with conventional total hip arthroplasties (THR) for many years with excellent results. Wear and corrosion of MoM arthroplasties can result in the release of metal ions into tissues around the hip joint and blood. From the 1980s onwards, the search for increasingly better coupling materials with low levels of wear led to the rise of hard-on-hard couplings such as ceramic-on-ceramic (CoC). The latter is currently the coupling with the longest known duration and with a wear rate close to zero. MoM coupling has been for a long time the most significant alternative, but systemic and local complications linked to the release of chromium (Cr) and cobalt (Co) ions, determine the withdrawn from the market. One other alternative proposed over the time has been Ceramic-on-Metal (CoM) bearing. Preliminary results have been described as favourable, but due to the failures of MoM, it has been withdrawn from the market, without causing significant clinical complications. In this narrative review, we analysed risks and benefits associated with the implantation of hybrid hard-on-hard bearings, such as CoM.

Keywords: ceramic-on-metal; hip replacement; hard-on-hard bearings

1. Introduction

Hip arthroplasty (THR) has significantly improved the quality of life of patients with symptomatic osteoarthritis. Osteoarthritis is a degenerative joint disease that leads to a significant reduction in autonomy. It is typically characterized by pain, joint stiffness, reduced muscle tone and consequent reduction in physical capacity. The hip and knee are the joints most affected. Half of the world's over 65 population is affected by osteoarthritis and 25% of these say they are unable to carry out normal daily activities. The European Project on Osteoarthritis (EPOSA) reported more accurate demographic data on this disease, involving 6 European countries (Germany, Italy, The Netherlands, Spain, Sweden and United Kingdom). By this, the prevalence of osteoarthritis is 30.4% [1].

In Italy, 40,775 hip prostheses were implanted in 2020 (data related to 7 regions), demonstrating that hip prosthetic replacement surgery is widespread and increasing in recent years [2].

Until the last century, degenerative pathologies of the hip joint were considered as unavoidable events, associated with the advanced age of the patients. Few were the patients on whom surgery was performed to relieve the pain. The first attempts at arthroplasty date back to the end of the 1800s. In France, Ollier tried to remodel the worn bone surface by interposing periarticular connective tissue and muscle flaps between the damaged articular surfaces. The first difficulties emerged immediately, mainly relating to the wear of the interposition material, and to the flare-up of joint stiffness and pain. In Italy, Carlo Marino Zuco (1946), Carlo Pais (1950), and Oscar Scaglietti (1952) made the first

surgical procedures but with not very encouraging results. In 1960 the British G.K. McKee and J. Watson Farrar marked one of the fundamental milestones in the development of arthroplasty exploiting the metal-on-metal joint coupling made in cobalt-chrome. The first resurfacing prosthesis was introduced in the early 1950s by Charnley who produced a cement less dual component Teflon prosthesis consisting of two thin 2-3 mm polytetrafluoroethylene cups without success. The first-generation metal-on-polyethylene (MoP) bearing resurfacing prostheses gave satisfactory short-term results. However, at longer follow-up results were inconsistent. The causes of the failures were erroneously attributed to head necrosis and fracture of the femoral neck. In reality, the main problem lay in the osteolysis induced by the wear debris of the polyethylene produced by the friction of the large prosthetic heads. Due to the less encouraging long-term results, the MoP was almost abandoned. The importance of Charnley's work is also due to his contribution to the understanding of the biomechanics of the hip joint. In fact, in the 1950s, despite the introduction of acrylic cement and the development of prosthetic designs, the number of failures due to early mobilization of the implants was unacceptable [3].

In 1961, unbeknownst to Charnley, one of his assistants experimented high density polyethylene demonstrating reduced wear. The same year Charnley implanted the first high-density polyethylene (HMWP) prosthesis. The friction problem was partly solved by applying the "moment of a force" principle: if the radius on which it acts approaches zero the direction of the force will tend to pass through the point of rotation and will not have the ability to rotate the object, but only to push it in its direction. At the end of this long work, the final dimensions judged optimal by Charnley were 22 mm for the head and 50 mm for the external diameter of the acetabular cup; thus, the concept of "low friction arthroplasty" was born [4].

In 1971 Judet first, and then Lord in 1978, proposed a prosthesis with a "madreporic" surface with trochanteric support and a long stem whose anchorage is achieved thanks to the multiple spherical irregularities subsequently osteointegrated into the bone. The cup was screwed into the acetabular cavity with a polyethylene insert. The ceramic-on-ceramic (CoC) prosthesis by Mittelmeier dates back to 1974. The happy intuition of the CoC coupling, which is still today the best choice in terms of wear and friction coefficient, proved unsuccessful at the bone-ceramic acetabular interface. Also, in 1974, Bousquet was the first to use the ceramic-on-polyethylene (CoP) coupling. At the end of the 70s but above all during the 80s research in the prosthetic field intensified and many models were created in this period. In 1983 Spotorno presented his cementless prosthesis characterized by proximal fixation. The hemispherical cup, of original conception, had expansion fins provided with small pins which ensured sure primary stability. From 1979 to 1993, Zweimuller presented a series of 12 conical stems with a rectangular section which allows greater cortical contact and guarantees rotational stability. In 1984 Muller re-evaluated the previously experimented MoM coupling [5].

MoM bearings have been used with conventional THR for many years and early applications have shown promise [6]. Low wear potential of mechanically well-studied prostheses, no relevant risk of bearing fracture, and a high design variability justified the application of MoM bearings even in hip resurfacing (HR) and large head hip arthroplasty (LH-THR) [7]. However, wear and corrosion of metal implants can release metal ions into the tissues around the hip and blood. Metal ions release can lead to "adverse reactions to metal debris" (ARMD) and potentially induce systemic adverse events (i.e., toxicity, teratogenicity and carcinogenicity) [8].

According to current knowledge, patients with values higher than $7\mu\text{g/l}$ must be carefully studied to evaluate their health risk and the possible indication for revision surgery. This is justified by the fact that the cut-off for risk of ARMD is set at $7\mu\text{g/L}$, as indicated by the Medicines and Healthcare Products Regulatory Agency (MHRA) [9].

The measurement of serum Cr and Co ions plays an essential role in assessing the health risk in patients with hard-on-hard bearings, such as CoM and MoM. Therefore, the methods for carrying out the blood sampling and the analysis of the sample must be rigorous and reliable, and must be aimed at avoiding contamination that could distort the result obtained. In addition, it is mandatory to exclude the presence of other implanted medical devices containing metal ions and occupational exposure to metals, as well as the intake of particular beverages such as beer the night before the

sampling. The possible intake of supplements containing Cr should also be investigated. Venous blood samples should be collected using polypropylene tubes and 21-gauge stainless steel needles, preventing metal contamination. This is made possible through the use of particular devices such as gloves without powder and isopropyl alcohol for disinfection. All collection tubes must be free of traces of metals.

An ASX510 autosampler (CETAC, Omaha, NE, USA) is used to analyze serum Cr and Co by Inductively Coupled Plasma mass spectrometry (ICP-MS) (Agilent Technologies, Palo Alto, CA). To quantify Co as ^{52}Co and Cr as Cr, the analysis is conducted by switching between two acquisition modes: normal and cool plasma conditions. A certified reference material (ClinChek Serum Control, lyophil., for Trace Elements, Level I, Recipe Chemicals + Instruments GmbH, München, Germany) is used to verify accuracy [10].

From the 1980s onwards, the search for increasingly better coupling materials with low levels of wear led to the emergence of hard-on-hard couplings such as CoC. The latter is currently the coupling with the longest known duration and with a wear rate close to zero. The fate of MoM was different, which was soon withdrawn from the market due to systemic and local complications linked to the release of Cr and Co ions. While the hard-on-hard CoM hybrid coupling has followed the fate of the MoM, withdrawn from the market, but as we will see without causing significant complications for the patient.

2. The Ceramic-on-Metal bearing

THAs with CoC or MoM bearings have showed good mid-term and long-term results. However, these couplings have advantages and disadvantages. Ceramics are known for having very low wear rates and high biocompatibility of debris, but they are associated with squeaking and/or component fracture. On the other hand, the wear rate of the MoM bearing is much greater, especially in the case of implant mal-positioning. The excessive wear leads to release of Cr and Co ions with local and systemic toxicity. For these reasons, a hybrid hard-on-hard bearing was introduced in the early 2000s: CoM. This bearing has advantages and at the same time fewer disadvantages compared to other hard-on-hard couplings. CoM coupling is in fact characterized by reduced adhesive and corrosion wear, reduced loss of metal ions because only one half of the implant is made of metal, with an expected longer survivorship. In addition, the risk of CoM bearing fracture and squeaking is lower than CoC. The first results at short- and medium-term follow-up for CoM were encouraging, showing a low risk of fracture, low release of Cr-Co ions, absence of squeaking and excellent clinical and radiographic outcomes. Serum Cr-Co ions level was found to be mildly above baseline, but lower than the MHRA threshold of $7\text{ }\mu\text{g/l}$. CoM implants have not been widely adopted over the years, probably due to an increased awareness of MoM risk of ARMD and metal ions systemic toxicity [11].

Additionally, the CoM bearing has another potential advantage: the liner can be thin, allowing for femoral heads of 36 mm. Indeed, it is known that the use of large diameter heads improves the stability of the implant, because the "Jump Distance" increases. The Jump distance is the degree of translation of the center of the femoral head required for hip dislocation. The wider the jump distance, the lower the risk of dislocation. Lazennec et al. proposed the use of jump distance as a predictor of dislocation. For this reason, a large head diameter is an interesting option to reduce the risk of dislocation after total hip arthroplasty, as demonstrated by Scifert et al.[12].

Furthermore, the CoM coupling also has the advantage of using the ceramic femoral head. In fact, it is known that the corrosion is lower at the morse taper when ceramic heads are implanted [13].

The 2017 British Joint Register (NJR) reported only 2156 hip prostheses implanted with CoM bearing. Most implants were performed between 2009 and 2010. But, the rate of revision of CoM at 7 years of follow-up was 6.17%, significantly lower than the MoM revision rate (12.2%) [14].

CoM is a bearing associated with high wear only if compared with CoC. The study of Affatato et al. studied the wear tendency of CoM hip bearings (three ball head diameters: 28, 32 and 36 mm), comparing them with CoC. The comparison with CoC is dictated by the fact that this is considered the gold standard for wear resistance. For this purpose, the weight loss over a standard wear simulation was monitored. In addition, electronic microscope evaluations were used to verify if any

carbides removal, for the metallic components, triggered wears debris production promoting abrasive third-body wear. After five million cycles, the results showed significantly greater wear in CoM compared with CoC, and significant greater wear for the 32-mm diameter compared with the 36-mm one. It was evident that the CoM coupling has a greater tendency to wear than CoC [15].

On the other hand, in the laboratory studies conducted by Williams et al., friction, wear, and ion levels were lower in CoM bearings compared with MoM; CoM reported very similar wear to CoC and therefore significantly low. If the components are not correctly implanted and in case of rim loading, all bearings showed increased wear. Despite this, CoM reported lower wear and absence of stripe wear compared with MoM bearings [16].

The laboratory studies carried out made it possible to study the wear mechanism in depth also using electronic microscopy and the hip simulator. Surface profilometry is performed using a 2D contacting profilometer.

The areas of transfer on the ceramic heads are visualized using Scanning Electron Microscopy (SEM), while the transfer composition is assessed by EDX (energy dispersion of x-rays), with a reduced beam energy of 10 keV. Wear rates are determined with the help of the hip simulator, in which the explanted bearings are compared with three new CoM bearing components, applying a twin peak loading cycle with a peak load of 3 kN. In the hip simulator, the bearings are fixed in the anatomical position, then a Flexion – Extension movement to the head (Range of motion: -15° to 30°) and Internal – External rotation to the acetabulum (ROM: $\pm 10^{\circ}$) are applied for 2 million cycles. Bearing surfaces are lubricated with 25% calf serum supplemented with 0.03% sodium azide. The lubricant fluid is substituted approximately every 0.33 million cycles. Wear rates are reported as volumetric wear per million cycles ($\text{mm}^3/\text{million cycles}$) after being measured gravimetrically at 0.5, 1 and 2 million cycles and converted to volumetric wear (mm^3) - considering density of the metal alloy and ceramic material to be 8330 kg/m^3 and 4365 kg/m^3 , respectively.

Isaac et al. reported their laboratory results: some evidence of transfer material was clearly showed on ceramic ball heads at visual inspection of the explanted bearings. ‘Heavy’ and ‘light’ metal transfer can be classified, on the other hand, there were also areas that had not changed following implantation. No rim damage was recorded during examination of the metal acetabular component, but only slight evidence of scratching within the bearing surface was evident. SEM was performed on both ceramic heads in the regions of visually observed ‘heavy’ material transfer. EDX analysis showed that a composition of cobalt and chromium elements was involved into the transfer material from the cobalt-chromium acetabular component to the ceramic ball head.

At 2 million cycles the measured wear rate for CoM bearings was $0.047 \text{ mm}^3 / \text{million cycles}$ (± 0.06). The mean wear rate when testing explanted both head and acetabular component was $0.15 \text{ mm}^3 / \text{million cycles}$, the highest value, respect the rate obtained from the test executed with the explanted head articulated with a new acetabular component, that was lower ($0.034 \text{ mm}^3 / \text{million cycles}$). The combination of explanted both head with acetabular component presented a higher bedding – in wear than the other bearings, but the steady – state wear was comparable with the other combination [17].

Exposure to higher levels of metal ions in the blood has raised doubts whether these may be related to the risk of carcinogenicity, as known for MoM. Even when faced with metal ion blood levels only slightly above the limit, some authors wanted to study the risk of chromosomal alterations of patients carrying CoM bearing. Kazi et al. proposed the chromosomal analysis in the peripheral blood lymphocytes. Cytogenetic biomarkers (24-colour fluorescent in situ hybridization – FISH) were detected in all 46 chromosomes of the peripheral blood lymphocytes. Aneuploidy (gain or loss) and structural (break or translocation) chromosomal aberrations were searched. Aneuploidy is characterized by the abnormality in the whole number of chromosomes (too many or too few) or by an alteration in the number of copies of chromosomes segments. The 24-colour FISH analysis revealed a significantly increased incidence of breaks and losses. On the other hand, there was a significantly reduced incidence of gains. In addition, patients with unilateral or bilateral CoM hip arthroplasty are not different in terms of chromosomal aberrations. The result demonstrates the recurrence of chromosomal alterations in the blood of these patients, but the result can only be

partially interpreted against CoM bearing as we do not have pre-implantation chromosomal studies performed on the same patients. In fact, only these could demonstrate the direct correlation between the development of chromosomal alterations and high levels of metal ions in the blood [18].

Nowadays, the prosthetic release of metal ions in the blood is not clearly linked to cancer onset. Some authors reported high rate of lymphatic and hematopoietic diseases, kidney and prostate cancers [19,20]. On the other hand, other authors have not demonstrated any cancer link [21,22]. It could be essential to analyze this relationship in the correct epidemiological terms, because it took more than 40 years to prove the association, also for MoM.

3. Discussion

The fate of the CoM coupling is closely linked to the MoM one and to the fear of causing similar risks to the health of patients. Despite the early withdrawal of this coupling from the market, the scientific evidence is often contradictory.

Cadossi et al. is one of the authors who demonstrated the opposite: Cr serum levels were significantly lower in CoM-THA than in MoM-THA group ($p=0.02$) at 3-years follow-up. So, CoM-THA patients are characterized by good clinical outcomes and low release of Cr [23].

Similarly, 74 patients (85 hips) were followed up at mean 50 months by Yi et al. Radiographic evaluation did not show radiolucency, osteolysis or loosening. On the other hand, serum metal ions levels were higher than normal values of the unexposed population. But age, cup abduction angle, cup anteversion angle, acetabular version, bilateral arthroplasty, cup screw used, hip stem implant type, or femoral head size did not correlate with metal ion levels in the organic fluids [24].

Studies previously published by the authors of this manuscript demonstrate that patients with CoM couplings did not undergo revision if the components were well positioned, confirming previous results reported in many other scientific papers. The revision and failure (revision plus pseudotumor) rate recorded by the authors were respectively 3.2% and 4.8%. Our revision rate is similar to rates reported for other bearing used in hip replacements, 3.8–6.7% [25].

Like Yi et al, also in our study the values of blood ions showed higher values than in the general population, but still lower than the recognized levels of danger. Evidence from our data showed that correct positioning of the acetabular component plays a key role in wear and consequently blood ion levels. If correctly implanted, CoM bearing is reliable and safe at a mean 8-year follow-up. This implant is characterized by minimal rise of metal blood ions and involved neither systemic or local toxicity nor influenced clinical results [11].

CoM bearing and short femoral stems demonstrated to be safe and reliable at long term follow-up, but the correct positing of the implant components is essential to avoid complications. [25].

Therefore, the CoM coupling did not entail particular risks for the patient even when associated with short stems, and this has been repeatedly confirmed in the literature. The need to analyze the safety of the hard-on-hard hybrid coupling in the implantation of short stems arises from the fact that the latter require careful techniques during implantation and therefore imperfect positioning is common, such as varus stem or in valgus, undersized stem, or tendency towards leg-length discrepancy especially in short first-generation stems. At a mean follow-up of 9 years, Mehta et al. reported a revision rate 4.5% and metal ion levels above MHRA thresholds on 6.06% [26]. In 2017, Schouten published a study between CoM and MoM in 83 patients, demonstrating significantly lower values of blood metal ions in the CoM group, good clinical outcomes and low rate of implant revision [27].

Calcar atrophy and stress shielding are found relatively frequent in patients implanted with short femoral stems, because of prosthetic stems design and to modification of the load lines, and this is not correlated to the effect of metal ions on bone turnover. In addition, spot welds are evident in the patients treated with CoM and femoral short stem implants and analyzed by the authors of this paper and by other authors, confirming an excellent fixation of the implants and optimal osseointegration. These results confirmed how short stems works well even at long term follow up, as recently described in the 2020 Australian Arthroplasty Register: revision rate at 15years of 6.35%,

better of 7.8% of other traditional stems, probably because of optimal load distribution across the metaphyseal region favoring proper osteointegration, regardless of the type of bearing used [27,28].

Hill et al reported an important case-series: a total of 287 CoM THAs were performed in 271 patients (mean age 55.6 years at a mean follow-up of 34 months) with a five-year survival rate of 96.9% and higher than expected but not dangerous levels of metal ions in the blood [29].

Maurer-Ertl et al. proposed a case-series of 20 patients underwent THA using a CoM bearing. Clinical outcomes were evaluated by standardized scores systems (Harris Hip Score and WOMAC Score) and radiological examination on X-rays. Metal ion analysis was conducted on patient's blood samples and the collected ion values were then correlated to the prosthesis components positioning. The obtained mean ion concentrations for Co and Cr were 3,1 $\mu\text{g/L}$ (range, 0,3–15,2 $\mu\text{g/L}$) and 1,6 $\mu\text{g/L}$ (range, 0,1–5,5 $\mu\text{g/L}$), respectively, with maximum levels lower than the international accepted threshold for revision of MoM device. The correlation analysis demonstrated a positive correlation between cup anteversion and Co and Cr blood levels. Routine follow-up with at least one obligatory evaluation of serum metal ion concentrations and a magnetic resonance imaging (MRI) once to exclude local soft tissue reactions are recommended [30].

Isaac et al. reported higher median ion blood levels in MoM bearings, respect to CoM. At 12 months of follow-up Co and Cr concentrations were 0.08 $\mu\text{g/l}$ and 0.22 $\mu\text{g/l}$, respectively, in CoM bearings and 0.48 $\mu\text{g/l}$ and 0.32 $\mu\text{g/l}$ in MoM joints, with a statistically significant difference for Cr levels ($p = 0.02$). In their study the Author tested in a hip joint simulator different CoM bearing (one couple of explanted head and acetabular component, one explanted head and a new acetabular component, and three new heads and acetabular components) and, after one million cycles all the wear rates were similar, with levels that were an order of magnitude less than that reported for MoM bearings. Two explanted ceramic heads from revision surgery revealing areas of thin metal transfer and explanted head and acetabular component presented higher bedding-in. Additionally, the Authors reported four outliers in each clinical group, correlated to component malposition [17].

4. Conclusions

In case of correctly positioned implant, CoM coupling is a safe and reliable bearing at medium- and long-term follow-up. Patients with CoM bearing carry a device that can release locally and systemically metal ions, so Cr and Co metal ions blood levels evaluation must be performed annually even if asymptomatic. Repeated blood analysis and revision should be considered in case of persistent high metal ions blood values. Future studies at longer follow-up are necessary to understand when and how revise these implants. Based on the available data, CoM coupling had been abandoned not because of the concrete risk of complications or failure, but only for the unsuccess of MoM bearings and to avoid possible risk of complaint and reimbursements.

Author Contributions: Conceptualization: M.S., G.L.; Data curation: M.S., V.C.; Writing of the original draft: M.S., R.G., A.S.; Review and Editing: G.L., G.S. All authors have read and agreed to the published version of the manuscript.

Funding: No funds received.

Acknowledgments: Nothing to declare.

Conflicts of Interest: The authors declare no conflict of interest.

References

1. Castell, M.V.; van der Pas, S.; Otero, A.; Siviero, P.; Dennison, E.; Denking, M.; Pedersen, N.; Sanchez-Martinez, M.; Queipo, R.; van Schoor, N.; Zambon, S.; Edwards, M.; Peter, R.; Schaap, L.; Deeg, D. Osteoarthritis and frailty in elderly individuals across six European countries: results from the European Project on OsteoArthritis (EPOSA). *BMC Musculoskelet Disord.* 2015, 17, 16:359. doi: 10.1186/s12891-015-0807-8.
2. Report Annuale 2020 del Registro Italiano ArtroProtesi (Riap). Available online: RIAP - Registro Italiano ArtroProtesi (iss.it) (accessed on 26 June 2023).

3. Steinberg, M.E. Reconstructive Surgery of the adult Hip: an overview. In Steinberg ME. The hip and its disorders. Philadelphia, WB Saunders Company 1991, 705-727.
4. Charnley, J.C. Arthroplasty of the hip: a new operation. *Lancet* 1961, 1, 1129-1132.
5. Ahnfelt, L.; Herberts, P.; Malchau, H. Prognosis of total hip replacement. *Acta Orthop Scand* 1990, 61, 1-26.
6. Hannemann, F.; Hartmann, A.; Schmitt, J.; Lützner, J.; Seidler, A.; Campbell, P.; Delaunay, C.P.; Drexler, H.; Ettema, H.B.; García-Cimbrelo, E.; Huberti, H.; Knahr, K.; Kunze, J.; Langton, D.J.; Lauer, W.; Learmonth, I.; Lohmann, C.H.; Morlock, M.; Wimmer, M.A.; Zagra, L.; Günther, K.P. European multidisciplinary consensus statement on the use and monitoring of metal-on-metal bearings for total hip replacement and hip resurfacing. *Orthop Traumatol Surg Res.* 2013, 99(3), 263-271. doi: 10.1016/j.otsr.2013.01.005.
7. Amstutz, H.C.; Le Duff, M.J.; Campbell, P.A.; Gruen, T.A.; Wisk, L.E. Clinical and radiographic results of metal-on-metal hip resurfacing with a minimum ten-year follow-up. *J Bone Joint Surg Am.* 2010, 92, 2663–2671. doi: 10.2106/JBJS.I.01715.
8. Langton, D.J.; Joyce, T.J.; Jameson, S.S. Adverse reaction to metal debris following hip resurfacing: The influence of component type, orientation and volumetric wear. *J Bone Joint Surg Br.* 2011, 93, 164–171. doi: 10.1302/0301-620X.93B2.25099.
9. Medicines and Healthcare Products Regulatory Agency. All metal-on-metal (MoM) hip replacements: updated advice for follow-up of patients. Medical Device Alert MDA/2017/018, London: Medicines and Healthcare Products Regulatory Agency (MHRA), 2017.
10. Slonimsky, E.; Kushnir, T.; Kadar, A.; Menahem, A.; Grundshtein, A.; Velekes, S; et al. Metal-on-metal hip replacement: MRI signal intensities of different body tissues and their relations to blood metal ion levels. *Isr Med Assoc J.* 2017, 19(11), 674–678.
11. Saracco, M.; Maccauro, G.; Urbani, A.; Ciavardelli, D.; Persichilli, S.; Ancillai, G.; Pasqualetti, P.; Calvisi, V.; Logroscino, G. Ceramic-on-metal bearing in short stem total hip arthroplasty: ions, functional and radiographic evaluation at mid-term follow-up. *Hip Int.* 2020, 30(2_suppl), 52-58. doi: 10.1177/1120700020971661.
12. Scifert, C; Noble, P; Brown, T; Bartz, RL; Kadakia, N; Sugano, N; Johnston, R; Pedersen, D; Callaghan, J. Experimental and computational simulation of total hip arthroplasty dislocation. *Orthop Clin North Am.* 2001, 32(4), 553–567.
13. Kurtz, SM; Kocagöz, SB; Hanzlik, JA; Underwood, RJ; Gilbert, JL; MacDonald, DW; et al. Do ceramic femoral heads reduce taper fretting corrosion in hip arthroplasty? A retrieval study. *Clin Orthop Relat Res.* 2013, 471, 3270–3282. doi: <https://doi.org/10.1007/s11999-013-3096-2>
14. National Joint Registry. National Joint Registry for England and Wales 14th Annual Report, Available online: <http://www.njrcentre.org.uk/njrcentre/default.aspx> (accessed on 26 June 2023).
15. Affatato, S.; Spinelli, M.; Squarzoni, S.; Traina, F.; Toni, A. Mixing and matching in ceramic-on-metal hip arthroplasty: an in-vitro hip simulator study. *J Biomech.* 2009, 42(15), 2439-2446. doi: 10.1016/j.jbiomech.2009.07.031.
16. Williams, S.; Schepers, A.; Isaac, G.; Hardaker, C.; Ingham, E.; van der Jagt, D.; Breckon, A.; Fisher, J. The 2007 Otto Aufranc Award. Ceramic-on-metal hip arthroplasties: a comparative in vitro and in vivo study. *Clin Orthop Relat Res.* 2007, 465, 23-32. doi: 10.1097/BLO.0b013e31814da946.
17. Isaac, GH; Brockett, C; Breckon, A; van der Jagt, D; Williams, S; Hardaker, C; Fisher, J; Schepers, A. Ceramic-on-metal bearings in total hip replacement: whole blood metal ion levels and analysis of retrieved components. *J Bone Joint Surg Br.* 2009, 91(9), 1134-1141. doi: 10.1302/0301-620X.91B9.22306.
18. Kazi, HA; Perera, JR; Gillott, E; Carroll, FA; Briggs, TW. A prospective study of a ceramic-on-metal bearing in total hip arthroplasty. Clinical results, metal ion levels and chromosome analysis at two years. *Bone Joint J.* 2013, 95B(8), 1040-1044. doi: 10.1302/0301-620X.95B8.31574.
19. Gillespie, WJ; Frampton, CM; Henderson, RJ; Ryan, PM. The incidence of cancer following total hip replacement. *J Bone Joint Surg* 1988, 70B, 539–542. doi: 10.1302/0301-620X.70B4.3403594.
20. Nyrén, O; McLaughlin, JK; Gridley, G; et al. Cancer risk after hip replacement with metal implants: a population-based cohort study in Sweden. *J Natl Cancer Inst* 1995, 87, 28–33. doi: 10.1093/jnci/87.1.28.
21. Mathiesen, EB; Ahlbom, A; Bermann, G; Lindgren, JU. Total hip replacement and cancer: a cohort study. *J Bone Joint Surg Br* 1995, 77, 345–350.
22. Visuri, T; Pulkkinen, P; Paavolainen, P; Pukkala, E. Cancer risk is not increased after conventional hip arthroplasty. *Acta Orthop* 2010, 81, 77–81. doi: 10.3109/17453671003667150.

23. Cadossi, M.; Mazzotti, A.; Baldini, N.; Giannini, S.; Savarino, L. New couplings, old problems: Is there a role for ceramic-on-metal hip arthroplasty? *J Biomed Mater Res B Appl Biomater.* 2016, 104, 204-209. doi: 10.1002/jbm.b.33383.
24. Yi, Z.; Bo, Z.; Bin, S.; Jing, Y.; Zongke, Z.; Fuxing, P. Clinical Results and Metal Ion Levels After Ceramic-on-Metal Total Hip Arthroplasty: A Mean 50-Month Prospective Single-Center Study. *J Arthroplasty.* 2016, 31, 438-441. doi: 10.1016/j.arth.2015.09.034.
25. Logroscino, G.; Saracco, M.; Maccauro, G.; Urbani, A.; Ciavardelli, D.; Consalvo, A.; Ferraro, D.; Falez, F. Ceramic-on-metal coupling in THA: long term clinical and radiographic outcomes using two different short stems. *BMC Musculoskelet Disord.* 2022, 22(Suppl 2), 1065. doi: 10.1186/s12891-022-05077-3.
26. Mehta, N.; Patel, D.; Leong, J.; Brown, P.; Carroll, FA. Functional outcomes & metal ion levels following ceramic on metal total hip arthroplasty: 9 year follow-up. *J Orthop.* 2021, 24, 131-134. doi: <https://doi.org/10.1016/j.jor.2021.02.030>.
27. Schouten, R.; Malone, AA; Frampton, CM; Tifen, C; Hooper, G. Five-year follow-up of a prospective randomised trial comparing ceramic-on-metal and metal-on-metal bearing surfaces in total hip arthroplasty. *Bone Joint J.* 2017, 99B(10), 1298-1303. doi: <https://doi.org/10.1302/0301-620X.99B10.BJJ2016-0905.R1>.
28. Australian Orthopaedic Association National Joint Replacement Registry (AOANJRR). Hip, Knee & Shoulder Arthroplasty: 2020 Annual Report. Available online: <https://aoanjrr.sahmri.com/annual-reports-2020> (accessed on 26 June 2023).
29. Hill, J.C.; Diamond, O.J.; O'Brien, S.; Boldt, J.G.; Stevenson, M.; Beverland, D.E. Early surveillance of ceramic-on-metal total hip arthroplasty. *Bone Joint J.* 2015, 97-B(3), 300-305. doi: 10.1302/0301-620X.97B3.33242.
30. Maurer-Ertl, W.; Prankh-Matzke, D.; Friesenbichler, J.; Bratschitsch, G.; Holzer, L.A.; Maier, M.; Leithner, A. Clinical Results and Serum Metal Ion Concentrations following Ceramic-on-Metal Total Hip Arthroplasty at a Mean Follow-Up of 60 Months. *Biomed Res Int.* 2017, 3726029. doi: 10.1155/2017/3726029.

Disclaimer/Publisher's Note: The statements, opinions and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of MDPI and/or the editor(s). MDPI and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions or products referred to in the content.