

Article

Not peer-reviewed version

---

# Interactions of CdSe nanocrystals with cationic proteins extracted from *Moringa oleifera* seeds

---

[Likius Shipwiisho Daniel](#)<sup>\*</sup>, Salatiel Kapofi, Martha Kandawa-Schulz, [Habauka Majority Kwaambwa](#)

Posted Date: 1 November 2023

doi: 10.20944/preprints202311.0060.v1

Keywords: *Moringa oleifera*; Cadmium Selenium nanocrystals; quenching; luminescence;; Stern-Volmer equation



Preprints.org is a free multidiscipline platform providing preprint service that is dedicated to making early versions of research outputs permanently available and citable. Preprints posted at Preprints.org appear in Web of Science, Crossref, Google Scholar, Scilit, Europe PMC.

Copyright: This is an open access article distributed under the Creative Commons Attribution License which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Article

# Interactions of CdSe Nanocrystals with Cationic Proteins Extracted from *Moringa oleifera* Seeds

Likius Shipwiisho Daniel <sup>1,2,\*</sup>, Salatiel Kapofi <sup>1</sup>, Martha Kandawa-Schulz <sup>1</sup> and Habauka M. Kwaambwa <sup>3</sup>

<sup>1</sup> Department of Physics, Chemistry and Material Science, Postbag 13301, University of Namibia, Windhoek, Namibia; kschulz@unam.na

<sup>2</sup> Multidisciplinary Research Service, Centre for Research Services, Postbag 13301, University of Namibia, Windhoek, Namibia; daniels@unam.na

<sup>3</sup> Faculty of Health, Natural Resources and Applied Sciences, Namibia University of Science and Technology, Private Bag 13388, 13 Jackson Kaujeua Street, Windhoek, Namibia; hkwaambwa@nust.na

\* Correspondence: daniels@unam.na; Tel.: +264 206 3390

**Abstract:** Even with significant developments in nanoscience, fairly little is known about the interactions of nanocrystal semiconducting materials with bio-macromolecules. To investigate the interfacial phenomena of cadmium selenide quantum dots (CdSe QDs) nanocrystals with proteins extracted from *Moringa oleifera* seeds, different concentrations of cadmium selenide quantum dots-*Moringa oleifera* seed protein (CdSe–MSP) complexes were prepared. Respective CdSe QDs with hexagonal phase and crystalline size in the range of 4–7 nm were synthesized and labelled with the purified mesoporous MSP having a surface area of 8.4 m<sup>2</sup>/g. The interaction mechanism between CdSe QDs and MSP was studied using the UV-Vis absorption, fluorescence emission and Fourier Transform Infrared spectroscopies. The UV-Vis absorption spectra showed absorption bands of CdSe-MSP complexes at 546.5 nm. The fluorescence intensity of CdSe QDs was found to decrease with an increasing concentration of MSP. The thermodynamic potentials  $\Delta H^\theta$  (–321.3 kJmol<sup>–1</sup>);  $\Delta S^\theta$  (156.0 JK<sup>–1</sup>mol<sup>–1</sup>) and  $\Delta G^\theta$  (–46.6 kJmol<sup>–1</sup>) were also calculated. The stability of the complex found, is strongly influenced by the electrostatics interaction and surface-bound complexation equilibrium attraction. This information can help to elucidate the surface characteristics of MSP and its potential interactions with other molecules or nanoparticles.

**Keywords:** *Moringa oleifera* protein; Cadmium-Selenium nanocrystals; quenching; luminescence; Stern-Volmer equation

## 1. Introduction

Quantum dots (QDs) are semiconductor nanoparticles with unique electronic and optical properties, which make them attractive for various applications, including electronics, optoelectronics, and biotechnology [1]. As a result, QDs have important applications in biological fluorophores imaging, tracking, and sensing. When QDs enter living systems, they first encounter proteins. The interactions between proteins and QDs significantly influence the structures and functions of the proteins, as well as the performance of the QDs [2]. It has been shown that the interaction of QDs with biological molecules can enhance optical properties and their stability or it may oppositely lead to their degradation [2,3]. However, the potential toxicity of these nanoparticles raises concerns about their safety for human health and the environment. The usage of Cd-based quantum dots may result in toxicity problems including cytotoxicity, environmental toxicity, and bioaccumulation. The toxicity of Cd-based quantum dots varies depending on factors such as concentration, exposure time, and physicochemical properties [4]. The main classification criteria for quantum dots are their core type, shape, structure, size, and ligands [5]. Due to material degradation, core-only quantum dots have been proven to be unstable [6]. Exposure to an oxidizing environment weakens the selenide layer on the surface of core-type quantum dots [7]. This causes leakage of cadmium ions from quantum dots such as CdSe QDs. The toxicity of cadmium quantum

dots may be caused by the hazardous cadmium ions they contain. To make secure QDs for widespread use, we need advanced surface components to prevent any core leakage. Recently, there has been a significant amount of research conducted on the implementation of an additional shell layer on the surface of Cd/Se quantum dots [8,9]. Adding a second shell layer, like a ligand, decreases the oxidation of Se and reduces the leakage of Cd ions [10]. The presence of ligands on the shells of quantum dots (QDs) enhances the stability of the QD dots. Although researchers have found that the shell and ligands of QDs can reduce toxicity by preventing core material leakage, some leakage can still happen [11]. For instead protein levels may drop below ideal levels for critical biological functions because of the creation of QD clusters. It is important to study how proteins and QDs interact to understand the overall effects of QDs on cells and tissues by understanding the physicochemical properties of the protein-metal-based quantum system [7]. A study recently published by Shivaji et al., [4] found that coating the Cd-based QDs with protein can prevent the core CdS QDs from photocorrosion, preventing the release of harmful Cd<sup>2+</sup> ions into the environment. The study used tea leaf extract, which is a practical method, to biofunctionalize the active surface of CdS QDs. According to the study, the chlorophyll/polyphenol moieties shielded the CdS QDs from photocorrosion and stopped the leaching of the Cd<sup>2+</sup> ions. The use of Cd-based quantum dots in water treatment has the potential to have negative environmental effects, which can be lessened with this strategy. However, more research is needed to understand and address the potential risks of using Cd-based quantum dots in water treatment. This is necessary to ensure their safe and sustainable use. Thus, the studies on the interactions between QDs and proteins thus, can provide a theoretical basis for the design, efficient application, and safety evaluation of QDs.

*Moringa oleifera* is a tropical plant that is widely used for its nutritional and medicinal properties. It has been shown to have coagulation properties, and cationic proteins extracted from its seeds have been used as a natural coagulant for water treatment [12–14]. Proteins extracted from the seeds of *Moringa oleifera* are of low molecular mass and are known to be effective agents in water treatment [12,13]. Previous studies have shown that *Moringa* seed proteins (MSP) exhibit peculiar properties and some of which include surface activity [15,16], conformational stability over a wide range of pH and ionic strength [17], proteins charge reversal by surfactant [18], adsorption and desorption depending on the surface type [19–25], amino acid composition [23], inducement of dense floc structures and high fractal dimensions [26] and recovery of cationic precious metals [27]. The solution acts as a natural cationic polyelectrolyte during wastewater treatment [28,29]. Recently, Thanki *et al.*, 2022 [30] investigated the effect of various operational parameters of MSP such as coagulation-flocculation pH (2–10), coagulant dosage (0.1–1.0 g L<sup>-1</sup>), optimized operational conditions and sedimentation kinetics suggesting that MSP can be employed as a promising coagulant for municipal wastewater with improved treatment efficiencies.

Despite many studies on the interaction of QDs with biological molecules [31], there has not been any investigation on the interactions *between Moringa oleifera* seed proteins (MSP) with QDs emanating from their respective unique properties applications articulated above and (potential) diverse applications. Detailed investigations are necessary due to many factors that affect the interaction mechanisms such as the size, surface charge and structure of QDs need to be explored for their obvious potential applications. Moreover, despite the remarkable studies done on nanocrystal QDs, little is known about the surface modification and the interaction mechanism of nanoparticles with macromolecules [32,33]. QD-protein hybrid bioconjugation at an atomic level has been studied for the dihydrolipoic acid (DHLLA) capped CdSe/ZnS core/shell QDs with maltose-binding protein in the gas phase using *ab initio* and ONIOM methods (that includes the IMOMM and IMOMO methods) as a potential candidate for enhanced light harvesting efficiency through theoretical investigation [34].

When CdSe quantum dots interact with cationic proteins extracted from *Moringa oleifera* seeds in water treatment, several processes may occur. One of the potential mechanisms is an electrostatic attraction between the positively charged cationic proteins and the negatively charged CdSe quantum dots. This attraction can lead to the formation of complexes between the two, which can affect the stability, aggregation, and reactivity of the nanoparticles [33]. In the case of water treatment

using MSP for which they are known, a drawback is that such organic materials and others from the extraction process are also an excellent source of nutrients for other bacterial regrowth, thus causing the water to foul quickly [35]. To eliminate this problem, the photocatalytic properties of the quantum dots can be considered as it can be able to destroy the bacteria. Thus, labelling the MSP with a photocatalyst semiconductor such as cadmium selenide quantum dots (CdSe QDs) may solve the problem of bacterial accumulation in water. It is known that proteins can chemically bind to many different surfaces as biomarkers [19–25]. When QDs are used as biomarkers, especially in vivo bio labelling, the interactions between small biomolecules in the biosystem and the surface of QDs may influence the efficiency of the electron-hole recombination process [32,36], leading to higher photocatalysis activity of the QDs. It is also important to bear in mind the possible toxicity of the protein-QDs system in water treatment applications.

This study focuses on the interactions of MSP with CdSe QDs, here referred to as the CdSe-MSP complex. The use of cationic proteins extracted from *Moringa oleifera* seeds as a model protein in the study of the interaction with CdSe quantum dots is a valid approach to understanding the physicochemical properties of the protein-nanoparticle system. The investigation of the interactions between CdSe QDs and MSP involved various experimental techniques to characterize the physicochemical properties of the complex system. Brunauer-Emmett-Teller (BET), Transmission electron microscopy (TEM), scanning electron microscope–Energy-dispersive X-ray spectroscopy (SEM–EDX), X-ray diffraction (XRD), UV-Vis, Fluorescence (FL) and the Fourier transform infrared (FTIR) spectroscopies techniques were employed in this research to obtain a comprehensive understanding of the physicochemical properties and mechanisms involved in the interaction between natural proteins and CdSe QDs. This information can be useful for the development of safer and more efficient QDs for various applications.

## 2. Materials and Methods

### 2.1. Chemical used

All chemicals and solvents were used as received without further purification and these were a stock solution of cadmium acetate dehydrate  $(\text{CH}_3\text{COO})_2\text{Cd}\cdot 2\text{H}_2\text{O}$ ,  $\geq 98\%$ , Merck), highly pure selenium powder (Se, 99.99% HPLC), trioctyl-n-phosphene oxide (TOPO, 99%, Aldrich), trioctylphosphine (TOP, 97%, Aldrich), hexadecyl amine (HDA, 98%, Aldrich), tetradecyl-phosphonic acid (TDPA, 97%, Aldrich), Octadecene (ODE, 90%, Merck), methanol, sodium chloride (NaCl), petroleum ether, ammonium sulfate  $(\text{NH}_4)_2\text{SO}_4$ , carboxymethylcellulose (CM-Cellulose micro granular 25–60  $\mu\text{m}$ , Biophoretics, USA), toluene and methanol. *M. oleifera* seeds were purchased from a local supplier in Windhoek, Namibia. All substances were dried and degassed before use to provide rigorously oxygen- and water-free conditions for the synthesis.

### 2.2. Synthesis of CdSe Quantum Dots

The CdSe quantum dots were synthesized in HDA-TOPO-TOP mixtures as a green chemical approach using the procedure initially reported by Mekis *et al* [37] and as modified by Gupta *et al* [38]. All synthetic routes were carried out in a dry environment. In a 50 mL three-neck flask, 5 g HDA, 8 g of TOPO, and 0.15 g TDPA were mixed as a one-pot synthesis. The mixture was dried at 120°C under vacuum for 20 min. The TOPSe stock solution was prepared by mixing selenium powder (2 g) in 5 mL of TOP and the mixture was heated to 270°C. The cadmium stock solution (2.5 g of  $\text{Cd}(\text{Ac})_2$  in 10 mL of TOP) was injected into the mixture while stirring, resulting in the nucleation of CdSe nanocrystals. Respective, the molar ratio between cadmium and selenium precursors was 1.4:1. The injection of the stock solution as well as the further nanocrystal growth, was carried out at 270°C. Finally, the red-coloured solution was obtained for CdSe QDs and washed several times with methanol, followed by centrifugation at 3000 rpm for 20 min. The washing was repeated three times. The above sediment was heated in a vacuum at 70°C for ca. 48 hrs.

### 2.3. Extraction and purification of MSP

The extraction and purification of protein powder, MSP, was done using the method of Ndabigengesere and Narasiah [39,40], and the experimental details are as described by Kwaambwa and Maikokera [15–17]. The procedure involves extraction with petroleum ether to remove oil, extraction of the proteins with water, precipitation of proteins with ammonium sulfate, filtration, dissolving the precipitate in water, dialysis to remove excess ammonium sulfate, adsorption through carboxymethyl cellulose column, and elution with 1M NaCl, dialysis and finally freeze-drying.

### 2.4. Synthesis of CdSe-MSP Complexes

The aqueous CdSe-MSP<sub>n</sub> complexes were prepared by mixing the increasing concentration of MSP<sub>n</sub> (n = 10, 25, 50, 80, 100 g L<sup>-1</sup>) with CdSe at a fixed concentration (5.23 x10<sup>-3</sup>M) dispersed in toluene; the complexes were prepared in a buffer solution at pH 8 [2]. The mixtures were subjected to an orbital shaker for agitation and homogenization at 25°C for 25 minutes at a speed of 150 rpm under a buffer solution at pH 8. The resultant aqueous CdSe-MSP (50 g L<sup>-1</sup>) was placed on the round bottom flask and subjected to the rotary evaporator at 120 rpm at a temperature of water bath of 40°C. The semi-solid CdSe-MSP was then subjected to freeze drying and the crystalline CdSe-MSP complexes were obtained.

### 2.5. Characterization of the synthesized CdSe QDs and CdSe-MSP complexes

The synthesized CdSe QDs were characterized for their crystal structure and phase using a Bruker D2 XRD instrument with radiation angle in the range of 0 to 60° at 2θ, using Bruker Eva software. XRD spectra were used to provide information on the phase of the QDs based on their diffraction pattern.

The nanostructure image of CdSe QD was observed with a transmission electron microscope (Tecnai 20 G<sup>2</sup> S-Twin TEM) at an accelerating voltage of 200 kV. The TEM image obtained was used to provide information on the size, shape, and uniformity of the QDs, as well as their crystal structure.

To observe the surface characteristics of the QDs, such as the presence of surface ligands, the CdSe-MSP<sub>50</sub> sample was prepared by drop-casting the QD-protein complex onto a carbon-coated copper grid. The surface morphology of the resultant complexes was then observed using a field-emission scanning electron microscope (JSM-IT300 SEM) equipped with Energy-dispersive X-ray spectroscopy (EDX) at an accelerating voltage of 5.0 kV.

### 2.6. Investigation of the interactions between CdSe QDs and MSP<sub>n</sub> complexes

The absorption spectra of CdSe QDs and CdSe-MSP complex samples were performed using a Perkin-Elmer Lambda 35 spectrometer to analyze the interference of MSP<sub>n</sub> in the optical property of the CdSe sample. The particle size of CdSe QDs was estimated from the UV-Vis absorption spectra recorded at 298 K temperature using Equation 1[26]:

$$D = (9.8127 \times 10^{-7})\lambda^3 - (1.7147 \times 10^{-3})\lambda^2 + (1.0064)\lambda - 194.84 \quad (1)$$

where D (nm) is the particle size of given CdSe QDs of 5.23 x10<sup>-3</sup> M and λ(nm) is the first exciton absorption peak of 546 nm.

Respective, the transition energies (band gaps) of given CdSe QD and CdSe-MSP<sub>n</sub> complexes were obtained by the plot of (ahv)<sup>2</sup> versus hv for direct transition and (ahv)<sup>1/2</sup> versus hv for indirect transition. The direct band gap and indirect band gap were obtained by extrapolating the linear region to the energy X-axis where (ahv)<sup>2</sup> = 0 and (ahv)<sup>1/2</sup> = 0, respectively.

The physical adsorption of nitrogen molecules and the surface area of the complexes were studied using the Brunauer-Emmett-Teller (BET) technique under the nitrogen gas (N<sub>2</sub>) on Micromeritics Trista 3000 instrument. Gas adsorption provides a distinct advantage as many classical models for particle measurement and characterization. The surface area and pore size of MSP were analyzed using the BET- surface area and the BET-isotherm plot. The area covered was calculated

by considering the amount of  $N_2$  molecules used to form the monolayer as well as the dimensions and the number of molecules.

The mechanisms of interaction between CdSe QDs and  $MSP_n$  were investigated by studying the physiochemical properties of the synthesized CdSe– $MSP$  complexes. The measurements for the emission spectra and intensity of steady-state fluorescence for CdSe QDs before and after mixing with  $MSP_n$  solutions were performed using a Perkin Elmer LS 45 spectrofluorophotometer with fast scan speed and low sensitivity. The CdSe– $MSP$  samples were excited at 280 nm and the emission range was 300–650nm, the path length of the cuvette was 1 cm. Fluorescence emission spectra were recorded at 298 K and 313 K temperatures.


FTIR technique was used to analyze the surface functional groups of the  $MSP_{50}$  and CdSe QDs before and after mixing. It also provides information on the nature and density of surface ligands on the CdSe QDs. The spectra were recorded in the range of 4000-500  $cm^{-1}$  using Opus software (version 6.5.6) on Bruker Platinum Tensor 27 ATR-IR Spectrophotometer.

### 3. Results and discussion

This section may be divided by subheadings. It should provide a concise and precise description of the experimental results, their interpretation, as well as the experimental conclusions that can be drawn.

#### 3.1. The structural and morphological characterization of CdSe QDs.

The X-ray diffraction pattern provides information about the crystalline phase of the synthesized CdSe quantum dots. Figure-1 shows the X-ray diffraction pattern of nanocrystalline CdSe QDs, contains three broad peaks at a diffraction angle of  $2\theta = 26.55^\circ$ ,  $43.87^\circ$  and  $51.93^\circ$  in correspondence to the Miller indices or plane (101), (110) and (112), respectively, for the bulk, CdSe QDs have a hexagonal (wurtzite) phase [22].



**Figure 1.** Powder X-ray diffraction pattern of CdSe QDs.

Figure 2 shows the EDX micrograph of CdSe QDs which reveals the elemental composition present in CdSe QDs. The ratio in percentage by weight (%) of Cd: Se was found to be 1:0.8 and also shows the presence of other elements such as carbon, oxygen phosphorus and chlorine which may have resulted from the organic solvents used such trioctyl-n-phosphene oxide, trioctylphosphine and other chemical reagents used during the synthesis of CdSe QDs. The elemental composition is summarized in the inserted table.




Figure 2. EDX micrograph of CdSe QDs.

The TEM image presented in Figure 3 was used to visualize the morphology and structure of CdSe QDs at the nanoscale level. This image provides information on the shape, size, and uniformity of the QDs crystal structure. The TEM image shows an even distribution of nearly spherical-shaped crystalline particles of CdSe QDs. The particle size was in the range of 4 -7 nm, which is similar to the crystal size of QDs reported [41]. Ideally, the CdSe QDs should be as uniform as possible to ensure consistent behaviour and properties. The variation in the particle size can be a result of the strain field [22]. The particle size of CdSe QDs was further estimated using UV–Vis absorption spectra and was found to be 3.0 nm. The same quantum dot material with different sizes showed distinct variations in their properties [41].





Figure 3. TEM micrograph of CdSe QDs.

### 3.2. The morphological characterization of MSP and CdSe–MSP complexes.


In the analysis of the surface area and pore size of MSP, the BET isotherm plot was employed to understand the physicochemical properties of the protein. Figure 4 depicts the adsorption isotherm of N<sub>2</sub> gas on MSP. It occurs in situations where interaction between the adsorbate molecules approaches that between adsorbate and adsorbent, i.e., the heat of adsorption is like the heat of condensation. Therefore, it is necessary to have a significant partial pressure of adsorbate before the adsorption process commences. Having the surface covered with adsorbate, the favourable adsorbed–adsorbate interaction would then lead to a very rapid adsorption process, as the partial pressure increases from 0.3 to 1.0 P/P<sub>0</sub>. This type of isotherm is typically observed when there is a limited number of available adsorption sites (MSP sites) on the surface, and the adsorbate molecules

(N<sub>2</sub>) begin to cluster or aggregate onto the surface, resulting in a lower adsorption capacity at higher concentrations [42].



**Figure 4.** Adsorption isotherm of N<sub>2</sub> gas on MSP.

Analysis of the experimental results using the BET equation gave a good straight-line data fit shown in Figure 5, over the partial pressure range 0.05–0.3. The BET isotherm, gives an accurate account of adsorption isotherm only within a restricted pressure range, i.e.  $0.05 \leq P/P_0 \leq 0.35$ . From the plot, the data are considered acceptable, since the square of a correlation coefficient,  $r^2$ , is not less than 0.995 [42]. The BET surface area of MSP was calculated to be 8.41 m<sup>2</sup>/g. The pore volume at single point adsorption total pore volume of pores less than 302 nm in diameter at  $P/P_0 = 0.9936$  was obtained to be 0.0245 cm<sup>3</sup>/g. The pore size of MSP<sub>50</sub> was calculated to be 11.7 nm, thus the *M. oleifera* seed coagulant protein is classified as mesoporous [31].




**Figure 5.** BET linear plot of the adsorption isotherm of N<sub>2</sub> gas on MSP.

This information can help to elucidate the surface characteristics of MSP and its potential interactions with other molecules or nanoparticles. Instead, it is expected that the mesoporous pores of MSP observed can be applied to host many guest molecules such as fluorescent imaging agents, including the recent synthesis CdSe QD (particle sizes 4–7 nm). Hence, the MSP has a higher adsorption capability toward other molecules such as surfactant and charged particle [32].

### 3.3. The structural and morphological characterization of CdSe–MSCP complexes.

To evaluate the CdSe QD for the presence of surface MSP<sub>n</sub>, the surface morphology of CdSe-MSP<sub>50</sub> was investigated using the SEM image presented in Figure 6; the image shows small particles of CdSe incorporated in the large MSP<sub>50</sub> matrix. It was then observed that there is no uniform


distribution of the particles of CdSe-MSP hence the complex is not a crystalline structure. The presence of MSP provides a protective layer around the nanoparticle, preventing aggregation and degradation and improving CdSE QD stability and biocompatibility [43]. MSP has a natural cationic protein [18] that can bind to the surface of CdSe QDs, stabilizing them and preventing aggregation or degradation. This binding is due to electrostatic interactions between the positively charged protein and the negatively charged surface of the QDs [44]. Thus, the MSP has a protective effect, preventing the CdSe QDs from interacting with other molecules or surfaces that may cause them to degrade or aggregate. In addition to improving stability, the presence of MSP has enhanced the biocompatibility of CdSe QDs [28], making them more suitable for biological applications. This is because MSP is a natural protein that is non-toxic and biocompatible, and therefore, its presence on the surface of CdSe QDs can reduce their toxicity and improve their biocompatibility.



**Figure 6.** The SEM image of CdSe-MSP<sub>50</sub>.

#### 3.4. Interaction between CdSe QDs and MSP using the UV-Vis absorption and fluorescence spectra

Figure 7 shows the well-defined absorption spectra of the CdSe QDs in the presence and absence of MSP at different concentrations. The well-defined spectra indicate that the QD dispersions are homogeneous and contain monodispersity nanocrystals. The first excitonic absorption peak centre is at 546. nm, corresponding to an absorption energy of 2.27 eV of CdSe QD. The absorption energy can be different as compared to pieces of literature depending on particle size and shape [30,41]. Upon the mixing of the CdSe solution with the different concentrations of MSP (10, 50 and 100 g/L), there was no new band observed. However, blue shifts in the absorption peaks and changes in the intensity of the maximum absorption band of CdSe QDs were observed. The shifts in the absorption spectra indicate the presence of strong interaction between CdSe QDs and MSP which can be attributed to molecular complexation in the formation of the CdSe-MSP stable conjugates. The resultant change in absorption intensity may indicate that the protein residues in the MSP were in the hydrophobic environment [36,36].



**Figure 6.** The UV-vis absorption spectra of pure CdSe QDs and CdSe-MSP<sub>n</sub> with the concentration of MSP<sub>n</sub> where n=10, 50 and 100 mg/mL, respectively.


The band gap structure of CdSe QDs and CdSe-MSP<sub>n</sub> was studied using the Tauc plot, to determine the energy of direct and indirect band gaps. As shown in Table 1, it was found that the direct band gap of CdSe QDs is 2.27 eV and the indirect band gap of 2.20 eV. The CdSe band gap decreased with the increase in the concentration of MSP. The formation of this complex can modify the electronic structure of the QDs, resulting in a change in their band gap energy [46]. These results indicate that CdSe QD interacts with MSP. The quenching of fluorescence emission results from the dynamic or static interaction between a quencher and fluorophore [47]. The quenching mechanisms between MSP and CdSe QDs were found to be dynamic quenching which is confirmed by the changes observed in the absorption spectra of the UV-Vis absorption analysis. This was further evaluated by fluorescence quenching experiments discussed as follows.

**Table 1.** Direct and indirect band gaps of CdSe QDs and CdSe-MSP complexes.

	Direct band gap	Indirect band gap
CdSe QDs	2.27	2.20
CdSe-MSP <sub>10</sub>	2.19	2.12
CdSe-MSP <sub>50</sub>	2.20	0.85
CdSe-MSP <sub>100</sub>	2.21	0.87

The intrinsic fluorescence intensity of the sample decreases due to the quenching of protein [16]. In this study, the intrinsic fluorescence of a protein originates mainly from tryptophan, phenylalanine and tyrosine amino acid residues, which often change upon interaction with nanocrystals [48]. To confirm this assertion, the interaction between CdSe QDs and MSP ligand was further studied using fluorescence quenching spectra. Figure 7 shows the fluorescence quenching spectra of the CdSe-MSP complexes at different concentrations. The result reflects that non-fluorescent CdSe-MSP complexes were formed due to quenching [49]. The inset figure demonstrates that the spectra have two emission peaks in the range of 280–400 nm wavelength, suggesting the presence of only two fluorescing proteins type in the solutions. The tyrosine residue emission can be seen in the spectra at 301 nm and the emission of MSP is dominated by tryptophan which absorbs at 343 nm [16]. This implies that the excitation of 280 nm selectively excites tryptophan and a minimum amount of tyrosine fluorescence. The contributors to the fluorescence of proteins are usually tryptophan, tyrosine and phenylalanine residues [16]. However, in this case, phenylalanine is not a significant contributor to the fluorescence spectra, since there is no emission peak at 280 nm. The fluorescence intensity reduced gradually with increased concentration of MSP, and a blue shift was also observed suggesting that the fluorescent CdSe nanocrystals are placed in a more hydrophobic environment after the addition of MSP, hence

energy transfer occurred [48]. Fluorescence quenching was therefore due to the formation of a non-fluorescent complex [47].



**Figure 7.** Fluorescence quenching spectra of CdSe nanocrystals in the presence and absence of MSP. The concentration of CdSe QDs =  $5.23 \times 10^{-3}$  M and excitation wavelength = 280 nm.

The fluorescence spectra of CdSe QDs in the absence and presence of MSP at different concentrations are shown in Figure 7 (the main spectra). The CdSe QD emission can be seen in the spectra at 598 nm [50]. At a very low concentration of  $10 \text{ gL}^{-1}$  (MSP<sub>10</sub>), there was a minimal decrease in fluorescence intensity compared to pure CdSe QD. However, sudden decreases in the fluorescence intensities were observed at a higher concentration of MSP (MSP<sub>100</sub>). Thus fluorescence quenching is higher at high concentrations of MSP. The quenching of fluorescence emission results from the dynamic interaction between a quencher and fluorophore [47]. In many interaction studies of quantum dots and protein, QDs have quenched the protein [50]. When QDs are near a protein, their fluorescence emission can be quenched due to energy transfer from the QD to the MSP.

In many interaction studies of quantum dots and protein, QDs have quenched the protein [49,50]. In the previous studies, we have used standard quenchers, viz. acrylamide, iodide and nitrate, to quench the fluorescence of the Moringa seed proteins [15], whereas, in the present study, the FL spectra showed a strong quenching effect of MSP in the fluorescence of CdSe QDs which is higher at MSP<sub>100</sub>. According to the study by Yan *et al* 2012 [51], the combination of protein with QDs interaction changes the external environment and structure of a protein, which yields in decrease fluorescence intensity. Hence, a similar explanation can be applied in the quenching between MSP and CdSe QDs. There exists a strong interaction between CdSe QDs and MSP as reflected by the steady decrease in fluorescence intensity that give rise to the quenching mechanisms [46]. The quenching effect may result from many molecular interaction mechanisms, such as surface-bound complexation equilibrium, ground state complex formation, molecular rearrangement, the electrostatic interaction and the energy transfer process [35,37,38,46] between the CdSe QDs and MSP.


### 3.5. Stern-Volmer Analysis of the CdSe QDs –MSP system interactions

The stern-Volmer plot of  $F_0/F$  against CdSe–MSP system with different concentrations of MSP was employed to provide valuable insights into the nature and strength of the interaction between these two components and determine the binding constant and quenching constants between a fluorophore (in this case, CdSe quantum dots) and a quencher (MSP) [19]. To perform the Stern-Volmer analysis, the fluorescence quenching intensity ( $F_0$ ) of the CdSe QDs in the absence and presence of different concentrations of MSP ( $F_{10,25,50,80,100}$ ) were extracted from Figure 7, and the data

was plotted on a Stern-Volmer plot shown in Figure 8 based on the Stern-Volmer equation presented in equation 2:

$$\frac{F_0}{F} = 1 + k_q \tau_0 [Q] = 1 + K_{sv} [Q] \quad (2)$$

Where  $F_0$  is the fluorescence intensity of CdSe QDs in the absence of the quencher,  $F$  is the fluorescence intensity of CdSe QD in the presence of the quencher,  $K_{sv}$  is the Stern-Volmer quenching constant,  $[Q]$  is the concentration of the quencher and  $K_q$  is protein quenching rate constant and  $\tau_0$  is the average lifetime of the fluorophore in the excited state usually for a biomolecule it is  $10^{-8}$  s. By plotting  $F_0/F$  against  $[Q]$ , the Stern-Volmer constant ( $K_{sv}$ ) was determined from the slope of the linear fit.



**Figure 8.** Stern-Volmer equation analysis of the CdSe-MSP system: the figure shows the plot of the ratio for relative fluorescence ( $F_0/F$ ) versus increasing concentration of MSP in mg/mL.

The Stern-Volmer plot presented establishes that there is a linear relationship between the relative fluorescence of a fluorophore (CdSE nanocrystals) intensity and concentration of quencher (MSP). At a very low concentration of the MSP ( $10$  and  $25$   $\text{g/L}^{-1}$ ), there was no significant change in the quenching effect, which suggests that there is minimal quenching to nearly stationed fluorescence quenching [39]. Therefore, at low concentrations and a very rare chance of conformational change it shows stationary fluorescence quenching then at higher concentrations due to structural rigidity steric hindrance may occur against acquiring electrostatic interaction with CdTe QDs because of high affinity towards them [3]. A steady increase in the quenching effect was observed upon the increase in the concentration of MSP ( $50$   $\text{g/L}$  to  $100$   $\text{g/L}$ ) which suggest a strong interaction and conformational change in the MSP structure and hence it indicates the possible existence of more binding sites and a higher affinity of MSP toward the CdSe QDs [40]. The Stern-Volmer quenching constant ( $K_{sv}$ ) was obtained as  $0.0235$ . The complex formation was further confirmed from the value of rate constant  $K_q$ , using equation 3:

$$K_q = \frac{K_{sv}}{\tau} \quad (3)$$

The binding constant ( $K_b$ ) and the quenching constant ( $K_q$ ) were also determined as  $1.78 \times 10^5$   $\text{mL/mg}$  and  $1.97 \times 10^7$   $\text{Lg}^{-1}$ , respectively. The fluorescence lifetime ( $\tau_0$ ) of the excited state of CdSe QDs in absence of MSP was also derived from a Stern-Volmer analysis and was found to be  $\tau_0 = 1.91 \times 10^{-9}$   $\text{s}^{-1}$ .

The quenching mechanisms of MSP with CdSe QDs were analysed using the modified Stern-Volmer equation known as the Scatchard method (equation 4–8) [30]. The number of binding sites ( $n$ ) and the static quenching constant ( $K$ ) which is the equilibrium constant in this present paper were

calculated using the Scatchard relation approximation. The thermodynamic parameter the Gibbs free energy  $\Delta G^\theta$ , the enthalpy change  $\Delta H^\theta$ , and the entropy change  $\Delta S^\theta$  were calculated using the equations below:

$$\log \left( \frac{F_0 - F}{F} \right) = \text{Log}K + n \log [Q] \quad (4)$$


$$\Delta G^\theta = -RT \ln K \quad (5)$$

$$\ln \left( \frac{K_2}{K_1} \right) = \left( \frac{1}{T_2} - \frac{1}{T_1} \right) \frac{\Delta H^\theta}{R} \quad (6)$$

$$\ln K^\theta = -\frac{\Delta H^\theta}{RT} + \frac{\Delta S^\theta}{R} \quad (7)$$

$$\Delta G^\theta = \Delta H^\theta - T\Delta S^\theta \quad (8)$$

where T is the temperature in (K) and R is the gas constant  $8.314 \text{ JK}^{-1}\text{mol}^{-1}$ . The interaction was carried temperatures 298.15 K and 313.15 K. From the Scatchard relation plot [33], equation (4) was equated to the equation of a straight line, thus the slope is equal to n and the y-intercept is a log. Therefore, the number of binding sites (n), and the binding constant which is also referred to as the equilibrium constant (K) was obtained. The Scatchard relation is represented by plotting of  $\log [(F_0-F)/F]$  versus  $\log [Q]$  at temperature 298.1 K and 313.15 K respectively as shown in Figure 9.




**Figure 9.** Scatchard relation represented by the plot of  $\log [(F_0-F)/F]$  versus  $\log [Q]$  at temperature 298.1 K and 313.15 K respectively.

The steady decrease in the fluorescence of CdTe QDs after interaction with MSP strongly indicates that some conformational changes are occurring due to the interaction suggesting the availability of more binding sites for CdTe QDs [3]. The number of binding sites was found to be 1.50 and 2.00 at temperatures 298.15 K and 313.15 K, respectively. The quenching constant was determined as  $K = 1.45 \times 10^8$  and  $7.21 \times 10^{10}$  at temperature (T) 298.15 K and 313.15 K, respectively. This implies that the system is dynamic quenching since the quenching constants tend to increase with temperature as higher temperature results in a larger diffusion coefficient. The enthalpy change ( $\Delta H^\theta$ ) was calculated to be  $-321.3 \text{ kJmol}^{-1}$ , a negative value and  $\Delta S^\theta$  was found to be  $156.0 \text{ JK}^{-1}\text{mol}^{-1}$  a positive value, based on these values, there is an indication that the binding mechanisms of MSP with CdSe QDs are entropically driven [40]. The change in Gibbs free energy ( $\Delta G^\theta$ ) was calculated to be  $-46.6 \text{ kJmol}^{-1}$  at 298.15 K and  $-65.1 \text{ kJmol}^{-1}$  at 313.15 K; a negative value indicates that the binding interaction is spontaneous [41]. The negative values of both  $\Delta H^\theta$  and  $\Delta G^\theta$  reveal that the major interaction mechanisms are the electrostatic interaction, van der Waals forces and hydrophobic interaction [37–40].

### 3.6. FTIR analysis of the CdSe QDs –MSP system interactions

To study the mechanism of electrostatic interactions of CdSe QDs with proteins at different concentrations, FTIR spectra of MSP, CdSe QDs, and CdSe-MSP<sub>50</sub>, were determined as shown in Figure 10.



**Figure 10.** Diagram represents the FTIR spectra of (a) MOCP; (b) CdSe-MOCP; (c) CdSe QDs.

In the case of MSP, Figure 10(a) shows notable absorption peaks of the phenol group at 3293.85  $\text{cm}^{-1}$ , primary amine at 1648.76  $\text{cm}^{-1}$ , 1535.75  $\text{cm}^{-1}$  nitro group and an Aliphatic amine at 1234  $\text{cm}^{-1}$ . The functional group of the two absorption bands at 1648.76  $\text{cm}^{-1}$  and 1535.75  $\text{cm}^{-1}$ , can also be related and show the presence of the amide I and amide II functional groups. The band at 1535.75  $\text{cm}^{-1}$  can also indicate the presence of the  $\alpha$ -helices [42]. In comparison, Kwaambwa and Maikokera [43] showed the presence of  $\alpha$ -helix secondary structure given by band at 1291  $\text{cm}^{-1}$ , which is absent in the FTIR spectrum of MSP, thus phenylalanine residues were not detected in the PL spectra in this study. The difference in the extracted structures of MSPs depends on the method of extraction and purification techniques used.

Figure 10(b) shows the spectrum of CdSe-MSP at a concentration of 50  $\text{mg/mL}$  of protein. The spectrum is identical to the one of MSP, hence a conclusion can be drawn that there is no new functional group between the CdSe QDs and MSP [44]. The formation of the new bond could have changed the CdSe-MSP spectrum thus the CdSe QDs did not influence the chemical structure of MSP. CdSe QDs are adsorbed into the MSP utilizing electrostatic interaction and surface-bound complexation equilibrium attractions which correlate to the fluorescence quenching mechanisms and the UV-Vis absorption spectra results [34].

## 4. Conclusions

The CdSe QDs were synthesized using the organic solvent trioctyl-n-phosphine oxide (TOPO) and trioctylphosphine (TOP). The crystalline size of CdSe QDs was determined by UV-Vis absorption to be in the range of 3.0 nm. XRD analysis revealed that CdSe QDs have a hexagonal phase with a particle size of 3.0-8.0 nm. The TEM image showed an even distribution, and the spherical surface of

CdSe QDs and confirmed the crystalline size CdSe QDs at a 10 nm scale. The BET analysis determined the surface area and pore size of MSP and it was classified as mesoporous. The SEM image indicated that the CdSe-MSP complex is not a crystalline structure. The interaction of CdSe QDs with the increasing concentration of MSP showed a decrease in fluorescence intensity which is classified as dynamic quenching. The Stern-Volmer quenching constant ( $K_{sv}$ ), binding constant ( $K_b$ ), quenching constant ( $K_q$ ) and the number of binding sites ( $n$ ) were determined, demonstrating the formation of CdSe-MSP complex, which proved the UV-Vis absorption spectra. The thermodynamic potentials were calculated using the Scatchard equation,  $\Delta G^\circ < 0$ ,  $\Delta H^\circ < 0$  and  $\Delta S^\circ > 0$  which indicates that the binding mechanisms in entropically favoured and spontaneous; it further demonstrated that the stable CdSe-MSP complex is a result of electrostatic interaction, molecular complexation and presence of hydrophobic interaction and Van der Waals forces. From the Scatchard relation plot of  $\log [(F_0-F)/F]$  versus  $\log [Q]$  at temperature 298.1 K and 313.15 K, respectively, the slopes ( $K_{sv}$ ) obtained do not depend on the concentration of MSP in dynamic quenching, whereas they do not change at any concentration of MSP in static quenching. The results obtained here confirm that the quenching of the CdSe by MSP is a dynamic process. Overall, the study of the interaction between MSP and CdSe QDs can contribute to the development of safer and more efficient nanoparticles for various applications, as well as provide a deeper understanding of the complex processes involved in the interaction between natural proteins and nanoparticles. Through the application of bioengineering, there is a potential that MSP can still retain the coagulation/flocculation properties while the CdSe acts as a photocatalyst response in killing the waterborne bacteria since it can enhance light harvesting efficiency.

**Supplementary Materials:** The following supporting information can be downloaded at the website of this paper posted on Preprints.or. Table S1: BET analysis Isotherm linear plot (Moringa Adsorption); Table S2: BET MOCP Surface Area plot; Table S3: Fluorescence spectra intensities of CdSe-MSP<sub>n</sub> System; Table S4: Scatchard relation plot for determination of thermodynamic potentials at T=298.15; Table S4: Scatchard relation plot for determination of thermodynamic potentials at T=313.15.

**Author Contributions:** Conceptualization, L.S.D, K.S., KM and KH.; methodology, KS, KH.; validation, LSD and KH.; formal analysis, KS and L.S.D.; investigation, KS, LSD; resources, KH; data curation, L.S.D, KH; writing—original draft preparation, KS and L.S.D.; writing—review and editing, L.S.D. and KH.; supervision, KH, LSD, KM.; project administration, KH and L.S.D. All authors have read and agreed to the published version of the manuscript.

**Funding:** National Commission of Science and Technology (NCRST): NCRST Capacity Building Research Grant.

**Data Availability Statement:** Not applicable

**Acknowledgments:** Authors are grateful to the UNAM and NUST for providing support and facility to conduct this research and the Centre of Research Service (CRS) for providing technical help and support. This research received external funding from National Commission Research Science and Technology (NCRST), under the call to strengthen research capacity at universities and research institutions (April 2017 to March 2020). Research project titled “Renewable Energy Initiative Project.”

**Conflicts of Interest:** The authors declare no conflict of interest.

## References

1. Bera D, Qian L, Tseng TK, Holloway PH. Quantum dots and their multimodal applications: a review. *Materials*. 2010 Apr;3(4):2260-345. <https://doi.org/10.3390/ma3042260>
2. Poderys V, Matulionyte M, Selskis A, Rotomskis R. Interaction of water-soluble CdTe quantum dots with bovine serum albumin. *Nanoscale Res Lett*. 2011 Dec;6:1-6. <http://www.nanoscalereslett.com/content/6/1/9>
3. Joglekar SS, Gholap HM, Alegaonkar PS, Kale AA. The interactions between CdTe quantum dots and proteins: understanding nano-bio interface. *AIMS Materials Science*. 2017;4(1):209-22. doi: 10.3934/matserci.2017.1.209
4. Shivaji, K., Sridharan, K., Kirubakaran, D. D., Velusamy, J., Emadian, S. S., Krishna-murthy, S., ... & Pitchaimuthu, S. (2023). Biofunctionalized CdS Quantum Dots: A Case Study on Nanomaterial Toxicity in the Photocatalytic Wastewater Treatment Process. *ACS omega*. <https://pubs.acs.org/doi/10.1021/acsomega.3c00496>.

5. Vasudevan, D., Gaddam, R. R., Trinchi, A., & Cole, I. (2015). Core-shell quantum dots: Properties and applications. *Journal of Alloys and Compounds*, 636, 395-404.
6. Wang, Z., & Tang, M. (2021). The cytotoxicity of core-shell or non-shell structure quantum dots and reflection on environmental friendly: A review. *Environmental Research*, 194, 110593.
7. Le, N., Zhang, M., & Kim, K. (2022). Quantum dots and their interaction with biological systems. *International Journal of Molecular Sciences*, 23(18), 10763.
8. Ratnesh, R. K., & Mehata, M. S. (2017). Synthesis and optical properties of core-multi-shell CdSe/CdS/ZnS quantum dots: Surface modifications. *Optical Materials*, 64, 250-256.
9. Liu, G., Liang, W., Xue, X., Rosei, F., & Wang, Y. (2021). Atomic Identification of Interfaces in Individual Core@ shell Quantum Dots. *Advanced Science*, 8(22), 2102784.
10. Joglekar, S. S., Gholap, H. M., Alegaonkar, P. S., & Kale, A. A. (2017). The interactions between CdTe quantum dots and proteins: understanding nano-bio interface. *AIMS Materials Science*, 4(1), 209-222.
11. Derfus, A. M., Chan, W. C., & Bhatia, S. N. (2004). Probing the cytotoxicity of semiconductor quantum dots. *Nano letters*, 4(1), 11-18.
12. Ndabigengesere, A., Narasiah, K. S. and Talbot, B. G. (1995). Active agents and mechanism of coagulation of turbid waters using *Moringa oleifera*. *Water Research*, 29(2), 703-710. [https://doi.org/10.1016/0043-1354\(94\)00161-Y](https://doi.org/10.1016/0043-1354(94)00161-Y)
13. Sánchez-Martín, J., Beltrán-Heredia, J., and Peres, J. A. (2012). Improvement of the flocculation process in water treatment by using *Moringa oleifera* seeds extract. *Brazilian Journal of Chemical Engineering*, 29(3), 495-502. <https://doi.org/10.1590/S0104-66322012000300006>
14. El Bouaidi, W., Libralato, G., Tazart, Z., Enaime, G., Douma, M., Ounas, A., ... & Loudiki, M. (2022). Nature-based coagulants for drinking water treatment: An ecotoxicological overview. *Water Environment Research*, 94(8), e10782. <https://doi.org/10.1002/wer.10782>
15. Maikokera, R., & Kwaambwa, H. M. (2007). Interfacial properties and fluorescence of a coagulating protein extracted from *Moringa oleifera* seeds and its interaction with sodium dodecyl sulphate. *Colloids and Surfaces B: Biointerfaces*, 55(2), 173-178. <https://doi.org/10.1016/j.colsurfb.2006.11.029>
16. Kwaambwa, H. M., & Maikokera, R. (2007). A fluorescence spectroscopic study of a coagulating protein extracted from *Moringa oleifera* seeds. *Colloids and surfaces B: Biointerfaces*, 60(2), 213-220. <https://doi.org/10.1016/j.colsurfb.2007.06.015>
17. Kwaambwa, H. M., & Maikokera, R. (2008). Infrared and circular dichroism spectroscopic characterisation of secondary structure components of a water treatment coagulant protein extracted from *Moringa oleifera* seeds. *Colloids and Surfaces B: Biointerfaces*, 64(1), 118-125. <https://doi.org/10.1016/j.colsurfb.2008.01.014>
18. Kwaambwa, H. M., & Rennie, A. R. (2012). Interactions of surfactants with a water treatment protein from *Moringa oleifera* seeds in solution studied by zeta-potential and light scattering measurements. *Biopolymers*, 97(4), 209-218. <https://doi.org/10.1002/bip.22014>
19. Kwaambwa, H. M., Hellsing, M., & Rennie, A. R. (2010). Adsorption of a water treatment protein from *Moringa oleifera* seeds to a silicon oxide surface studied by neutron reflection. *Langmuir*, 26(6), 3902-3910. <https://doi.org/10.1021/la9031046>
20. Jerri, H. A., Adolfsen, K. J., McCullough, L. R., Velegol, D., & Velegol, S. B. (2012). Antimicrobial sand via adsorption of cationic *Moringa oleifera* protein. *Langmuir*, 28(4), 2262-2268. <https://doi.org/10.1021/la2038262>
21. Kwaambwa, H. M., Hellsing, M. S., Rennie, A. R., & Barker, R. (2015). Interaction of *Moringa oleifera* seed protein with a mineral surface and the influence of surfactants. *Journal of colloid and interface Science*, 448, 339-346. <https://doi.org/10.1016/j.jcis.2015.02.033>
22. Moulin, M., Mossou, E., Signor, L., Kieffer-Jaquinod, S., Kwaambwa, H. M., Nermark, F., ... & Rennie, A. R. (2019). Towards a molecular understanding of the water purification properties of *Moringa* seed proteins. *Journal of Colloid and Interface Science*, 554, 296-304. <https://doi.org/10.1016/j.jcis.2019.06.071>
23. Nordmark, B. A., Bechtel, T. M., Riley, J. K., Velegol, D., Velegol, S. B., Przybycien, T. M., & Tilton, R. D. (2018). *Moringa oleifera* seed protein adsorption to silica: effects of water hardness, fractionation, and fatty acid extraction. *Langmuir*, 34(16), 4852-4860. <https://doi.org/10.1021/acs.langmuir.8b00191>
24. Nouhi, S., Pascual, M., Hellsing, M. S., Kwaambwa, H. M., Skoda, M. W., Höök, F., & Rennie, A. R. (2018). Sticking particles to solid surfaces using *Moringa oleifera* proteins as a glue. *Colloids and Surfaces B: Biointerfaces*, 168, 68-75. <https://doi.org/10.1016/j.colsurfb.2018.01.004>
25. Nouhi, S., Kwaambwa, H. M., Gutfreund, P., & Rennie, A. R. (2019). Comparative study of flocculation and adsorption behaviour of water treatment proteins from *Moringa peregrina* and *Moringa oleifera* seeds. *Scientific reports*, 9(1), 17945. <https://doi.org/10.1038/s41598-019-54069-2>
26. Hellsing, M. S., Kwaambwa, H. M., Nermark, F. M., Nkoane, B. B., Jackson, A. J., Wasbrough, M. J., ... & Rennie, A. R. (2014). Structure of flocs of latex particles formed by addition of protein from *Moringa* seeds. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 460, 460-467. <https://doi.org/10.1016/j.colsurfa.2013.11.038>

27. Amuanyena, M. O., Kandawa-Schulz, M., & Kwaambwa, H. M. (2019). Magnetic iron oxide nanoparticles modified with Moringa seed proteins for recovery of precious metal ions. *Journal of Biomaterials and Nanobiotechnology*, 10(02), 142. <https://doi.org/10.4236/jbnb.2019.102008>
28. Drbohlovova, J., Adam, V., Kizek, R., & Hubalek, J. (2009). Quantum dots—characterization, preparation and usage in biological systems. *International journal of molecular sciences*, 10(2), 656-673. <https://doi.org/10.3390/ijms10020656>
29. Sutherland, J. P., Folkard, G. K., & Grant, W. D. (1990). Natural coagulants for appropriate water treatment: a novel approach. *Waterlines*, 8(4), 30-32.
30. Thanki, A., Padhiyar, H., Singh, N. K., Yadav, M., & Christian, J. (2022). Municipal Wastewater Treatment Using *Moringa oleifera* Seed and Press Cake Powder: A Comparative Analysis. *CLEAN—Soil, Air, Water*, 2100336. <https://doi.org/10.1002/clen.202100336>
31. Rosenthal, S. J., Chang, J. C., Kovtun, O., McBride, J. R., & Tomlinson, I. D. (2011). Biocompatible quantum dots for biological applications. *Chemistry & biology*, 18(1), 10-24. <https://doi.org/10.1016/j.chembiol.2010.11.013>
32. Joglekar, S. S., Gholap, H. M., Alegaonkar, P. S., & Kale, A. A. (2017). The interactions between CdTe quantum dots and proteins: understanding nano-bio interface. *AIMS Materials Science*, 4(1), 209-222. <https://doi.org/10.3934/mat.2017.1.209>
33. Lohse, S. E., & Murphy, C. J. (2012). Applications of colloidal inorganic nanoparticles: from medicine to energy. *Journal of the American Chemical Society*, 134(38), 15607-15620. <https://doi.org/10.1021/ja307589n>
34. Kathiresan, R., Gopalakrishnan, S., & Kolandaivel, P. (2017). Interaction and bioconjugation of CdSe/ZnS core/shell quantum dots with maltose-binding protein. *Computational and Theoretical Chemistry*, 1101, 96-101. <https://doi.org/10.1016/j.comptc.2016.12.038>
35. Wang, Y., Zheng, J., Zhang, Z., Yuan, C., & Fu, D. (2009). CdTe nanocrystals as luminescent probes for detecting ATP, folic acid and l-cysteine in aqueous solution. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 342(1-3), 102-106. <https://doi.org/10.1016/j.colsurfa.2009.04.020>
36. Liang J, Cheng Y, Han H. Study on the interaction between bovine serum albumin and CdTe quantum dots with spectroscopic techniques. *Journal of Molecular Structure*. 2008; 892(1-3); 116-120. <https://doi.org/10.1016/j.molstruc.2008.05.005>
37. Mekis, I., Talapin, D. V., Kornowski, A., Haase, M., & Weller, H. (2003). One-pot synthesis of highly luminescent CdSe/CdS core-shell nanocrystals via organometallic and “Greener” chemical approaches. *The Journal of Physical Chemistry B*, 107(30), 7454-7462. <https://doi.org/10.1021/jp0278364>
38. Gupta, D. K., Verma, M., Sharma, K., & Saxena, N. S. (2017). Synthesis, characterization and optical properties of CdSe/CdS and CdSe/ZnS core-shell nanoparticles. *Indian Journal of Pure & Applied Physics (IJPAP)*, 55(2), 113-121. <https://doi.org/10.56042/ijpap.v55i2.14671>
39. Ndabigengesere, A., & Narasiah, K. S. (1998). Use of *Moringa oleifera* seeds as a primary coagulant in wastewater treatment. *Environmental Technology*, 19(8), 789-800. <https://doi.org/10.1080/09593331908616735>
40. Ndabigengesere, A., & Narasiah, K. S. (1998). Quality of water treated by coagulation using *Moringa oleifera* seeds. *Water research*, 32(3), 781-791. [https://doi.org/10.1016/S0043-1354\(97\)00295-9](https://doi.org/10.1016/S0043-1354(97)00295-9)
41. Yuan, G., Gomez, D., Kirkwood, N., & Mulvaney, P. (2018). Tuning single quantum dot emission with a micromirror. *Nano Letters*, 18(2), 1010-1017. <https://doi.org/10.1021/acs.nanolett.7b04482>
42. Naderi, M. (2015). Surface area: Brauer–emmett–teller (BET). In *Progress in filtration and separation* (pp. 585-608). *Academic Press*. <https://doi.org/10.1016/B978-0-12-384746-1.00014-8>
43. Yu, M., Saeed, M. H., Zhang, S., Wei, H., Gao, Y., Zou, C., ... & Yang, H. (2022). Luminescence enhancement, encapsulation, and patterning of quantum dots toward display applications. *Advanced Functional Materials*, 32(13), 2109472. <https://doi.org/10.1002/adfm.202109472>
44. Wang, H., Nienhaus, K., Shang, L., & Nienhaus, G. U. (2022). Highly Luminescent Positively Charged Quantum Dots Interacting with Proteins and Cells. *Chinese Journal of Chemistry*, 40(22), 2685-2693. <https://doi.org/10.1002/cjoc.202200350>
45. Lima, C. N., Cabral Filho, P. E., Santos, B. S., Moura, P., & Fontes, A. (2019). Interactions of mannose binding-lectin with red blood cells by employing cationic quantum dots. *International Journal of Biological Macromolecules*, 125, 1168-1174. <https://doi.org/10.1016/j.ijbiomac.2018.12.098>
46. Dzagli, M. M., Canpean, V., Iosin, M., Mohou, M. A., & Astilean, S. (2010). Study of the interaction between CdSe/ZnS core-shell quantum dots and bovine serum albumin by spectroscopic techniques. *Journal of Photochemistry and Photobiology A: Chemistry*, 215(1), 118-122. <https://doi.org/10.1016/j.jphotochem.2010.08.008>
47. Lai, L., Lin, C., Xu, Z. Q., Han, X. L., Tian, F. F., Mei, P., ... & Liu, Y. (2012). Spectroscopic studies on the interactions between CdTe quantum dots coated with different ligands and human serum albumin. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*, 97, 366-376. <http://dx.doi.org/10.1016/j.saa.2012.06.025>

48. Siddiqui, G. A., Siddiqi, M. K., Khan, R. H., & Naeem, A. (2018). Probing the binding of phenolic aldehyde vanillin with bovine serum albumin: Evidence from spectroscopic and docking approach. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*, 203, 40-47. <https://doi.org/10.1016/j.saa.2018.05.023>
49. Hu, Y. J., Ou-Yang, Y., Dai, C. M., Liu, Y., & Xiao, X. H. (2010). Binding of berberine to bovine serum albumin: spectroscopic approach. *Molecular biology reports*, 37, 3827-3832. <https://link.springer.com/article/10.1007/s11033-010-0038-x>
50. Chu, V. H., Lien Nghiem, T. H., Le, T. H., Lam Vu, D., Nhung Tran, H., & Lien Vu, T. K. (2012). Synthesis and optical properties of water-soluble CdSe/CdS quantum dots for biological applications. *Advances in natural sciences: nanoscience and nanotechnology*, 3(2), 025017. <https://doi.org/10.1088/2043-6262/3/2/025017>
51. Yan, H., Wu, J., Dai, G., Zhong, A., Chen, H., Yang, J., & Han, D. (2012). Interaction mechanisms of ionic liquids [Cnmim] Br (n= 4, 6, 8, 10) with bovine serum albumin. *Journal of Luminescence*, 132(3), 622-628. <https://doi.org/10.1016/j.jlumin.2011.10.026>

**Disclaimer/Publisher's Note:** The statements, opinions and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of MDPI and/or the editor(s). MDPI and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions or products referred to in the content.