

Article

Not peer-reviewed version

# Fabrication and Characterization of Porous PEGDA Hydrogels for Articular Cartilage Regeneration

Silvia Gonella , Margarida F. Domingues , Filipe Miguel , [Carla S. Moura](#) , [Carlos A.V. Rodrigues](#) , [Frederico Castelo Ferreira](#) , [João C. Silva](#) \*

Posted Date: 18 April 2024

doi: 10.20944/preprints202404.1210.v1

Keywords: Articular cartilage tissue engineering; Biocompatibility tests; Chondrogenic differentiation; Gas foaming; Hydrogels; Mesenchymal stem/stromal cells; Polyethylene glycol diacrylate



Preprints.org is a free multidiscipline platform providing preprint service that is dedicated to making early versions of research outputs permanently available and citable. Preprints posted at Preprints.org appear in Web of Science, Crossref, Google Scholar, Scilit, Europe PMC.

Copyright: This is an open access article distributed under the Creative Commons Attribution License which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

## Article

# Fabrication and Characterization of Porous PEGDA Hydrogels for Articular Cartilage Regeneration

Silvia Gonella <sup>1,2,†</sup>, Margarida F. Domingues <sup>1,2,†</sup>, Filipe Miguel <sup>1,2</sup>, Carla S. Moura <sup>3,4,5</sup>, Carlos A.V. Rodrigues <sup>1,2</sup>, Frederico Castelo Ferreira <sup>1,2</sup> and João C. Silva <sup>1,2,\*</sup>

<sup>1</sup> Department of Bioengineering and iBB-Institute for Bioengineering and Biosciences, Instituto Superior Técnico, Universidade de Lisboa, Av. Rovisco Pais, 1049-001 Lisboa, Portugal

<sup>2</sup> Associate Laboratory i4HB – Institute for Health and Bioeconomy, Instituto Superior Técnico, Universidade de Lisboa, Av. Rovisco Pais, 1049-001 Lisboa, Portugal

<sup>3</sup> Polytechnic Institute of Coimbra, Applied Research Institute, Rua da Misericórdia, Lagar dos Cortiços – S. Martinho do Bispo, 3045-093 Coimbra, Portugal

<sup>4</sup> CDRSP-Centre for Rapid and Sustainable Product Development, Polytechnic of Leiria, Rua de Portugal-Zona Industrial, 2430-028 Marinha Grande, Portugal

<sup>5</sup> Research Centre for Natural Resources Environment and Society (CERNAS), Polytechnic Institute of Coimbra, Bencanta, 3045-601 Coimbra, Portugal

\* Correspondence: joao.f.da.silva@tecnico.ulisboa.pt

† These authors contributed equally to this work.

**Abstract:** Functional articular cartilage regeneration remains an unmet medical challenge, increasing the interest for innovative biomaterial-based tissue engineering (TE) strategies. Hydrogels, 3D macromolecular networks with hydrophilic groups, present articular cartilage-like features such as high water content and load-bearing capacity. In this study, 3D porous polyethylene glycol diacrylate (PEGDA) hydrogels were fabricated combining the gas foaming technique and an UV-based crosslinking strategy. The 3D porous PEGDA hydrogels were characterized in terms of their physical, structural and mechanical properties. Our results showed that the size of the hydrogels pores can be modulated by varying the initiator concentration. In vitro cytotoxicity tests showed that 3D porous PEGDA hydrogels presented high biocompatibility both with human chondrocytes and osteoblast-like cells. Importantly, the 3D porous PEGDA hydrogels supported the viability and chondrogenic differentiation of human bone marrow-derived mesenchymal stem/stromal cells (hBM-MSCs)-based spheroids as demonstrated by the positive staining of typical cartilage extracellular matrix (ECM) (glycosaminoglycans (GAGs)) and upregulation of chondrogenesis marker genes. Overall, the produced 3D porous PEGDA hydrogels presented cartilage-like mechanical properties and supported MSC-spheroid chondrogenesis, highlighting their potential as suitable scaffolds for cartilage TE or disease modelling strategies.

**Keywords:** articular cartilage tissue engineering; biocompatibility tests; chondrogenic differentiation; gas foaming; hydrogels; mesenchymal stem/stromal cells; polyethylene glycol diacrylate

## 1. Introduction

Articular cartilage (AC) is a specialized connective tissue that covers the bone extremities within diarthrodial joints [1]. Its primary functions include protecting the underlying subchondral bone from mechanical damage [2] and providing a lubricated surface conducive to smooth articulation and minimized friction [1,3]. AC comprises a sparse population of specialized cells, the chondrocytes, surrounded by a dense extracellular matrix (ECM), devoid of blood/lymphatic vessels and nerves [4,5]. Predominantly composed of water, the ECM facilitates nutrient transport to chondrocytes and acts as a lubricant [1], harboring structural macromolecules, such as collagen type II, proteoglycans, non-collagenous proteins and glycoproteins [4]. Chondrocytes, derived from mesenchymal

stem/stromal cells (MSCs), play a crucial role in maintaining tissue homeostasis by synthesizing ECM components, growth factors and enzymes in response to various stimuli, albeit presenting low metabolic activity [1]. AC exhibits four distinct zones, each characterized by varying ECM composition and chondrocyte content. The superficial zone, in contact with the synovial fluid, contributes to the tensile properties of AC, presenting high chondrocyte density; conversely, the middle and deep zones primarily withstand compressive forces, containing elevated levels of proteoglycans, while the calcified zone secures the collagen fibrils to the subchondral bone [1].

In the event of an injury, the absence of blood vessels and the low metabolic rate of chondrocytes hinder the delivery of oxygen, nutrients and immune cells, and the production of new cartilage, thus compromising the tissue's self-healing ability [3,6,7]. Consequently, if left untreated, injuries to AC, whether acute or chronic traumatic events, are often unresolved and can progress to osteoarthritis (OA) [8]. OA, a chronic degenerative joint disease, primarily affects the elderly population and is characterized by AC degradation, synovial inflammation and subchondral bone thickening [3,6]. It mainly manifests in the knees, hip, spine and hands [3,9], featuring symptoms like activity-exacerbated pain, deformity and reduced range of motion [3]. Although the pathogenesis of OA remains elusive, evidence suggests an imbalance in tissue remodeling [4], possibly triggered by chondrocyte apoptosis induced by oxidative stress and mechanical signals [10]. In 2019, approximately 528 million individuals worldwide suffered from OA, of which 10 and 18% were men and women with over 60 years of age, respectively [11,12]. With an ageing population and the rising prevalence of risk factors such as obesity, this number is expected to continue to increase in the future [13]. Current treatments for OA, including non-surgical interventions such as physical therapy and medication, as well as surgical procedures (e.g., microfracture, mosaicplasty, autologous chondrocyte implantation (ACI)) offer limited efficacy, which has prompted the development of alternative approaches [7]. Regenerative medicine, for instance, which comprises cell therapy and tissue engineering (TE), is currently being explored for AC repair and regeneration [3].

Cartilage TE aims to promote effective regeneration of damaged cartilage through the development and in vivo implantation of functional biomimetic scaffolds combined with cells, growth factors and other biochemical cues [14]. These constructs are meticulously designed to replicate the structural/compositional properties of native AC and provide an optimal environment for chondrocyte growth and ECM production [6]. Cartilage TE requires careful consideration regarding the scaffold material (natural or synthetic), scaffold type (e.g., 3D printed structures, sponges, nanofibrous matrices, hydrogels), cell types (e.g., chondrocytes, MSCs) and growth factors/small molecules (e.g., transforming growth factor- $\beta$  (TGF $\beta$ s), kartogenin) to include [14–17]. Besides their capacity to differentiate into chondrocytes, MSCs are a promising source for cartilage TE strategies due to their high availability for isolation from several human tissues (e.g., adipose tissue, bone marrow, synovial membrane, umbilical cord), high in vitro proliferation capacity, low immunogenicity and favorable immunomodulatory/trophic properties [18–20]. The scaffold material must exhibit biocompatibility, biodegradability (essential for in vivo implantation) and mechanical properties similar to the native AC tissue, supporting chondrogenesis [5].

Hydrogels are crosslinked 3D macromolecular networks that possess high-water content, making them promising scaffold types for cartilage TE [14]. Hydrogels can be produced from natural biomaterials, such as collagen and hyaluronic acid – naturally present in AC –, or from synthetic materials, such as polyglycolic acid (PGA), polylactic acid (PLA), and polyethylene glycol (PEG) – which can be tailored to attain specific mechanical properties [5]. Among synthetic hydrogels, polyethylene glycol diacrylate (PEGDA), synthesized via PEG acrylation and photopolymerizable with UV light, is particularly attractive for cartilage regeneration: PEGDA hydrogels exhibit high hydrophilicity, resembling the aqueous AC environment, and can achieve a compressive modulus comparable to native cartilage ( $790 \pm 360$  kPa) [21,22]. Furthermore, PEGDA scaffolds have been shown to sustain TGF- $\beta$ -mediated chondrogenesis of undifferentiated cells, such as MSCs [23]. In addition to mechanical properties, hydrogels for cartilage TE should possess adequate porosity to facilitate nutrient diffusion, thereby supporting chondrocyte survival, proliferation and migration within the 3D structure [14]. Several techniques have been used to control hydrogel porosity,

including solvent casting, freeze-drying, gas foaming, and micropatterning [24]. Gas foaming, in particular, stands out as a cost-effective method for introducing porosity in hydrogels, capable of yielding porosities up to 90% [21,26]. It involves the generation of gaseous porogens within a polymer during polymerization, which become entrapped inside the crosslinked polymer, resulting in a porous structure conducive to cell infiltration [26]. Foaming agents are incorporated into the prepolymer solution, releasing gases either through chemical reactions or by the addition of inert gases at low/high pressures [27]. For instance, sodium bicarbonate, the most used foaming agent, releases CO<sub>2</sub> in mildly acidic conditions [21].


In this study, we developed 3D porous PEGDA hydrogels using a combination of gas foaming and ultraviolet (UV) light-based polymerization, for cartilage TE or disease modeling applications. The fabricated porous hydrogels were characterized in terms of their water content, swelling behavior, structural and morphological features, and mechanical properties under compressive loading. The *in vitro* biocompatibility of the porous hydrogels was evaluated using relevant human cell populations (chondrocytes and osteoblasts) of the articular joint microenvironment. Finally, bone marrow-derived MSC spheroids were produced, seeded onto the porous hydrogels and cultured in chondrogenic medium for 21 days. The final MSC-derived aggregates were assessed concerning their viability, the presence of cartilage ECM components (histological stainings), and expression of typical chondrogenic marker genes (qRT-PCR analysis).

## 2. Results and Discussion

### 2.1. Production and Structural Characterization of 3D Porous PEGDA Hydrogels

3D porous PEGDA hydrogels were fabricated by combining gas foaming and UV-induced crosslinking. Gas foaming commonly requires mixing foaming agents with a prepolymer solution, leading to the release of gas bubbles that become trapped within the hydrogel matrix during polymerization, resulting in porous structures. While polymerization is often induced by non-photocurable initiators or temperature changes [28–30], in this study, UV-induced crosslinking was the chosen method, with sodium bicarbonate and acetic acid serving as the foaming agents. This approach, previously used to produce porous PEG-based hydrogels [31–33], offered a superior control over hydrogel crosslinking and allowed a notable reduction in polymerization from 30 minutes [29] to 45 seconds.

Different formulations of 20% PEGDA hydrogels were prepared by adjusting the gas foaming and crosslinking parameters to optimize scaffold porosity and pore size. The resulting scaffolds displayed a porous foam structure with a thickness of approximately 6-8 mm, notably higher than the non-porous PEGDA hydrogels produced solely via UV crosslinking, as illustrated in Figure 1.






**Figure 1.** – Macroscopic (A) top-view and (B) lateral view of a porous PEGDA scaffold produced via gas foaming and UV-based crosslinking and a traditional non-porous PEGDA scaffold.

Initially, we evaluated the effect of the foaming agents' concentration on scaffold morphology using two formulations based on a prior study by Poursamar et al. [34]: 6% sodium bicarbonate with 6.75% acetic acid and 10% sodium bicarbonate with 11.25% acetic acid. SEM analysis revealed that increasing the concentration of the foaming agents resulted in thicker and more heterogeneous scaffolds, exhibiting regions lacking pores alongside areas with larger pores, as depicted in Figure 2A. Conversely, the lowest concentrations of sodium bicarbonate and acetic acid yielded scaffolds with smaller and more evenly distributed pores. Hence, the amount of porogen particles and the degree of gas foaming influenced scaffold porosity, as previously evidenced by Lim et al. [35]. Similar




outcomes were reported by Nam et al. [36] in PLLA scaffolds fabricated using the gas foaming technique with ammonium bicarbonate. Given the higher homogeneity in pore size, the lowest porogen concentration was selected for further tests.



**Figure 2.** – (A, B) Scanning Electron Microscopy analysis of porous PEGDA scaffolds with different (A) gas foaming parameters and (B) initiator concentration. Scale bar: 100  $\mu\text{m}$  (C) Size distribution of the pore diameter of scaffolds with different initiator concentration (n=50).

Next, we examined how the photoinitiator concentration affected the scaffold pore characteristics, using concentrations of 0.1%, 0.45% and 0.95% (v/v) respectively. As observed in Figure 2B, all scaffold formulations exhibited spherical-shaped pores evenly dispersed throughout the scaffold thickness. Typically, foam stabilizers such as surfactants are used in gas foaming to prevent liquid drainage and bubble coalescence, promoting the formation of more homogenous foams [37]. However, since foam stabilizers were not used in this study, the observed homogeneity was likely achieved through the strategic placement of sodium bicarbonate at the bottom of the well, rather than its dispersion within the prepolymer solution. Additionally, higher photoinitiator concentrations resulted in a reduction in the average pore size and pore size distribution, as illustrated in Figure 2C: pore sizes of  $800 \pm 260 \mu\text{m}$ ,  $319 \pm 121 \mu\text{m}$ , and  $233 \pm 60 \mu\text{m}$  were observed for photoinitiator concentrations of 0.1%, 0.45% and 0.95%, respectively. These results were expected, as increased photoinitiator concentration implies a faster crosslinking, resulting in more stable foams that limit bubble coalescence and the formation of larger pores [27].


Micro-computed tomography (Micro-CT) analysis corroborated these findings (Figure 3), demonstrating increased scaffold porosity and interconnectivity with higher photoinitiator concentrations. The porosity ranged from 41.5% to 64.5%, consistent with the porosity of porous 20% PEGDA hydrogels reported by Sannino et al. [31] (64.29-68.43%). However, the authors reported smaller pore sizes of 55.6-92.1  $\mu\text{m}$ , likely due to the lower concentration of sodium bicarbonate used (40 mg/ml). For the 0.95% photoinitiator formulation, interconnectivity reached 100%, implying that all pores were accessible for cell seeding, migration and nutrient/oxygen flow [38].



**Figure 3.** – (A) Micro-CT analysis of PEGDA scaffolds with different initiator concentration (0.1%, 0.45% and 0.95% v/v). (B) Porosity and interconnectivity of the three scaffold formulations.

The water content and swelling degree of the three formulations of porous scaffolds were evaluated alongside non-porous scaffolds with 0.95% photoinitiator concentration. All porous scaffolds exhibited a water content exceeding 89% (Figure 4A), whereas the non-porous scaffold displayed a water content of 81%, in line with the results of Nguyen et al. [39] and consistent with the water content reported for cartilage tissue (approximately 80%) [1]. Additionally, water content increased with photoinitiator concentration, albeit not significantly.

The porous hydrogels displayed similar swelling behaviors, reaching swelling degrees of  $23.7 \pm 3.7\%$ ,  $61.4 \pm 6.0\%$  and  $58.4 \pm 6.3\%$  after 24h, for photoinitiator concentrations of 0.1%, 0.45% and 0.95%, respectively (Figure 4B). The swelling degree increased rapidly during the initial 1-3 h and stabilized thereafter, due to the established equilibrium between the ions present in the hydrogel and the surrounding medium [40]. Particularly, the hydrogels with 0.1% photoinitiator concentration had a lower swelling degree compared to those with higher concentrations, possibly due to their reduced thickness and consequently reduced available surface for water uptake. In contrast, the non-porous hydrogels exhibited a distinct swelling behavior, with a swelling degree of approximately -10% throughout the 24h-period, indicating that their polymer network was likely highly compacted and restricted water uptake.



**Figure 4.** (A) Water content and (B) swelling behavior of non-porous and porous hydrogels with different photoinitiators concentrations (0.1%, 0.45% and 0.95% v/v) (n=3).


In TE, scaffold pore size plays a pivotal role in facilitating cell penetration, migration, nutrient diffusion and removal of metabolic waste [41]. Several studies have reported differing optimum ranges for cell penetration and chondrogenic differentiation for cartilage TE, depending on factors such as cell type, biomaterial and the chosen architecture. For chondrocytes, scaffold pore sizes of 150-300  $\mu\text{m}$  have been shown to promote cell proliferation and the synthesis of cartilage ECM components, including collagen type II and GAGs [42–44]. Conversely, Yamane et al. [45] observed enhanced chondrocyte proliferation and ECM synthesis in scaffolds with pore size of 400  $\mu\text{m}$ , possibly due to differences in scaffold hydrophilicity and biomaterials used. Regarding adipose stem/stromal cells (ASCs), various pore size ranges have been suggested for chondrogenic differentiation, including 100-150  $\mu\text{m}$  [46], 200-300  $\mu\text{m}$  [47] and 350-450  $\mu\text{m}$  [48]. Im et al. [49] reported that scaffolds with pore size of 400  $\mu\text{m}$  promoted enhanced proteoglycan production and expression of cartilage gene markers, while scaffolds with pore size of 200  $\mu\text{m}$  enhanced cell proliferation. Similar findings were reported by Oh et al. [50], who compared pore sizes of 370-400  $\mu\text{m}$  to 90-105  $\mu\text{m}$ . For MSCs, a pore size of 170-500  $\mu\text{m}$  has been identified to support chondrogenesis [51,52]. Within this range, Matsiko et al. [53] found that scaffolds with a pore size of 300  $\mu\text{m}$  enhanced cell proliferation, chondrogenic gene expression and cartilage-like matrix deposition. Considering the broad range of pore sizes deemed suitable for MSC proliferation and chondrogenic differentiation, we chose to seed MSCs in the scaffold with 0.95% photoinitiator concentration. This formulation exhibited a pore size range of 170-290  $\mu\text{m}$  and higher interconnectivity in comparison with the other formulations tested.

The mechanical properties, including compressive modulus, strength and elastic recovery, were assessed for both non-porous and porous hydrogels with 0.95% photoinitiator concentration. While all scaffolds exhibited elastomeric behavior (Supplementary Figure S1), porous scaffolds did not break under the applied strain, rendering the evaluation of their compressive strength impossible. Conversely, non-porous hydrogels presented a compressive strength of  $77 \pm 5$  kPa and a compressive modulus of  $180 \pm 8$  kPa, as shown in Figure 5. These values align with the compressive modulus of PEGDA hydrogels reported by Xiao et al. [54] ( $183 \pm 14$  kPa) and Moura et al. [55] ( $210 \pm 20$  kPa). However, other studies have reported different compressive modulus for 20% PEGDA hydrogels, including 69-83 kPa [56], 250 kPa [39] and 424-560 kPa [57–59], likely due to the different crosslinking mechanisms and the molecular weight of the PEGDA precursor used. The compressive modulus of the porous hydrogels was notably lower compared to their non-porous counterparts, measuring at  $40 \pm 10$  kPa,  $48 \pm 1$  kPa and  $53 \pm 9$  kPa with photoinitiator concentrations of 0.1%, 0.45% and 0.95%, respectively. This was expected since porous hydrogels have a greater void volume compared with non-porous hydrogels, resulting in a reduced effective cross-sectional area, which is key for preserving the original structure under external stress [60–62].

Additionally, the porous hydrogels exhibited high elastic recovery of 84.3-99.2%, which indicates their ability to almost readily return to their original shape, making them suitable for use under compressive loading stimuli, as constantly occurs in the articular cartilage within the knee



joint. After swelling, both porous and non-porous hydrogels exhibited lower compressive moduli and compressive strength (where applicable). In porous hydrogels, this reduction is directly linked to the water uptake they experienced: as the hydrogel swells, its network density decreases, resulting in a softer material [63]. As for the non-porous hydrogels, their decreased compressive modulus after swelling is more likely attributed to their decreased volume fraction, as evidenced by their negative swelling degree, which directly correlates with the elastic modulus [64].




**Figure 5.** – (A) Compressive Modulus (kPa) and (B) compressive strength (kPa) and elastic recovery (%) of three 0.95% v/v PEGDA scaffold formulations: non-porous and porous scaffolds (after fabrication and after 1h of swelling) (n=3). #Hydrogels broke. & Hydrogels did not break. \*\*\* $p < 0.001$ ; \*\*\*\* $p < 0.0001$ .

Unlike the non-porous hydrogels, the porous scaffolds exhibited a compressive modulus lower than the reported equilibrium compressive modulus for cartilage (0.08-2.1 MPa) [65]. Yet, they may offer a more favorable environment for MSC chondrogenic differentiation compared to the non-porous scaffolds. According to Park et al. [66], MSCs seeded on softer matrices (< 1 kPa) exhibit increased collagen type II production, in contrast to MSCs seeded on stiffer substrates. This observation has been corroborated by Steward et al. [67] using 3D agarose scaffolds with stiffness ranging from 0.5 kPa to 25 kPa. The authors propose that, although this stiffness range does not fully replicate that of mature human cartilage, it may simulate the cartilage environment during its developmental stage, potentially aiding in MSC differentiation into a cartilage phenotype [66].

## 2.2. In Vitro Biocompatibility of 3D Porous PEGDA Hydrogels with Relevant Cell Populations

The cytotoxicity of the 3D porous PEGDA hydrogels was assessed through indirect and direct compatibility tests using human MG-63 osteoblastic-like cells and human chondrocytes. The results, depicted in Figure 6, indicate that cells exhibited high viability on both porous and non-porous scaffolds, comparable to the negative control. Unlike chondrocytes, MG-63 cells displayed slightly higher viability in the non-porous scaffolds, although the difference was not statistically significant.

Direct contact tests further supported these findings, showing that both porous and non-porous scaffolds exhibited similar performance to the negative control. MG-63 cells and human chondrocytes remained in confluent monolayers and displayed their characteristic morphology [68,69]. Additionally, no inhibition halo was observed in proximity to the scaffolds, indicating excellent biocompatibility, consistent with previous studies on porous PEGDA scaffolds [70,71].




**Figure 6.** – (A) MTT assay results and (B) direct contact test images of porous and non-porous PEGDA scaffolds with human MG-63 osteoblasts and chondrocytes. (n=3), \*\*\*\* $p$ <0.0001.

### 2.3. Chondrogenic Differentiation of MSC-Spheroids on 3D Porous PEGDA Hydrogels

Spheroids of MSCs, each comprising 400 cells, were generated in Aggrewell plates. After 24 h, the spheroids were seeded onto the 3D porous PEGDA hydrogels and cultured in chondrogenic medium for 21 days (Figure 7A). MSCs were employed for their potential to differentiate into chondrocytes and their capacity for extensive in vitro expansion, while the use of spheroids was preferred over single cells to promote cell-cell contact and mimic the cartilaginous condensations characteristic of embryonic development [72].

Prior to seeding, the spheroids exhibited a spherical and compact morphology, with an average diameter of  $157 \pm 8 \mu\text{m}$ , as illustrated in Figure 7B. Their dimensions closely matched the pore size range of the scaffold, indicating potential for effective colonization of the construct. Additionally, it has been reported that aggregates of similar size exhibit superior chondrogenic differentiation compared to 1-2 mm pellets [73].




**Figure 7.** – (A) Production and seeding of spheroids on porous PEGDA hydrogel scaffolds, fabricated with the gas-foaming technique. (B) Pore size of porous PEGDA hydrogels (SEM images, left) and spheroid diameters (brightfield image, right) (n=50). Scale bar:  $100 \mu\text{m}$ .

After 21 days of culture, Safranin-O stainings showed that the MSC-derived spheroids were localized within the pores of the scaffold (Supplementary Figure S2). The aggregates retained their initial spherical morphology and most cells within the aggregate remained viable, as shown in Figure 8A. Although a small number of dead cells were observed, no necrotic center was evident, largely due to the small diameter of the aggregates, which allowed sufficient oxygen distribution. Alcian Blue and Safranin-O stainings performed on the final spheroids further revealed the presence of proteoglycans and GAGs, respectively, both typical components of the articular cartilage ECM.

To assess the expression of chondrogenic markers, quantitative polymerase chain reaction (qRT-PCR) was performed on MSC aggregates at day 1 (before differentiation) and on spheroid-seeded PEGDA porous scaffolds at day 21 (after differentiation). Specifically, the expression levels of *COL1A1* (collagen type I, a marker for undifferentiated mesenchymal tissue), *COL2A1* (collagen type II, indicative of cartilaginous tissue), *SOX9* (a transcription factor for chondrogenic genes) and *ACAN* (aggrecan, main cartilage proteoglycan) were evaluated and normalized to 2D MSC cultures at day 0 (before spheroid formation and scaffold seeding). As illustrated in Figure 8B, MSC aggregates exhibited decreased expression of *COL1A1* (0.27-fold) and increased expression of *COL2A1* (7.1-fold), *SOX9* (12.1-fold) and *ACAN* (2.5-fold), compared to 2D MSC cultures, which is consistent with the literature [72,74]. This suggests that, while MSC aggregates undergo some level of pre-conditioning, their 3D configuration alone is insufficient to initiate chondrogenesis. Chondrogenic stimuli, such as medium supplemented with TGF- $\beta$ s, are still required to support proper MSC chondrogenesis [72].

In spheroid-seeded PEGDA scaffolds, following 21 days of differentiation, a similar trend of *COL1A1* downregulation and *COL2A1*, *SOX9* and *ACAN* upregulation was observed, when compared to 2D culture, confirming successful chondrogenic differentiation. Notably, there was a significant increase in the expression of *COL2A1* (35.9-fold) and *SOX9* (41.2-fold), while *ACAN* levels

exhibited a more moderate increase (5.7-fold). In comparison with MSC aggregates at day 1, the aggregates cultured in PEGDA porous hydrogels showed similar expression of *COL1A1* but increased expression of *COL2A1* (5.1-fold), *SOX9* (3.4-fold) and *ACAN* (2.3-fold). These findings not only highlight the capacity of the 3D porous PEGDA scaffold to support chondrogenesis but also demonstrate that combining MSC aggregates with a porous PEGDA scaffold of suitable pore size might be a more effective approach for inducing chondrogenic differentiation, when compared to scaffold-free MSC aggregates and conventional 2D monolayer cultures. Hence, the spheroid-seeded 3D porous PEGDA scaffold holds significant promise for cartilage TE or in vitro OA modelling strategies.



**Figure 8.** – (A) Live/Dead (green: live cells, red: dead cells), Alcian Blue and Safranin-O stainings of MSC spheroids at day 21 post-seeding. (B) qRT-PCR analysis of *COL1A1*, *COL2A1*, *SOX9* and *ACAN* in 2D cultures (control), 3D spheroids (day 1) and in 3D spheroids cultured on PEGDA porous hydrogels (day 21 post-seeding). Gene expression levels were normalized to that of glyceraldehyde 3-phosphate dehydrogenase (*GAPDH*, endogenous control) and calculated as fold-change relative to the control sample (2D MSC cultures at day 0, before spheroid formation and scaffold seeding). (n=3), \* $p < 0.05$ , \*\* $p < 0.01$ .



### 3. Conclusions

In summary, 3D porous PEGDA hydrogels were developed using the gas foaming technique coupled with UV-induced crosslinking and presented different porosities according to the foaming agents and photoinitiator concentrations used. The optimal porosity for cartilage TE and MSC chondrogenic differentiation was obtained using 6% sodium bicarbonate, 6.75% acetic acid and 0.95% photoinitiator, yielding pore sizes of 170-290  $\mu\text{m}$ . While the scaffold presented a compressive modulus of  $53 \pm 9$  kPa, lower than the stiffness range of mature cartilage (0.08-2.1 MPa) [65], it may mimic more closely the stiffness of cartilage during its developmental stage. Consequently, the porous hydrogel scaffold could potentially facilitate MSC chondrogenic differentiation more effectively than non-porous PEGDA hydrogels of higher compressive modulus. After being cultured in chondrogenic medium, MSC-derived aggregates of  $157 \pm 8$   $\mu\text{m}$  in diameter were found within the scaffold's pores, exhibiting increased expression of *COL2A1*, *SOX9* and *ACAN*, and decreased expression of *COL1A1* in comparison to 2D MSC cultures before differentiation and scaffold-free MSC aggregates, which exhibited a similar trend, but showed less pronounced upregulation of *COL2A1*, *SOX9* and *ACAN* genes. This suggests that, while MSC aggregates experienced a certain degree of pre-conditioning due to their 3D configuration, chondrogenesis was significantly enhanced in the 3D porous PEGDA hydrogel scaffold after differentiation, highlighting its suitability for cartilage TE strategies or in vitro disease modelling.

### 4. Materials and Methods

#### 4.1. Materials

Poly(ethylene glycol) diacrylate (PEGDA, 575 Da), HEPES, phosphate buffer saline (PBS), sodium bicarbonate, acetic acid, glycine, isopropanol, hydrochloric acid (HCl), paraformaldehyde (PFA), the photoinitiator dimethoxy-2-phenylacetophenone (DMPA), N-vinyl-pyrrolidone (NVP), 1X MEM non-essential aminoacids, L-ascorbic acid, ascorbic acid 2-phosphate, L-Proline, dexamethasone, Alcian Blue 8GX powder, Safranin-O dye and the 3-(4,5-Dimethylthiazol-2-yl)-2,5-Diphenyltetrazolium Bromide (MTT) assay kit were acquired from Sigma-Aldrich (St. Louis, MI, USA). Dulbecco's Modified Eagle Medium (DMEM), high-glucose DMEM, fetal bovine serum (FBS), antibiotic-antimycotic mixture (Anti-Anti), sodium pyruvate, Collagenase Type IV powder, High-capacity cDNA reverse transcription kits, MicroAmp™ Fast Optical 96-well reaction PCR plates, SYBR™ Green Master Mix and LIVE/DEAD™ viability/cytotoxicity kit were supplied by Thermo Fisher Scientific (Waltham, MA, USA). The RNeasy Mini Kit for RNA extraction was obtained from Qiagen (Hilden, Germany). ITS™+ Premix supplement (6.25  $\mu\text{g}/\text{mL}$  bovine insulin; 6.25  $\mu\text{g}/\text{mL}$  transferin; 6.25  $\mu\text{g}/\text{mL}$  selenous acid; 5.33  $\mu\text{g}/\text{mL}$  linoleic acid; 1.25  $\mu\text{g}/\text{mL}$  bovine serum albumin) and ultra-low attachment 24 culture well plates were purchased from Corning Inc (New York, USA). Transforming growth factor- $\beta 3$  (TGF- $\beta 3$ ) was obtained from R&D Systems (Minneapolis, MN, USA). AgreeWell™400 microwell plates were acquired from STEMCELL Technologies (Vancouver, Canada).

#### 4.2. Fabrication of 3D Porous PEGDA Hydrogels

For the production of 3D porous PEGDA hydrogels, the gas foaming technique was combined with UV light-based crosslinking. PEGDA (MW 575 Da) was dissolved in a 10 mM HEPES (238 g/mol) solution in 0.01M PBS to achieve a final concentration of 20% v/v. To prepare the photoinitiator solution, 300 mg of DMPA were added to each mL of N-vinyl-pyrrolidone (NVP) and the solution was subjected to vigorous agitation in a thermomixer to allow complete dissolution of the powder before use and was kept in the dark. After the addition of the photoinitiator, the final solution was filtered through a 0.22  $\mu\text{m}$  filter (Merck Millipore, Burlington, MA, USA). To optimize the porosity/pore size and physical features of the porous hydrogels, different formulations were tested as described in Table 1. To fabricate the scaffolds, the sodium bicarbonate powder was evenly spread on the bottom of a well of a 6-well culture plate. Afterwards, 1.8 mL of PEGDA (with photoinitiator) solution and the proportional amount of acetic acid were poured into the well and the plate was

exposed to UV light for 45 seconds. The reaction occurring between acetic acid and sodium bicarbonate leads to the formation of carbon dioxide bubbles, which are responsible for the generation of pores within the hydrogel structure. Non-porous hydrogels were produced using the described protocol (without sodium bicarbonate). The final hydrogel scaffolds were obtained using a round punch (with a diameter of 14 mm) in order to perfectly fit the size of a well of a 24-well culture plate.

**Table 1.** Summary of the formulations tested to produce porous PEGDA hydrogels.

PEGDA concentration	20% v/v PEGDA in 10 mM HEPES solution
Photoinitiator concentration	0.1% v/v 0.45% v/v 0.95% v/v
UV curing time	45 seconds
Gas foaming parameters	6% w/v Sodium bicarbonate + 6.75% v/v Acetic acid 10% w/v Sodium bicarbonate + 11.25% v/v Acetic acid

4.3. Characterization of 3D Porous PEGDA Hydrogels

4.3.1. Scanning Electron Microscopy (SEM) and Pore Size Measurements

The morphology and pore size of the produced hydrogels were observed by Scanning Electron Microscopy (SEM) analysis. Before the imaging, the samples were coated with an Au/Pd layer of 30 nm using a Polaron model E5100 coater (Quorum Technologies, Lewes, UK). Images were obtained using a Field Emission Gun Scanning Electron Microscope (FEG-SEM) equipment (JEOL, JSM-7001F model, Tokyo, Japan) with the accelerated voltage set at 15 kV. Pore size measurements were performed using the ImageJ software version 1.53j (NIH, Bethesda, MD, USA). The average pore sizes were calculated from 50 (n=50) well-defined individual pores from at least three different SEM images.

4.3.2. Micro-Computed Tomography (μ-CT) Analysis

The internal microstructure of the different porous PEGDA hydrogels was obtained through μ-CT analysis using a SkyScan 1174v2 version 1.1 (Bruker, Billerica, MA, USA) scanner equipment. The acquisition was made using the following parameters: image pixel size of 16.65 μm; source voltage of 50 kV; source current of 800 μA; exposure time of 700 ms; rotation step of 0.7° (no filter). 3D reconstruction was done using the Software NRecon version 1.7.4.6 (Bruker) and CTVox version 3.3.1 (Bruker) program was used to provide a 3D visualization of the scanned samples. μ-CT analysis allows the evaluation of scaffold microstructural features such as porosity and interconnectivity, which are calculated as:

$$Porosity\ (\%) = \frac{V_{pores}}{V_{pores} + V_{scaffold}} \times 100$$

(1)

$$Interconnectivity\ (\%) = \frac{V_{open\ pores}}{V_{open\ pores} + V_{closed\ pores}} \times 100$$

(2)

#### 4.3.3. Swelling Behaviour and Water Content

A swelling test was performed on 20% (v/v) 3D porous (three formulations with different concentrations of photoinitiator – 0.1%, 0.45%, 0.95%) and non-porous hydrogels. Immediately after the crosslinking process, the hydrogels were extracted from the mold, weighted ( $W_0$ ) and left to soak in PBS. At each time point, the samples were removed and weighted ( $W_s$ , especially care was taken to remove the excess PBS from the surface of the hydrogels, so that only the weight of incorporated PBS was taken into account). The swelling equilibrium weight ( $W_s$ ) and the dry weight ( $W_0$ ) were then used to calculate the % of swelling ratio:

$$\text{Swelling ratio (\%)} = \frac{(W_s - W_0)}{W_0} \times 100 \quad (3)$$

$$\text{Water content (\%)} = \frac{(W_0 - W_d)}{W_0} \times 100 \quad (4)$$

To measure the water content, the hydrogels were dried for 24h at 37°C after fabrication and weighted ( $W_d$ ). The water content was calculated considering the initial ( $W_0$ ) and dried ( $W_d$ ) weights of the hydrogels:

Three independent hydrogels (n=3) were considered for both swelling ratio and water content analyses.

#### 4.3.4. Mechanical Properties under Compressive Testing

The compressive tests of the hydrogel samples (diameter of 14 mm and height of 4 mm, n=3 samples per condition) were performed on an Univert mechanical tester (Model UV-200-01; CellScale Biomaterials Testing, Waterloo, Canada) equipped with a 10 N load cell and using a compression rate of 1 mm/min. The obtained force-displacement curves were then transformed into stress-strain plots given the sample dimensions and considering Equations (5) and (6).

$$\text{Stress} = \sigma = \frac{F}{A} \quad (5)$$

where F (Newton, N) is the applied force and A (mm<sup>2</sup>) is the cross-section area.

$$\text{Strain} = \varepsilon = \frac{\Delta L}{L_0} \quad (6)$$

where  $\Delta L$  (mm) is the displacement and  $L_0$  (mm) is the initial height.

The compressive Young's modulus (Equation (7)) can be calculated from the initial linear strain region (0-15%) of the stress-strain curve.

$$\text{Young's Modulus} = \frac{\sigma}{\varepsilon} \quad (7)$$

where  $\sigma$  (N.mm<sup>-2</sup> = MPa) is the stress and  $\varepsilon$  (non-dimensional) is the strain.

#### 4.4. In Vitro Cytotoxicity Tests

The cytocompatibility of the hydrogels (diameter:14 mm and height: 3mm) was assessed using human chondrocytes and human MG-63 osteoblast-like cells in conformity with the ISO 10993-5 guidelines [75]. Human chondrocytes were acquired from CELL Applications, Inc. (San Diego, CA, USA) and cultured using a medium composed of high-glucose DMEM supplemented with 10% FBS (v/v), 1X MEM non-essential aminoacids, 0.4 mM L-Proline, 0.2 mM L-Ascorbic acid and 1% (v/v) Anti-anti. Human MG-63 osteoblast-like cells were obtained from ATCC (CRL-1427™, Manassas, VA, USA) and cultured in DMEM supplemented with 10% FBS and 1% Anti-anti. Both cell types were cultured in an incubator at 37 °C and 5% CO<sub>2</sub> in a humidified atmosphere and passaged to new flasks when confluence (≈80–90%) was reached. The culture medium was completely renewed every 2–3 days. Porous and non-porous 20% (v/v) PEGDA hydrogels were sterilized by several washes and incubation overnight in a 1% Anti-anti solution (in PBS). The samples were evaluated by means of indirect (extract) and direct contact cytotoxicity tests. For both cell types, the cells were seeded on tissue-culture treated polystyrene plates at a density of 1x10<sup>5</sup> (24-well plate) and 2x10<sup>5</sup> (12-well plate) per well for the indirect and direct contact tests, respectively. The cells were then cultured for 24 h at 37 °C and 5% CO<sub>2</sub> to achieve confluent monolayers. Cells cultured in the respective culture medium were the negative controls, while latex material was used as positive control of a cytotoxic response. To prepare the extraction media for the indirect tests, the hydrogels were incubated in culture

medium (ratio of 0.2 g/mL) for 24 h at 37 °C and 5% CO<sub>2</sub>. Afterwards, the cells were cultured in the respective extraction medium for 72 h at 37 °C and 5% CO<sub>2</sub> in a humidified incubator. When the incubation period was finished, the extraction media were removed and the MTT-based in vitro toxicology assay kit was used according to the manufacturer's instructions. Briefly, the cell cultures were incubated in a 1 mg/mL MTT solution (prepared in PBS, yellow color) for 4h at 37 °C. Then, the violet formazan product, resulting from the reduction of MTT by metabolically viable cells, was dissolved with the appropriate MTT solvent (0.1 N HCl in anhydrous isopropanol) under agitation for 5 min. Finally, the resultant solutions were transferred to a 96-well plate and the absorbance values were measured using a microplate reader (Infinite M200 PRO, TECAN, Switzerland) at 570 nm. The percentage of cell viability of the different samples was calculated by comparison with the values obtained for the negative control cultures, which were considered to have 100% viable cells. Four independent samples (n=4) of each condition were assayed, and the absorbance of each sample was read in triplicate.

Regarding the direct contact assays, each hydrogel condition (n=3, porous vs. non-porous) and respective controls were placed on top of a confluent monolayer of chondrocytes or osteoblasts and incubated for 72 h at 37 °C in a humidified atmosphere with 5% CO<sub>2</sub>. The viability and morphology of the cells in direct contact with the materials were qualitatively assessed using an inverted optical microscope (LEICA DMI3000B, Leica Microsystems, Germany) connected to a digital camera (Nikon DXM1200F, Nikon Instruments Inc.; Japan).

#### *4.5. MSC Spheroids Culture and Differentiation on 3D Porous PEGDA Hydrogels*

hBM-MSCs (36 years healthy male donor) were isolated from bone marrow aspirates according to protocols previously established at the Institute for Bioengineering and Biosciences (iBB) - Instituto Superior Técnico (IST) [20]. Bone marrow aspirates were obtained from Instituto Português de Oncologia Francisco Gentil, Lisboa-Potugal after written informed consent and with the approval of the Ethics Committee of the respective clinical institution. hBM-MSCs were thawed from a frozen stock (nitrogen liquid tanks) and cultured in DMEM supplemented with 10% FBS (MSC qualified) and 1% Anti-anti at 37 °C and 5% CO<sub>2</sub>. The culture medium was fully changed every 2–3 days and the cells were passaged when a confluence of around 80-90% was reached. All experiments were done using hBM-MSCs in passages between 4 and 6.

Prior to the preparation of the spheroids, 1 mL of AggreWell Rinsing solution (STEMCELL Technologies) was added to each well of the AggreWell™400 plate to minimize the adhesion of the cells to the microwells. Then, the plate was centrifuged to remove the rinsing solution, 500 µL of culture media were added to each well and the plate was centrifuged again to completely eliminate any air bubbles. To produce the spheroids in accordance with the manufacturer's protocol, hBM-MSCs were harvested, centrifuged and resuspended in an appropriate media volume to achieve spheroids of 400 cells and considering that each well of an AggreWell plate generates 1200 spheroids. Thus, 500 µL of the cell suspension were added to each well, followed by an incubation of 5 min at room temperature and a centrifugation (1500 rpm for 10 min) of the AggreWell plate. After 18 h of incubation at 37 °C and 5% CO<sub>2</sub>, the samples were imaged to assess the size of the spheroids produced. The area of the spheroids (n = 50) was measured using the area measurement algorithm from ImageJ software after adjusting the threshold until the border of the spheroid. For each well, the spheroids were carefully transferred to a falcon tube, left to deposit on the bottom, and the DMEM + 10% FBS (MSC) media was removed. The 1200 spheroids (one well) were resuspended in 200 µL of chondrogenic medium consisting of high glucose DMEM supplemented with 100 nM dexamethasone, 50 µg/mL ascorbic acid 2-phosphate, 40 µg/mL L-Proline, 1mM sodium pyruvate, ITS™+ Premix, 1% Anti-anti and 10 ng/mL TGF-β3. Upon gentle mixing, a 50 µL suspension (containing around 300 spheroids) was placed dropwise on different spots on the top of each hydrogel scaffold placed in ultra-low attachment plates. The constructs were then incubated at 37 °C and 5% CO<sub>2</sub> for 1 h before adding 1 mL of chondrogenic medium to each well. The cultures were maintained for 21 days under chondrogenic induction conditions at 37 °C and 5% CO<sub>2</sub>, and the media was carefully changed twice a week. According to previously obtained results for hydrogel porosity,



pore size and biocompatibility, the formulation selected for the spheroid differentiation studies was (PEGDA 20% v/v, photoinitiator DMPA 0.95% v/v, 6% w/v Sodium bicarbonate, 6.75% v/v Acetic acid).

#### 4.6. Assessment of Spheroid Viability and Chondrogenic Differentiation after Culture on 3D Porous PEGDA Hydrogels

##### 4.6.1. Live/Dead Staining

The viability of the spheroids cultured on the 3D porous hydrogels for 21 days under chondrogenic induction was assessed using the LIVE/DEAD assay kit. Briefly, the spheroids were collected from the porous hydrogels, placed in a new plate, and incubated with a solution of 4  $\mu$ M calcein-AM and 2  $\mu$ M ethidium bromide (prepared in PBS) for 1 h at room temperature and protected from light. Then, the spheroids were washed once with PBS and immediately imaged using a LEICA DMIB3000B inverted fluorescence microscope.

##### 4.6.2. Alcian Blue and Safranin-O Stainings

The spheroids harvested from the porous PEGDA hydrogels (and also one sample of spheroid-containing porous hydrogels) were fixed in 4% (v/v) PFA solution (in PBS) for 20 min at room temperature, washed twice with PBS and incubated overnight in 15% (v/v) sucrose solution at 4 °C. The samples were embedded in 7.5%/15% (v/v) gelatin/sucrose solution and frozen in isopentane at -80 °C. 12  $\mu$ m sections were cut on a cryostat-microtome (Leica CM3050S, Leica Microsystems), collected on Superfrost™ Microscopic Slides (Thermo Fisher Scientific) and stored at -20 °C.

To assess for the presence of sulfated glycosaminoglycans (GAGs), typical constituents of articular cartilage ECM, the histological sections were stained with Alcian Blue and Safranin-O. The sections were first de-gelatinized in PBS for 45 min at 37 °C and incubated in a 0.1 M Glycine solution for 10 min at room temperature. The spheroids were then stained with a 1% (w/v) Alcian Blue solution (prepared in 0.1 N HCl) for 1 h at room temperature. Alternatively, other samples were stained with a 0.1% (w/v) Safranin-O solution (in distilled water) and left incubating for 20 min at room temperature. For both stainings, the slides were washed several times in PBS and imaged in an inverted optical microscope LEICA DMI3000B equipped with a Nikon DXM1200F digital camera.

##### 4.6.3. Quantitative Real-Time Polymerase Chain Reaction (qRT-PCR) Analysis

To assess the chondrogenic differentiation of the spheroids, a qRT-PCR assay was performed considering three different conditions: 2D cultured cells at Day 0; Aggregates removed from the AggreWell plate at Day 1; and Aggregates cultured on the porous PEGDA hydrogels for 21 Days in chondrogenic medium.

Prior to the RNA extraction, the spheroids were treated with a 0.3% w/v Collagenase IV solution for 3 h at 37 °C to allow cell disaggregation and lysis. RNA was isolated using the RNeasy Mini Kit following the manufacturer's guidelines and quantified in a NanoVue Plus™ spectrophotometer (GE Healthcare, Chicago, IL, USA). Afterwards, cDNA was synthesized from the purified RNA using High-Capacity cDNA Reverse Transcription Kit (Applied Biosystems) according to the manufacturer's protocol. Briefly, previously prepared reaction mixtures were incubated in a T100™ thermal cycler (Bio-Rad, Hercules, CA, USA) for 10 min at 25 °C, 120 min at 37 °C and 5 min at 85 °C, and then were kept at 4 °C until further use. qRT-PCR analysis was performed using SYBR™ Green Master Mix and StepOnePlus real-time PCR system (Applied Biosystems). All reactions were carried out at 95 °C for 10 min, followed by 40 cycles of 95 °C for 15 s and 60 °C for 1 min. All samples were analyzed in triplicates (n=3). The CT values obtained were normalized against the expression of the housekeeping gene glyceraldehyde-3-phosphate (GADPH), and their analysis was performed using the  $2^{-\Delta\Delta CT}$  method. Gene expression results for the target genes COL1A1, COL2A1, Sox9 and ACAN were determined as a foldchange relative to the baseline expression of the target genes in the control sample (2D hBM-MSCs cultures before scaffold seeding). The primer sequences used in the qRT-PCR analysis are presented in Table 2.

**Table 2.** Primer sequences (forward and reverse) used in the qRT-PCR analysis.

Gene	Forward primer sequence	Reverse primer sequence
GADPH	5'-GGTCACCAGGGCTGCTTTTA-3'	5'-CCTGGAAGATGGTGATGGGA -3'
COL1A1	5'- CATCTCCCCTTCGTTTTTGA -3'	5'- CCAAATCCGATGTTTCTGCT-3'
COL2A1	5'- GGAATTCCTGGAGCCAAAGG-3'	5'- AGGACCAGTTCTTGAG-3'
SOX9	5'- TACGACTACACCGACCACCA-3'	5'- TTAGGATCATCTCGCCCATC-3'
ACAN	5'- CACTGGCGAGCACTGTAACAT-3'	5'- TCCACTGGTAGTCTTGGGCAT-3'

4.7. Statistical Analysis

Results are presented as average values ± standard deviation (SD). In this study, all the experimental procedures were performed using three independent samples (n=3), unless specified differently. Statistical analysis of the results was performed through one-way ANOVA, followed by Tukey post hoc test using the GraphPad Prism 5 software. Data were considered statistically significant when the p-values obtained were lower than 0.05 (95% confidence intervals, \* p < 0.05).

**Supplementary Materials:** The following supporting information can be downloaded at the website of this paper posted on Preprints.org. Figure S1: Representative Stress-Strain Curve for an unconfined compression test for 3 conditions of non-porous hydrogels with 0.95% v/v photoinitiator and porous hydrogels with 0.1%, 0.45% or 0.95% v/v photoinitiator concentration, after fabrication and after swelling for 24h; Figure S2: Safranin-O staining on a histological section of the 3D porous PEGDA scaffold seeded with MSC aggregates.

**Author Contributions:** Conceptualization: S.G.; M.D.; C.A.V.; F.C.F. and J.C.S.; Investigation and experimental work: S.G.; M.D.; F.M.; C.S.M.; C.A.V. and J.C.S.; Writing – original draft preparation: S.G.; M.D. and J.C.S.; Writing – review and editing: C.S.M.; C.A.V.; J.C.S. and F.C.F.; Supervision: C.A.V.; F.C.F. and J.C.S.; Funding acquisition: F.C.F. and J.C.S.; All authors have read and agreed to the published version of the manuscript.

**Funding:** The authors acknowledge funding from FCT—Portuguese Foundation for Science and Technology (FCT/MCTES) with dedicated funding from the InSilico4OCReg (PTDC/EME-SIS/0838/2021) project grant, and also FCT/MCTES funding to iBB (UIDB/04565/2020 and UIDP/04565/2020), CDRSP (UIDB/04044/2020 and UIDP/04044/2020) and Associate Laboratory i4HB (LA/P/0140/2020). Carla Moura thanks the national funding by FCT through the institutional scientific employment program-contract (CEECINST/00077/2021).

**Institutional Review Board Statement:** Not applicable.

**Informed Consent Statement:** Not applicable.

**Data Availability Statement:** All data from this study are available from the authors upon request.

**Acknowledgments:** The authors thank Isabel Nogueira (MicroLab IST) for her assistance in obtaining the SEM images of the hydrogels.

**Conflicts of Interest:** The authors declare no conflict of interest.

References

1. Fox, A. J. S.; Bedi, A.; Rodeo, S. A. The basic science of articular cartilage: structure, composition, and function. *Sports Health* **2009**, *1*, 461–468.
2. Kempson, G. E. The mechanical properties of articular cartilage. In *The Joints and Synovial Fluid*, 1st ed.; Sokoloff L.; Ed.; Academic Press: New York, NY, USA 1980; Volume 2, pp. 177–238.
3. Roseti, L.; Desando, G.; Cavallo, C.; Petretta, M.; Grigolo, B. Articular cartilage regeneration in osteoarthritis. *Cells* **2019**, *8*, 1305.
4. Buckwalter, J. A.; Mankin, H. J.; Grodzinsky, A. J. Articular cartilage and osteoarthritis. *Instr Course Lect* **2005**, *54*, 465–480.

5. Armiento, A. R.; Stoddart, M. J.; Alini, M.; Eglin, D. Biomaterials for articular cartilage tissue engineering: Learning from biology, *Acta Biomater* **2018**, *65*, 1–20.
6. Kwon, H.; Paschos, N. K.; Hu, J. C.; Athanasiou, K. Articular cartilage tissue engineering: the role of signaling molecules. *Cell Mol Life Sci* **2016**, *73*, 1173–1194.
7. Athanasiou, K. A.; Darling, E. M.; Hu, J. C. In vitro tissue engineering of hyaline articular cartilage. In *Articular Cartilage Tissue Engineering*, 1st ed.; Seidel, A., Ed; Springer: Cham, Switzerland, 2010; Volume 1, pp. 31–53.
8. Flik, K. R.; Lewis, P.; Kang, R. W.; Cole, B. J. Articular cartilage. In *Clinical Sports Medicine*, pp. 505–514, Elsevier, 2006.
9. GBD 2021 Osteoarthritis Collaborators. Global, regional, and national burden of osteoarthritis, 1990–2020 and projections to 2050: a systematic analysis for the global burden of disease study 2021. *Lancet Rheumatol* **2023**, *5*, e508–e522.
10. Gu, Y.-T.; Chen, J.; Meng, Z.-L.; Ge, W.-Y.; Bian, Y.-Y.; Cheng, S.-W.; Xing, C.-K.; Yao, J.-L.; Fu J.; Peng L. Research progress on osteoarthritis treatment mechanisms. *Biomed. Pharmacother* **2017**, *93*, 1246–1252.
11. World Health Organization. Osteoarthritis. Available online: <https://www.who.int/news-room/fact-sheets/detail/osteoarthritis> (accessed on 21 February 2024)
12. Allen, K. D.; Thoma, L. M.; Golightly, Y. M. Epidemiology of osteoarthritis. *Osteoarthritis Cartilage* **2022**, *30*, 184–195.
13. Plotnikoff, R.; Karunamuni, N.; Lytvyak, E.; Penfold, C.; Schopflocher, D.; Imayama, I.; Johnson, S. T.; Raine, K. Osteoarthritis prevalence and modifiable factors: a population study. *BMC Public Health* **2015**, *15*, 1195.
14. Borrelli, J.; Jr; Olson, S. A.; Godbout, C.; Schemitsch, E. H.; Stannard, J. P.; Giannoudis, P. V. Understanding articular cartilage injury and potential treatments. *J Orthop Trauma* **2019**, *33*, S6–S12.
15. Wei, W.; Dai, H. Articular cartilage and osteochondral tissue engineering techniques: Recent advances and challenges. *Bioactive Materials* **2021**, *6*, 4830–4855.
16. Zhang, Z.; Mu, Y.; Zhou, H.; Yao, H.; Wang, D.-A. Cartilage tissue engineering in practice: Preclinical trials, clinical applications, and prospects. *Tissue Engineering. Part B, Reviews* **2023**, *29*, 473–490.
17. Silva, J. C.; Udangawa, R. N.; Chen, J.; Mancinelli, C. D.; Garrudo, F. F. F.; Mikael, P. E.; Cabral, J. M. S.; Ferreira, F. C.; Linhardt, R. J. Kartogenin-loaded coaxial PGS/PCL aligned nanofibers for cartilage tissue engineering. *Materials Science & Engineering. C, Materials for Biological Applications* **2023**, *107*, 110291.
18. Huang, Y.-Z.; Xie, H.-Q.; Silini, A.; Parolini, O.; Zhang, Y.; Deng, L.; Huang, Y.-C. Mesenchymal stem/progenitor cells derived from articular cartilage, synovial membrane and synovial fluid for cartilage regeneration: Current status and future perspectives. *Stem Cell Reviews* **2017**, *13*, 575–586.
19. Tan, A. R.; Hung, C. T. Concise review: Mesenchymal stem cells for functional cartilage tissue engineering: Taking cues from chondrocyte-based constructs. *Stem Cells Translational Medicine* **2017**, *6*, 1295–1303.
20. Silva, J. C.; Han, X.; Silva, T. P.; Xia, K.; Mikael, P. E.; Cabral, J. M. S.; Ferreira, F. C.; Linhardt, R. J. Glycosaminoglycan remodeling during chondrogenic differentiation of human bone marrow-/synovial-derived mesenchymal stem/stromal cells under normoxia and hypoxia. *Glycoconjugate Journal* **2020**, *37*, 345–360.
21. Annabi, N.; Nichol, J. W.; Zhong, X.; Ji, C.; Koshy, S.; Khademhosseini, A.; Dehghani, F. Controlling the porosity and microarchitecture of hydrogels for tissue engineering. *Tissue Eng Part B Rev* **2010**, *16*, 371–383.
22. Gäbler, S.; Stampfl, J.; Koch, T.; Seidler, S.; Schüller, G.; Redl, H.; Juras, V.; Trattng, S.; Weidisch, R. Determination of the viscoelastic properties of hydrogels based on polyethylene glycol diacrylate (PEG-DA) and human articular cartilage. *Int J Mater Eng Innov* **2009**, *1*, 3–20.
23. Williams, C. G.; Kim, T. K.; Taboas, A.; Malik, A.; Manson, P.; Elisseff, J. In vitro chondrogenesis of bone marrow-derived mesenchymal stem cells in a photopolymerizing hydrogel. *Tissue Engineering* **2003**, *9*, 679–688.
24. Foudazi, R.; Zowada, R.; Manas-Zloczower, I.; Feke, D. L. Porous hydrogels: Present challenges and future opportunities. *Langmuir: The ACS Journal of Surfaces and Colloids* **2023**, *39*, 2092–2111.
25. Nicodemus, G. D.; Bryant, S. J. The role of hydrogel structure and dynamic loading on chondrocyte gene expression and matrix formation. *J Biomech* **2008**, *41*, 1528–1536.
26. Garg, T.; Singh, O.; Arora, S.; Murthy, R. Scaffold: a novel carrier for cell and drug delivery. *Crit Rev Ther Drug Carrier Syst.* **2012**, *29*, 1–63.
27. Dehghani, F.; Annabi, N. Engineering porous scaffolds using gas-based techniques. *Curr Opin Biotechnol* **2011**, *22*, 661–666.
28. Ju, Y. M.; Park, K.; Son, J. S.; Kim, J.-J.; Rhie, J.-W.; Han, D. K. Beneficial effect of hydrophilized porous polymer scaffolds in tissue-engineered cartilage formation. *Journal of Biomedical Materials Research. Part B, Applied Biomaterials* **2008**, *85*, 252–260.
29. Keskar, V.; Marion, N. W.; Mao, J. J.; Gemeinhart, R. A. In vitro evaluation of macroporous hydrogels to facilitate stem cell infiltration, growth, and mineralization. *Tissue Engineering. Part A* **2009**, *15*, 1695–1707.

30. Barbetta, A.; Gumiero, A.; Pecci, R.; Bedini, R.; Dentini, M. Gas-in-liquid foam templating as a method for the production of highly porous scaffolds. *Biomacromolecules* **2009**, *10*, 3188–3192.
31. Sannino, A.; Netti, P. A.; Madaghiele, M.; Coccoli, V.; Luciani, A.; Maffezzoli, A.; Nicolais, L. Synthesis and characterization of macroporous poly(ethylene glycol)-based hydrogels for tissue engineering application. *Journal of Biomedical Materials Research. Part A* **2006**, *79*, 229–236.
32. Oliviero, O.; Ventre, M.; Netti, P. A. Functional porous hydrogels to study angiogenesis under the effect of controlled release of vascular endothelial growth factor. *Acta Biomaterialia* **2012**, *8*, 3294–3301.
33. Beaman, H. T.; Monroe, M. B. B. Highly porous gas-blown hydrogels for direct cell encapsulation with high cell viability. *Tissue Engineering. Part A* **2023**, *29*, 308–321.
34. Poursamar, S. A.; Hatami, J.; Lehner, A. N.; da Silva, C. L.; Ferreira, F. C.; Antunes, A. P. M. Gelatin porous scaffolds fabricated using a modified gas foaming technique: characterisation and cytotoxicity assessment. *Materials Science Engineering. C, Materials for Biological Applications* **2015**, *48*, 63–70.
35. Lim, Y.-M.; Gwon, H.-J.; Shin, J.; Jeun, J. P.; Nho, Y. C. Preparation of porous poly( $\epsilon$ -caprolactone) scaffolds by gas foaming process and in vitro/in vivo degradation behavior using  $\gamma$ -ray irradiation. *Journal of Industrial and Engineering Chemistry* **2008**, *14*, 436–441.
36. Nam, Y. S.; Yoon, J. J.; Park, T. G. A novel fabrication method of macroporous biodegradable polymer scaffolds using gas foaming salt as a porogen additive. *Journal of Biomedical Materials Research* **2000**, *53*, 1–7.
37. Amani, P.; Miller, R.; Javadi, A.; Firouzi, M. Pickering foams and parameters influencing their characteristics. *Advances in Colloid and Interface Science* **2022**, *301*, 102606.
38. Li, J.; Huang, H.; Xu, T.; Li, J.; Guo, T.; Lu, X.; Ren, J.; Ren, X.; Weng, J. Effect of the interconnecting window diameter of hydroxyapatite scaffolds on vascularization and osteoinduction. *Ceramics International* **2022**, *48*, 25070–25078.
39. Nguyen, Q. T.; Hwang, Y.; Chen, A. C.; Varghese, S.; Sah, R. L. Cartilage-like mechanical properties of poly(ethylene glycol)-diacrylate hydrogels. *Biomaterials* **2012**, *33*, 6682–6690.
40. Ricka, J.; Tanaka, T. Swelling of ionic gels: quantitative performance of the Donnan theory. *Macromolecules* **1984**, *17*, 2916–2921.
41. Loh, Q. L.; Choong, C. Three-dimensional scaffolds for tissue engineering applications: role of porosity and pore size. *Tissue Engineering. Part B, Reviews* **2013**, *19*, 485–502.
42. Zhang, Q.; Lu, H.; Kawazoe, N.; Chen, G. Pore size effect of collagen scaffolds on cartilage regeneration. *Acta Biomaterialia* **2014**, *10*, 2005–2013.
43. Nava, M. M.; Draghi, L.; Giordano, C.; Pietrabissa, R. The effect of scaffold pore size in cartilage tissue engineering. *Journal of Applied Biomaterials Functional Materials* **2016**, *14*(3), e223–e229.
44. Stenhamre, H.; Nannmark, U.; Lindahl, A.; Gatenholm, P.; Brittberg, M. Influence of pore size on the redifferentiation potential of human articular chondrocytes in poly(urethane urea) scaffolds. *Journal of Tissue Engineering and Regenerative Medicine* **2011**, *5*, 578–588.
45. Yamane, S.; Iwasaki, N.; Kasahara, Y.; Harada, K.; Majima, T.; Monde, K.; Nishimura, S.-I.; Minami, A. Effect of pore size on in vitro cartilage formation using chitosan-based hyaluronic acid hybrid polymer fibers. *Journal of Biomedical Materials Research. Part A* **2007**, *81*, 586–593.
46. Lim, S. M.; Jang, S. H.; Oh, S. H.; Yuk, S. H.; Im, G. I.; Lee, J. H. Dual-growth-factor-releasing PCL scaffolds for chondrogenesis of adipose-tissue-derived mesenchymal stem cells. *Advanced Engineering Materials* **2010**, *12*, B62–B69.
47. Ye, C.; Hu, P.; Ma, M.-X.; Xiang, Y.; Liu, R.-G.; Shang, X.-W. PHB/PHBHHx scaffolds and human adipose-derived stem cells for cartilage tissue engineering. *Biomaterials* **2009**, *30*, 4401–4406.
48. Jang, C. H.; Koo, Y.; Kim, G. ASC/chondrocyte-laden alginate hydrogel/PCL hybrid scaffold fabricated using 3D printing for auricle regeneration. *Carbohydrate Polymers* **2020**, *248*, 116776.
49. Im, G.-I.; Ko, J.-Y.; Lee, J. H. Chondrogenesis of adipose stem cells in a porous polymer scaffold: influence of the pore size. *Cell Transplantation* **2012**, *21*, 2397–2405.
50. Oh, S. H.; Kim, T. H.; Im, G. I.; Lee, J. H. Investigation of pore size effect on chondrogenic differentiation of adipose stem cells using a pore size gradient scaffold. *Biomacromolecules* **2010**, *11*, 1948–1955.
51. Fan, H.; Hu, Y.; Zhang, C.; Li, X.; Lv, R.; Qin, L.; Zhu, R. Cartilage regeneration using mesenchymal stem cells and a PLGA-gelatin/chondroitin/hyaluronate hybrid scaffold. *Biomaterials* **2006**, *27*, 4573–4580.
52. Uematsu, K.; Hattori, K.; Ishimoto, Y.; Yamauchi, J.; Habata, T.; Takakura, Y.; Ohgushi, H.; Fukuchi, T.; Sato, M. Cartilage regeneration using mesenchymal stem cells and a three-dimensional poly-lactic-glycolic acid (PLGA) scaffold. *Biomaterials* **2005**, *26*, 4273–4279.
53. Matsiko, A.; Gleeson, J. P.; O'Brien, F. J. Scaffold mean pore size influences mesenchymal stem cell chondrogenic differentiation and matrix deposition. *Tissue Engineering. Part A* **2015**, *21*, 486–497.
54. Xiao, Y.; He, L.; Che, J. An effective approach for the fabrication of reinforced composite hydrogel engineered with SWNTs, polypyrrole and PEGDA hydrogel. *Journal of Materials Chemistry* **2012**, *22*, 8076.
55. Moura, C.; Trindade, D.; Vieira, M.; Francisco, L.; Ângelo, D. F.; Alves, N. Multi-material implants for temporomandibular joint disc repair: Tailored additive manufacturing production. *Frontiers in Bioengineering and Biotechnology* **2020**, *8*, 342.



56. Della Sala, F.; Biondi, M.; Guarnieri, D.; Borzacchiello, A.; Ambrosio, L.; Mayol, L. Mechanical behavior of bioactive poly(ethylene glycol) diacrylate matrices for biomedical application. *Journal of the Mechanical Behavior of Biomedical Materials* **2020**, *110*, 103885.
57. Christensen, R. K.; von Halling Laier, C.; Kiziltay, A.; Wilson, S.; Larsen, N. B. 3D printed hydrogel multiassay platforms for robust generation of engineered contractile tissues. *Biomacromolecules* **2020**, *21*, 356–365.
58. Zhang, R.; Larsen, N. B. Stereolithographic hydrogel printing of 3D culture chips with biofunctionalized complex 3D perfusion networks. *Lab on a Chip* **2017**, *17*, 4273–4282.
59. Chan, V.; Zorlutuna, P.; Jeong, J. H.; Kong, H.; Bashir, R. Three-dimensional photopatterning of hydrogels using stereolithography for long-term cell encapsulation. *Lab on a Chip* **2010**, *10*, 2062–2070.
60. Dadsetan, M.; Hefferan, T. E.; Szatkowski, J. P.; Mishra, P. K.; Macura, S. I.; Lu, L.; Yaszemski, M. J. Effect of hydrogel porosity on marrow stromal cell phenotypic expression. *Biomaterials* **2008**, *29*, 2193–2202.
61. Mohanty, S.; Larsen, L. B.; Trifol, J.; Szabo, P.; Burri, H. V. R.; Canali, C.; Dufva, M.; Emnéus, J.; Wolff, A. Fabrication of scalable and structured tissue engineering scaffolds using water dissolvable sacrificial 3D printed moulds. *Materials Science & Engineering. C, Materials for Biological Applications* **2015**, *55*, 569–578.
62. Hwang, C. M.; Sant, S.; Masaeli, M.; Kachouie, N. N.; Zamanian, B.; Lee, S.-H.; Khademhosseini, A. Fabrication of three-dimensional porous cell-laden hydrogel for tissue engineering. *Biofabrication* **2010**, *2*, 035003.
63. Muniz, E. C.; Geuskens, G. Compressive elastic modulus of polyacrylamide hydrogels and semi-IPNs with poly(N-isopropylacrylamide). *Macromolecules* **2001**, *34*, 4480–4484.
64. Li, Z.; Liu, Z.; Ng, T. Y.; Sharma, P. The effect of water content on the elastic modulus and fracture energy of hydrogel. *Extreme Mechanics Letters* **2020**, *35*, 100617.
65. Schinagl, R. M.; Gurskis, D.; Chen, A. C.; Sah, R. L. Depth-dependent confined compression modulus of full-thickness bovine articular cartilage. *Journal of Orthopaedic Research: Official Publication of the Orthopaedic Research Society* **1997**, *15*, 499–506.
66. Park, J. S.; Chu, J. S.; Tsou, A. D.; Diop, R.; Tang, Z.; Wang, A.; Li, S. The effect of matrix stiffness on the differentiation of mesenchymal stem cells in response to TGF- $\beta$ . *Biomaterials* **2011**, *32*, 3921–3930.
67. Steward, A. J.; Wagner, D. R.; Kelly, D. J. The pericellular environment regulates cytoskeletal development and the differentiation of mesenchymal stem cells and determines their response to hydrostatic pressure. *European Cells & Materials* **2013**, *25*, 167–178.
68. Otero, M.; Favero, M.; Dragomir, C.; Hachem, K. E.; Hashimoto, K.; Plumb, D. A.; Goldring, M. B. Human chondrocyte cultures as models of cartilage-specific gene regulation. In *Methods in Molecular Biology*, 1st ed.; Picot, J., Eds. Humana Press: Clifton, N.J.; U.S.A.; 2012; Volume 107, pp. 301–336.
69. Surmeneva, M. A.; Kovtun, A.; Peetsch, A.; Goroya, S. N.; Sharonova, A. A.; Pichugin, Grubova; I. Y., Ivanova, A. A.; Teresov, A. D.; Koval, N. N.; et al. Preparation of a silicate-containing hydroxyapatite-based coating by magnetron sputtering: structure and osteoblast-like MG63 cells in vitro study. *RSC Advances* **2013**, *3*, 11240.
70. Musumeci, G.; Loreto, C.; Carnazza, M. L.; Strehin, I.; Elisseeff, J. OA cartilage derived chondrocytes encapsulated in poly(ethylene glycol) diacrylate (PEGDA) for the evaluation of cartilage restoration and apoptosis in an in vitro model. *Histology and Histopathology* **2011**, *26*, 1265–1278.
71. Musumeci, Giuseppe, Carnazza, M. L.; Loreto, C.; Leonardi, R.; Loreto, C.  $\beta$ -Defensin-4 (HBD-4) is expressed in chondrocytes derived from normal and osteoarthritic cartilage encapsulated in PEGDA scaffold. *Acta Histochemica* **2012**, *114*, 805–812.
72. Johnstone, B.; Hering, T. M.; Caplan, A. I.; Goldberg, V. M.; Yoo, J. U. In vitro chondrogenesis of bone marrow-derived mesenchymal progenitor cells. *Experimental Cell Research* **1998**, *238*, 265–272.
73. Markway, B. D.; Tan, G.-K.; Brooke, G.; Hudson, J. E.; Cooper-White, J. J.; Doran, M. R. Enhanced chondrogenic differentiation of human bone marrow-derived mesenchymal stem cells in low oxygen environment micropellet cultures. *Cell Transplantation* **2010**, *19*, 29–42.
74. Suzuki, S.; Muneta, T.; Tsuji, K.; Ichinose, S.; Makino, H.; Umezawa, A.; Sekiya, I. Properties and usefulness of aggregates of synovial mesenchymal stem cells as a source for cartilage regeneration. *Arthritis Research & Therapy* **2012**, *14*, R136.
75. International Organization for Standardization. ISO 10993-5, Biological evaluation of medical devices—Part 5: Tests for in vitro cytotoxicity, **2009**.

**Disclaimer/Publisher's Note:** The statements, opinions and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of MDPI and/or the editor(s). MDPI and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions or products referred to in the content.