

Review

Not peer-reviewed version

# Current Trends on Unique Features and Role of Nanomaterials in Personal Care Products

Nimasha Rathnasinghe , [K.G. Kaushani](#) , B.P.S. Rajapakshe , [Awanthi De Silva](#) , R.A. Jayasinghe ,  
A.H.L.R Nilmini , Nadeeka D Tissera , [Ruchira N Wijesena](#) , [Gayan Priyadarshana](#) \*

Posted Date: 30 July 2024

doi: 10.20944/preprints202407.2373.v1

Keywords: Cosmetics; Features; Nanomaterials; Nanotechnology; Skincare



Preprints.org is a free multidiscipline platform providing preprint service that is dedicated to making early versions of research outputs permanently available and citable. Preprints posted at Preprints.org appear in Web of Science, Crossref, Google Scholar, Scilit, Europe PMC.

Copyright: This is an open access article distributed under the Creative Commons Attribution License which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Review

# Current Trends on Unique Features and Role of Nanomaterials in Personal Care Products

Nimasha Rathnasinghe <sup>1,2</sup>, K.G. Kaushani <sup>1,2</sup>, B.P.S. Rajapakshe <sup>1,2</sup>, Awanthi De Silva <sup>3</sup>, R.A. Jayasinghe <sup>4</sup>, A.H.L.R. Nilmini <sup>1</sup>, Nadeeka D. Tissera <sup>5</sup>, Ruchira N. Wijesena <sup>5</sup> and Gayan Priyadarshana <sup>1,\*</sup>

<sup>1</sup> Department of Materials and Mechanical Technology, Faculty of Technology, University of Sri Jayewardenepura, Pitipana, Homagama, 10200, Sri Lanka

<sup>2</sup> Faculty of Graduate Studies, University of Sri Jayewardenepura, 10250, Sri Lanka

<sup>3</sup> Royal Australian Chemistry Institute, Vale Street, North Melbourne, Victoria, Australia

<sup>4</sup> Department of Civil and Environmental Technology, Faculty of Technology, University of Sri Jayewardenepura, Pitipana, Homagama, 10200, Sri Lanka

<sup>5</sup> Department of Textile and Clothing Engineering, Institute of Technology, University of Moratuwa, Diyagama, Homagama, 10200, Sri Lanka

\* Correspondence: Correspondence: gayanp@sjp.ac.lk; +94713287738

**Abstract:** Nanotechnology has applications in a variety of scientific specialties, encompassing health, technological devices, and now cosmetics under the generic term of nanocosmetics. Due to the improved particle qualities, such as color, transparency, and solubility, acquired at the nanoscale, nanotechnology significantly affects the cosmetic industry. Skin penetration mechanism depends heavily on the nanoparticles' physicochemical properties, including stiffness, hydrophobicity, size, and charge. An expanding industry that requires more research and development has been created by nanoparticle production technologies. Liposomes, solid lipid nanoparticles, cubosomes, dendrimers, and other nanomaterials offer advanced skincare properties. Cosmetics made using nanotechnology have the advantages of product diversity, increased bioavailability of active compounds, and enhanced pleasing appearance of cosmetics with long-lasting benefits. The various cosmetic brands' utilization of various types of nanomaterials in their products is highlighted in this review.

**Keywords:** cosmetics; features; nanomaterials; nanotechnology; skincare

## 1. Introduction

Innovative interactions between the domains of polymers and material sciences have been taking place during the past two decades in the pharmaceutical business, leading to the creation of new drug delivery methods [1]. With the help of nanoscale shape and size manipulation, structures, devices, and systems can be designed, characterized, manufactured, and used. Numerous industries, including those in food, cosmetics, agriculture, medicine, paints, and textiles, have found extensive use for nanotechnology.

Numerous factors contribute to the widespread use of nanomaterials in the cosmetics industry. The vast increase in consumer demand has resulted in the creation of cosmetic formulations with improved performance, appealing appearance, retention, and most importantly safety. [2]. The potential of nanomaterials to increase the distribution of cosmetic components into the skin is arguably the most commonly asserted benefit of their usage in cosmetics. Lipid vesicles, such as liposomes, are microscopic lipid (fat) structures that can encapsulate compounds. Due to their small size, they can penetrate the skin more easily, facilitating the absorption of the encapsulated compounds into deeper layers of skin [1].

Nanomaterials can also be employed to give formulations that contain components that could disintegrate as a result of oxidation or other factors more stability. Nanoscale versions of substances

are used by cosmetic makers to provide products with improved UV protection, longer effects, deeper skin penetration, finish quality, higher color, etc [3]. Because nanoparticles would aid in delivering greater performance and higher finish quality of the items, manufacturers of cosmetics have worked to create a variety of more attractive contemporary cosmetic-related goods that include nanoscale components. Improved shelf life and enhanced formulation penetration at the application site are two of the main advantages of using nanoparticles in cosmetics.

Recent scientific developments and global efforts to foster nanotechnology and nanomedicine research are indications that products of nanotechnology are expected to revolutionize modern medicine. These developments directly benefit the field of drug delivery. 90% of all pharmaceuticals contain solid particles as their active compounds. These developments directly benefit the field of drug delivery. The active ingredient in 90% of all medicines is in the form of solid particles, according to pharmaceuticals [4]. Improved skin penetration is made possible by their high specific surface area ratio, nanoparticles are increasingly being used in cosmetic formulations. The skin can be effectively absorbed and penetrated by the nano-based products.

The surface of nanoparticles, which serve as a delivery mechanism, has the active components adsorbed on them. Incorporating nanoparticles of various shapes and chemical compositions into cosmetics formulations can indeed maximize the benefits derived from their shape- and size-dependent activities [2]. The presence of nanoparticles in cosmetic products can operate as active substances, consistency-improving elements, and transporters, and can boost the efficacy of cosmetic products. These nanoparticles can be added to cosmetics to give them new properties. Different kinds of nanomaterials exist, each with a unique set of properties and potential uses.


## 2. Nanotechnology

In nanotechnology, structures and systems at the atomic and molecular sizes are created through the manipulation of materials [5]. The creation, evaluation, and use of compositions, structures, and devices on the nanoscale by manipulating size and shape is nanotechnology, which is the most promising technological advancement of the twenty-first century [6].

Depending on how they are structurally shaped, nanomaterials fall into one of three categories: materials with a single dimension at the nanoscale, such as surface coatings or thin films with a length dimension; materials with two dimensions, length, and width such as nanowires and nanotubes; and materials with three dimensions, the width, length, and depth of quantum dots and colloids, will revolutionize sophisticated materials such as drugs and diagnostic supplies, chemical materials, cosmetics, electricity sector and electric appliances [7].

In 1959, renowned physicist Richard Feynman coined the term nanotechnology. At the nanoscale, matter has been found to have distinctive characteristics. Nanoparticles with sizes ranging from 1 to 100 nanometers are particularly advantageous because they exhibit unique properties that enhance their ability to penetrate through the barriers [8]. To produce, process, and exploit chemical, biological, and physical systems at scales ranging from single atoms or molecules to submicron dimensions, as well as to integrate the resulting nanostructures into larger systems, the term "nanotechnology" is used. By integrating nanotechnology into broader systems, such as smart materials, electronics, information technology, drug delivery, and biotechnology, many contemporary medical, industrial, and environmental issues have been resolved [9].

Nanoparticles are found in creams for cellulite reduction, wrinkle reduction, and skin-lightening moisturizing, sunscreens, deodorants, soaps, face powders, perfumes, make-up in the cosmetic industry, shampoos, conditioners, toothpaste, and nail polishes in general[10].



**Figure 1.** Nanomaterials in different cosmetic applications[11].

When compared to bulk material, nanoparticles' physicochemical properties are different, and this naturally depends on their size and shape. By changing the shape and size at the nanoscale level, the nanomaterials surprisingly establish a distinctive character with new features and abilities. Different morphologies of nanomaterials, such as nanorods, nanoparticles, and nanosheets, can be identified based on their dimensionality [12]. As nanomaterials, "nanoemulsions" are a type of emulsions with consistent, tiny droplets ranging from 20 to 500 nm that are becoming more and more common as platforms for the controlled release and ideal dispersion of active components [10,13].

Nanotechnology involves the manipulation and utilization of materials at the nanoscale, typically ranging from 1 to 100 nanometers in size. This field encompasses a multidisciplinary approach, drawing from physics, chemistry, biology, materials science, and engineering. Nanotechnology enables the precise control and engineering of materials and structures at the atomic and molecular levels, leading to the development of novel properties and functionalities not observed in bulk materials [14].

### 3. Nanotechnology in Skincare Products

Nanotechnology-based cosmetic delivery technologies include nanoemulsions, nanocrystals, nanocapsules, liposomes, niosomes, dendrimers, carbon nanotubes, solid lipid nanoparticles, and carbon nanotubes. Submicron emulsions (SME), which have uniform and very small droplet sizes, are the most recent nanoparticulate systems for skincare (20-500 nm). In cosmetics, their demand is expanding. Where the industry uses a variety of procedures with fewer environmental risks, including the development of nanomedicine, antioxidant use, and nanocarrier modification [6,15].

Drug delivery techniques using nanoparticles such as micelles, polymeric nanocapsules, solid lipid nanoparticles, nanoemulsions, nanocrystals, liposomes, and niosomes are of interest to the cosmetic industry [6]. Nanoparticles are being used in an expanding number of commercial applications that could result in skin absorption and direct contact with people [16].

The advantages of utilizing nanocosmetics include preventing substances from deteriorating chemically or enzymatically, managing their release, especially when irritants are present in excessive dosages, and increasing the residence period of pharmaceutical or cosmetic ingredients in the stratum corneum [10,13]. In 1995, Lancôme became the first business to commercialize a cosmetic based on nanotechnology when it released a face lotion to combat skin aging that contained tiny, pure vitamin E capsules [17]. Other global businesses started funding research to create nanocosmetics following the initiative [10]. Brands such as Dermazone Solution, Skinceuticals, Estee Lauder, Shiseido, Garnier, and Johnsons & Johnsons, as well as Christian Dior, Procter & Gamble, Anna Pegova, Revlon, and Chanel, have invented products in this field [13]. Global brands like Avenue, Bioderma, L'Oréal, Laroche-posay, Garnier, and others from around the world and locally claim that their products are



higher in efficacy because they incorporate micellar nanotechnology into their formulations, i.e., facial cleansers [18].

To effectively distribute active compounds through skin barriers, formulations for cosmetics usually employ several nano-systems or novel nanocarriers. These nano-systems can assist with the penetration or absorption of cosmeceutical active moieties inside epidermal layers, allowing for a burst or continual release of actives [19].

When nanotechnology first emerged, it was hailed as a major scientific breakthrough and a step toward producing high-quality goods; the cosmetics industry is already well-versed in its use [20]. Nanoscale compounds are used by cosmetics manufacturers to provide several benefits, including enhanced UV defense, longer-lasting effects, deeper skin penetration, color intensity, and excellent finish. In both domestic and international markets for beauty products, a revolutionary technology known as micellar nanoparticles is being widely adopted and commercialized [18]. When applied to the skin, numerous nanoparticles used in cosmetics that claim to increase skin absorption may instead be unstable and incapable of delivering substances below the skin's surface layer. By encouraging greater diffusion of the cosmetic vehicle penetrates the skin's surface layer, they may, however, facilitate skin absorption [1,21].

The quantity of nanoparticles currently being researched demonstrates the significance of this science to the large and well-established beauty industry. Indeed, because of the biocompatibility, stability, and antioxidant properties of nanoparticles, Active Cosmetic Ingredients are reliably delivered to the skin and better absorbed. These nanostructures can be incorporated into recipes for deodorants, hair products, skin-whitening products, anti-aging creams, makeup, nail care, and dental products like elixirs and toothpaste [22].

These colloidal aqueous solutions improve drug stability in the sectors of cosmetics and dermatology,[23], regulate and delay drug distribution [24] and increase drug adhesion on the skin [25,26]. Among the various nanopharmaceutic agents nanoemulsions, nanosuspensions, nanocapsules, nanoshells and nanotubes, and lipids are important [27].

Nanotechnology can be applied to cosmetics for several reasons, such as improving the solubility and stability of active ingredients, controlling the rheological properties from the point of production to the consumer, and meeting sensory expectations and product efficacy during dermal application [28].

#### **4. Nanomaterials Used in Skincare Products**

The inclusion of both hydrophilic and hydrophobic compounds, enhanced stability, controlled release, targeted transport to target cells, and the capacity to elicit a biological reaction at concentrations below therapeutic levels are just a few benefits of using nanomaterials in cosmetics [29]. Nowadays, it's well understood that using nanoscale materials, which serve as both an active component and/or a carrier, can enhance the performance of cosmetics in a variety of ways. As a result, it may be simple to identify certain technologies as industry standards [20,30].

Cubosomes, nanodots, liposomes, dendrimers, and nano-emulsions are only a few examples of nano-sized substances that are now frequently used in cosmetics as a result of the nanotechnology integration into the manufacture and formulation of cosmetics. These nanoparticle-based cosmetics also referred to as nano-cosmeceuticals, have increased the potential uses of cosmetics to treat aging-related skin conditions like distributed hyperpigmentation, dehydration, and wrinkled skin [3,31]. In addition, numerous different nanosized varieties can be found in sunscreen, anti-aging products, and curling irons [31].

Nano-carriers have been utilized for passive drug administration into and through the skin because they have several benefits compared to typical passive distribution techniques, including increased drug loading, site-targeted distribution, the regulated release of the active ingredient, improved stability, soothed skin irritation, protection from degradation, larger surface area, higher solubility, and enhanced active pharmaceutical ingredient penetration into the skin [30,32].




Figure 2. Nanomaterials used in topical applications.

When developing drug delivery systems in the early 1970s, liposomes were the first type of nano-carriers used [32]. Liposomes are composed of a lipid bilayer, which is why Dior invented cream capture in 1986.

Hydrophobic and hydrophilic compounds can be delivered using liposomes, which are non-hazardous, biocompatible, and biodegradable vesicles that can easily encapsulate active ingredients. By enhancing their skin absorption, liposomes can raise the concentration of active substances [6]. To raise the percentage of bioactive components (such as vitamins A, E, and CoQ10) in the epidermis without causing any immediate or long-term harm, liposomes are applied topically or for transdermal distribution [33]. Another one of the reasons liposomes are so used extensively in the cosmetics industry is that they are simple to make [15].

Nanoemulsions are transparent liquid dispersions that contain a surfactant, an oil phase, and 20 to 200 nm in terms of size [34]. The creation of nanoemulsions as a means of administering medications orally, parenterally, intranasally, topically, and for intratracheally. Topical nanoemulsions with gamma-aminobutyric acid, an inhibitory neurotransmitter with properties that calm the muscles, are being researched for the treatment of wrinkles [35]. Bicontinuous nanoemulsions, water-in-oil nanoemulsions, oil-in-water nanoemulsions, and many other varieties of nanoemulsions can be produced depending on the composition. Sinerga's Nanocream® is an emulsifier mixture that may be used to create oil-in-water nanoemulsions. Wet wipes, sprayable emulsions, and hyper-fluid emulsions are all intended applications for this substance [19,36].

Nanoemulsion (O/W nanoemulsion) offers better cosmetic characteristics that make this nanosystem capable of producing micellar nanoparticles of lesser sizes (10 - 200 nm), which promotes uniform distribution on the skin, high stability, boosts active component delivery capabilities, pleasant aesthetic character, bigger surface area, and skin feel [18,37]. The reason is that they are stable for the skin's absorption of lipophilic substances, and they are an excellent carrier for the treatment of acne vulgaris [38].

Microdispersions called nanoemulsions are nanosized droplets of one insoluble liquid in another that are differentiated by their great thermodynamic stability and small dispersed phase size (100 nm) [39]. Active substances can more easily reach the skin and hair because of nanoemulsions' pleasant, light, and non-greasy nature. They are an effective method of delivering certain critical hydrophobic chemicals (antioxidants, fat-soluble vitamins, lipids, etc.) when used in therapeutic concentrations (antioxidants, fat-soluble vitamins, lipids, etc.) [40]. Nanoemulsions are utilized to increase the skin's barrier function and decrease transdermal water loss [29,40].

Many cosmeceuticals, including deodorants, sunscreens, shampoos, lotions, nail polishes, conditioners, and hair serums, use nanoemulsions as a delivery system [41]. In the development of cosmetics, nanoemulsions are utilized to promote quick penetration, active transport of active ingredients, and skin hydration [42].

For instance, a new Nano-based gel has been developed by TRI-K Industries and its patent partner Kemira, to improve the effectiveness of different skin care products. One novel nanoemulsion carrier system is called Kemira Nanogel to is simple to make while simultaneously offering extra advantages as a result of its nanotechnology characteristics [27].

Lipid nanoparticles, which can range in size from 50 to 1000 nm, are physiological lipid-based submicron colloidal carriers distributed in aqueous surfactant solutions or water. Solid Lipid Nanoparticles (SLNs) are frequently employed in the cosmeceuticals industry due to their intrinsic qualities, such as constrained features, a tiny structure that permits direct proximity to the skin, enhanced skin permeability, minimal toxicity, and other qualities. The benefits of SLNs and nanostructured lipid carriers (NLCs) include improved shelf life of the finished product, improved bioavailability and site-specific action, desired degree of occlusion and consequent skin hydration, and active ingredient stabilization [6]. The SLN/NLC mark abides by a set of standards.

The following is outlined in the "VW Beetle 1938 Principle": 1. 1. Physical adherence of the skin 2. Occlusion due to physical film formation 3. Physical barriers that prevent drug entry 4. Chemical interactions between skin lipids and particle lipids. It prevents the materials from deteriorating [6]. In turn, this causes chemicals to be released slowly. It is employed in the perfume business and as an insect repellent. Since it promotes skin moisture and permeates the corneal layer. To lessen the redness of an allergic reaction, they are also utilized by Nano repair creams and lotions [43]. When compared to oral therapy, solid lipid nanoparticles with cyproterone acetate loaded on them improved transdermal delivery and penetration, which reduced systemic adverse effects and produced therapeutic medication levels in the target area. Acne lesions and sebum production can both be reduced with the help of the oral drug cyproterone acetate. NLCs, OCT, and SLNs were used to encase the BMDBM to block UVA rays. With 2.5% BMDBM and 1% OCT, the best outcomes are attained [6,44].

For dermal application of cosmetic items, well-tolerated carrier systems include SLNs and NLCs. There are a wide variety of cosmetic ingredients; Coenzyme Q10, retinol, tocopherol (vitamin E), and ascorbyl palmitate (vitamin A) are just a few. they provide controlled release profiles showing minimal toxicity and cytotoxicity for an extended period [33,45]. Additionally, Acne, skin mycosis, psoriasis, atopic eczema, and inflammations have all been treated with lipid nanoparticles in research studies [46].

When applied to the skin's surface, ZnO and TiO<sub>2</sub> nanoparticle mixtures are transparent. When compared to formulations with bigger particles, this transparency offers cosmetic acceptability. The goal of the current investigation was to evaluate the possible systemic exposure and epidermal penetration of an innovative sunscreen formulation containing ZnO nanoparticles. After applying ZnO nanoparticulate sunscreen formulation topically for 24 hours, we were able to pinpoint the ZnO

particle distribution throughout the epidermis and measure the cumulative zinc content that penetrated by use of in vitro epidermal membranes. Recent studies on pig skin subjected to sunscreen formulations containing ZnO in minute form (averaging 80 nm for the main particles) and TiO<sub>2</sub> (needle-like particles ranging in size from 30 to 60 nm) indicated that none of the particle types could pierce the pig's stratum corneum.

Additionally, the availability of the sunscreen ingredient octyl methoxycinnamate (OMC) in porcine skin was improved by encapsulating it in solid lipid nanoparticles (250 instead of being a direct result of nano-encapsulation itself, it was found in the latter investigation. This effect was produced via simple formulation thermodynamics, which improved partitioning into the stratum corneum. Solid lipid nanoparticles have been linked to higher degrees of penetration as a result of their immediate effect on skin moisture, which results in improved stratum corneum water retention, which causes the skin's surface to form a film and effectively occlude the application location. When compared to rates previously reported for chemical sunscreens, human skin only absorbed a small amount of nanoparticle-coated ZnO. A mineral oil vehicle allowed for the in vitro absorption of oxybenzone at levels of between 5 and 7 percent across human epidermal membranes, compared to 0.03-0.14% for octocrylene, 0.07 and 0.17 percent for ethylhexyl methoxycinnamate, and 0.09 and 0.20 percent for ethyl hexyl dimethyl [6].

Recently, the use of nanoparticles made of titanium dioxide (TiO<sub>2</sub>) and zinc oxide (ZnO) has increased due to their ability to sustain the UV blocking and absorbing qualities of conventional sunscreens without having the white chalky appearance. Meanwhile, it has been claimed that a few changes to the standard ZnO or TiO<sub>2</sub> UV protection system have increased the sun protection factor (SPF)[33,47]. Since 1995, L'Oreal has employed nanocapsules containing active substances including retinol, vitamin A, and beta-carotene that can penetrate the skin's deep layers to provide antiaging effects. The dimensions of these tiny biodegradable polymeric shells range from 300 to 600 nm [48].

Essential oils are composed of lipophilic and extremely volatile secondary plant metabolites with their antibacterial activity, they can be employed in the cosmetics sector, complementary medicine, and agro-alimentary purposes [49]. The active ingredient is contained in a cavity within the liquid/solid core of a nano-capsule, it has a polymer barrier surrounding it made of either natural or manmade polymers. The production of hydrogels and emulgels depends on nano-capsules. Additionally, hydrogel is employed in the production of several goods for personal care [15]. The nanocapsule's sensory properties have been established that when the cosmetics industry grows, certain companies change the product's features to improve quality and effectiveness. Sensory analysis is used to accomplish this purpose. Only human reactions can determine how much this product's use is impacted. The study and development of the beauty industry have proven that this sensory analysis is a powerful analytical tool.

The active components in lipoic acid nanocapsules serve to both prevent and treat skin anti-aging. Increase the physiochemical stability of lipoic acid once the substance has been protected against deterioration via nanocapsulation. Lipoic acid-containing cosmetics outperform substitutes in terms of dependability, stickiness, oiliness, and sulfur odor [50]. Furthermore, as compared to Benzoyl peroxide alone, the Chitosan-alginate Nanoparticles successfully benzoyl peroxide (BP), an anti-acne drug that is often encapsulated, which demonstrated stronger antibacterial efficacy against propionic bacterium *acnes* while causing less damage to eukaryotic cells [6].

It is possible to load desired chemicals inside nanocapsules, which are polymeric nanoparticles with a hollow interior. These nanocapsules can then be shielded from the outside environment. To get retinol into the skin's deepest layers, L'Oreal (a French business with a nanotechnology patent in the US) has employed polymer nanocapsules [26]. In addition, Lancôme developed a product called Primordiale Optimum Lip that delivered 100% botanically pure vitamin E using nanocapsule technology to prevent lip bleeding and feathering brought on by fine lines and wrinkles [31].

Nanocapsules are employed in the manufacturing of cosmetics to safeguard chemicals, lessen chemical smells, and fix compatibility problems between formulation elements. Polymeric nanocapsule suspensions can either be used as a finished product that is applied directly to the skin or as an ingredient in semisolid formulations [51]. UV filters, for example, can only penetrate a certain



amount of skin with the use of nanocapsules [52], or administer active chemicals to the skin's deep layers, such as genistein [26,53].

Following the nanocapsules' topical use produces a light coating of skin that evaporates when in contact with water. The increased potential of the skin to keep the vital element in reserve in comparison to this thin film for long-term delivery [25,54].

Fullerenes are a novel class of materials produced via nanotechnology, such as carbon fullerenes. The term "buckyballs" is also used to describe fullerenes. In terms of antioxidant activity, fullerenes outperform vitamins by at least two orders of magnitude. A brightening effect of fullerene is also present. By eliminating UV-induced free radicals and lowering excessive melanin formation, it enhances the appearance of the skin. The use of fullerenes in cosmeceutical treatments for skin renewal has received attention because of their antioxidant characteristics, which have been used in many cosmetic goods. They are utilized to create creams with a healthy appearance that are then applied to lighten under-eye shadows [55,56].

Due to their potent anti-radical oxygen species (ROS) scavenging abilities, fullerenes have been considered for usage in the creation of skin-rejuvenating cosmetic compositions [57]; But there is still considerable disagreement over their safety [33]. Because they penetrate the skin so well, 'Fullerene' nanoparticles made of carbon are used in moisturizers and anti-aging products. As a result, nano-scale compounds are frequently used in the cosmetics business. [5].

The carbon spheres known as fullerenes measure 1 nm in diameter and contain 60 carbon atoms. Despite being hydrophobic, fullerenes can be chemically functionalized by incorporating a hydrophilic component, allowing them to be water-soluble and able to transport biomolecules like DNA and proteins [58]. The therapeutic uses are made possible by their small size, spherical form, and hollow interior [38]. Because aging skin is linked to increased oxidative stress and apoptosis, the development of cosmetic treatments for skin rejuvenation spurred a lot of scientists to research the application of fullerenes. In experiments with human keratinocytes, fullerenes showed substantial antioxidant properties and no cytotoxicity [57,59].

The cosmetic industry, which explores new cosmetic uses of scientific advancements, is a rapidly expanding sector. Fullerenes were the focus of research into cosmetics last year because of their potent antioxidant abilities and capacity to absorb free radicals. Although several research assessing the biological activities of fullerenes have produced highly encouraging results, their application in cosmetic items is still very low [57].

The development of sunscreen formulas may make use of fullerenes. Effectively shields the skin from UVA and UVB radiation, as well as shielding it from DNA damage and immunosuppression. In a recent patent, it was stated that a sunscreen formulation comprising carbon nanotubes (structures similar to fullerene made of molecular-scale tubes of graphitic carbon) was developed [57].

Nanocrystals demonstrated several properties, including increased membrane penetration, greater adhesion, and permeation of the gastrointestinal membrane; these qualities were subsequently utilized to affix nanoparticles for topical administration [32]. Also, nanotechnology is a major help in toothpaste formulations for preventing the degeneration of tooth enamel [6,60].

Rutin is a flavonoid that is present in nanocrystals, which are made up of atoms in a monocrystalline or polycrystalline structure and have a minimum of one dimension smaller than 100 nanometers. A nanocrystal version of the antioxidant rutin called Juvedical was introduced in 2000 by the cosmetics company Juvena. According to a study, the original rutin molecule is 500 times more bioactive in this form than it is in its water-soluble form, rutin glycoside. Rutin glycoside and rutin nanocrystals were compared using the sun protection factor [61]. It was particularly interesting since the skin contained a significantly higher concentration of the active ingredients synthesized as nanocrystals than the glycoside or powder, despite the nanocrystal solution being less soluble. A similar study discovered that Gel-based rutin nanocrystals had the strongest antioxidant (neutralizing) activity when compared to the powder or the form that is readily accessible for purchase [31,62].

Nanogold and nanosilver both possess antifungal and antibacterial properties. They are regularly used in cosmeceutical products such as face masks, deodorant, and anti-aging lotion. They have been added to facial masks and moisturizing creams [63,64].

Cosmetic manufacturers exploit nanosilver's enhanced antibacterial properties for a variety of applications. Several manufacturers currently provide underarm deodorants that purport to provide up to 24-hour antibacterial protection due to the silver in the product. The usage of gold nanoparticles in toothpaste is similar to that of nanosilver since they are thought to be very effective at removing oral germs [3].

The size of gold nanoparticles, also known as nanogold, ranges from 5 nm to 400 nm. They can be formed into forms in a variety, including nanoshells, nanospheres, nanoclusters, nanorods, nanocubes, nanotriangles, and branching nanotriangles. Shape, size, dielectric qualities, and environmental factors all have a significant impact on the frequency response of gold nanoparticles.

By guiding the drug to the proper therapeutic region, niosomes, which are biodegradable and typically harmless vesicles made of nonionic surfactants, aid in the attainment of site-specific delivery. Although it is similar to liposomes, it is stable and has hydrophilic and hydrophobic ends. Lancôme was hence the first item L'Oreal released in 1987. Amphiphilic or lipophilic medicines are transported by niosomes [29,32]

Dendrimers are unimolecular nanostructures that are globular, symmetrical and have several strongly branching segments. The total number of branch series determines dendrimer formation [19,65]. Dendrimers have been investigated for use in cosmetics and pharmaceuticals. These monodisperse, unimolecular functional end groups are highly concentrated at the perimeter of symmetrical, unimolecular micellar nanostructures [33].

A high density of surface functioning is provided by dendrimers, which are symmetrical structures that are clearly defined, consistently branched and have a tree-like shape with branch terminals. Numerous cosmetic products use it because of its size and molecular weight. Lavender and nail polish are comparable. They are beneficial in the fields of artificial tanning, hair, skin, and nail care because of their revolutionary film-forming ability. They can be used to treat acne [6].

Cubosomes are distinct nanoparticles of the crystal phase that are continuously cubic and liquid with a significantly increased specific surface area than the parent cubic phase. Additionally, it may moisturize the skin and has a high heat stability [6,66].

It is created when a certain ratio of water and a microstructure is combined with liquid crystalline particles of a particular surfactant. Due to the affordable monetary value of the basic materials and the possibility of regulating the act of functionalizing release, they are a desirable option for both medicine delivery and cosmetic applications [3].

Nanospheres are spherical polymeric matrices the size of the particles ranges from 10 to 200 nm. Both biodegradable and non-biodegradable nanospheres are present in various nanoscale carriers, whether crystalline or amorphous. Pure or modified starch, gelatin, and albumin-based nanospheres are examples of biodegradable nanospheres, as opposed to Polylactic acid is an example of a non-biodegradable nanosphere. The skin's outermost layer receives active chemicals when nanospheres are employed in cosmeceutical products for the skin or body [19].

The drugs or medicine is bound, broken down, adhered to, or encapsulated by nanospheres, which shield it from enzymatic and chemical destruction. To more precisely and effectively deliver active substances to the skin's deeper layers and their therapeutic potential on the affected area, nanospheres are utilized in dermal treatments and cosmetic products [42].

## 5. Unique Features of Nanomaterials in Skincare Products

Numerous techniques have already been shown by research on nanotechnology to improve the effectiveness of cosmetics, including 1) enhancing the skin penetration and entrapment effectiveness of the active ingredient, 2) regulating medication release, 3) enhancing physical stability, 4) enhancing moisturizing ability, and 5) enhancing UV protection [20]. Nanoscale materials frequently have different chemical or physical characteristics from their bigger counterparts, such as elevated biologically harmful action, owing to their small size and peculiarly high surface area-to-volume

ratio. This is one of the reasons why nanoscale compounds are becoming more and more popular in the beauty sector [5].

**Table 1.** Nanomaterials and specific properties of nanomaterials used in personal care products.

Nanomaterials	Personal Care Products	Specific properties of nanomaterials	References
Nanoemulsions	Nano-based gel	Improve the effectiveness of products	[41]
	Deodorants	As a delivery system	
Nanoemulsions	Sunscreens	Promote quick penetration	[42]
	Shampoos	Active transport of active ingredients	[6]
	Lotions		
	Nail Polishes		
	Conditioners		
Nanoemulsions	Hair Serums	Skin hydration	
Lipid nanoparticles		Permits direct proximity to the skin	[31].
		Enhance skin permeability	
		minimal toxicity	
	Nano repair cream	Improve the shelf life of the finished product	
	Lotions		
Lipid nanoparticles	Moisturizer	Improve bioavailability and site-specific action,	[67]
	Anti-wrinkle creams	The desired degree of occlusion	[43]
	Sunscreen	Consequent skin hydration	
Lipid nanoparticles		active ingredient stabilization	
Nanoparticle		Transparency than large particles	[6]
	Sunscreen	Higher degrees of penetration	
Nanoparticle	Antiaging creams	Immediate effect on skin moisture	[47][33]
Nano-capsule		Improve quality and effectiveness	[15]
	Hydrogel	Increase the physiochemical stability of ingredients	
	Anti-aging creams	Stronger antibacterial efficacy	
	Anti-acne drug	Able to deliver targeted tissue or cells	
	Lip balms		
Nano-capsule	UV filters	The active ingredient is shielded from potentially hazardous external influences	[50]
			[52]
Fullerenes	Sunscreen	Antioxidant activity	[55–57]
	Antiaging creams	Penetration in the skin	
Fullerenes	Anti-wrinkle creams	Able to transport biomolecules	
	Eye gels	Anti-radical oxygen species (ROS) scavenging abilities	
	Moisturizer		

Nanocrystals		Increased membrane penetration	
	Toothpaste	Greater adhesion	[60]
	Anti-aging cream	A higher concentration of the active ingredients	[32]
	Sun protection cream	synthesized	[61]
		Strongest antioxidant (neutralizing) activity	

The use of nanoparticles in the cosmetic sector aims for long-lasting advantages and improved stability. The extensive surfaces of nanomaterials make it possible to transfer ingredients through the skin more effectively [28,51]. The stiffness, hydrophobicity, size, charge, and other physicochemical properties of the nanocarriers have an impact on how well they penetrate the skin. By lowering the dose of medications supplied, the using nanoscaled carriers for medication delivery is anticipated to boost therapeutic specificity and decrease side effects [38,68].

In comparison to their parent or bigger size equivalents, nanoscale particles are distinct regarding hue, consistency of the structure, optical activity, transparency, chemical reactivity, and solubility. For instance, the size-matching properties of nanoscale materials with the biological architecture of skin cells provide easier contact, improved solubility, and the selective control of cellular activities at their naturally occurring scale [4]. Cosmetics made with these nanoparticles have enhanced skin penetration, longer-lasting benefits, and superior UV protection [1,3].

Sivanskar and Kumar attempted to calculate the proportion of a spherical micrometer-sized particle that was shrunk to nanometer size and had more surface area [4]. Increased surface area improves dispersibility (sedimentation rate is reduced to nearly zero) and dissolution rate of drug or cosmetic ingredients. Because nanoscale materials have a bigger surface area and more surface imperfections than bulk materials, more contact points can support van der Waals attraction, which improves adhesion. A better cosmetic outcome will be obtained with improved skin adherence. The surface area has a greater impact on particle reactivity. Different bioactivity could be produced by these distinctive chemical characteristics and may aid in the prediction of potential biological responses obtained from nanomaterials used in cosmetics [69].

Nanomaterials' optical transparency and activity are advantageous for cosmetic items. This is particularly obvious in numerous lotions and sunscreens. Titanium oxide and zinc oxide are the active chemicals in sunscreen. Their bigger size particles leave a conspicuous white tint on the skin when used, but nanosized particles in comparable products do not, improving the aesthetics of the nanoproduct [70].

Even materials with a high solid density that is less than a nanometer can be suspended in a liquid without settling because of Brownian motion and form well-dispersed systems. As a result, cosmetics containing nanoscale ingredients will remain suspended for a longer duration than those containing microscale ingredients. This type of nanosized skin preparation has a longer shelf life as a result of this trait since unstable characteristics like creaming, cracking, Ostwald ripening or phase inversion take longer to observe or manifest. Therefore, it should not be shocking that there is a strong desire to acquire and utilize available nanomaterials in the manufacture of cosmetics. The reactivity of materials with nanoscale surface areas is increased because there are more active sites for chemical reactions [31].

The color cosmetics business was one of the most passionate early users of nanotechnology. Nano-sized materials frequently have different chemical or physical properties from their larger equivalents because of their small dimensions and extraordinarily high surface area-to-volume ratio such as increased unfavorable biological activity. This is one of the reasons why nano-scale materials are already becoming extremely prevalent in the personal care industry. Increased effectiveness, transparency, distinctive consistency, preservation of bioactive substances, and improved attentiveness from customers are a few potential advantages of adding nanoparticles to cosmetics. When viewed at a macroscale, larger particles like Zinc oxide and Titanium dioxide are both white



and impenetrable, however, when observed at a nanometer scale, they are translucent. This makes it possible for them to be used in moisturizers and foundation. Wrinkles can be covered by the "soft focus" effect created by aluminum oxide and other nanoparticles. These components may be found in expensive face powders, foundations, and concealer sticks [5].

As cosmetic items, moisturizers were developed to help cure skin dehydration, which showed up as flaking, scaling, and drying of the skin's surface. Humectants, which are often found in moisturizers, help the skin's surface retain moisture, giving it a smooth, fresh appearance. When the skin is hydrated and supple, atopic dermatitis and pruritus can be avoided and controlled. To increase solubility and add sparkle, cosmetic manufacturers started employing nanoscale materials (like liposomes) as envelopes or carriers for cosmetic chemicals. One such component in cosmetics is vitamin E.

These products' particular benefits are supposed to counteract the problems that cause aging, providing firmness and suppleness to aging skin. The triceramide nano-capsules in Lancôme's Hydrazen cream are said to protect skin from daily stress over the long run while regaining the skin's ideal comfort and softness. Nanosized UV filters and antioxidants are utilized in Caudalie's Vinosun Anti-Aging Suncare and L'Oreal's Plentitude Revitalift, an anti-wrinkle cream that also contains nanoparticles, to regenerate aging skin [31].

The release of silver ions from silver nanoparticles may be the cause of their antibacterial activity, according to published literature, and comparable studies on nanosilver and its derivatives have been carried out extensively to take advantage of its special antibacterial and antifungal capabilities [71,72]. However, because of their special capabilities for loading and unloading medications as well as their simplicity in production, gold nanoparticles have potential use in cosmetics. They can be conjugated with chemicals from cosmetic formulations to raise the caliber of the final product because they are readily functionalized, often via thiol linkages. According to studies, toothpaste, and other commercially available personal care products now contain nanogold to generate excellent oral cleansing [16,31].

As their names suggest, UV filters and sunscreens shield the skin from the sun's damaging ultraviolet rays. In UV filters, the two main materials used as nanoparticles are zinc oxide (ZnO) and titanium dioxide (TiO). Even though certain organic substitutes (such as those produced by ivy plants) are being investigated, the nanoparticles of these two oxides have been widely used in sunscreens to prevent UV damage to the skin. They reflect UV-A and UV-B radiation while more effectively absorbing UV light than their bigger particle-sized competitors as a unique quality. TiO nanoparticle-based sunscreen formulations have fewer oily, translucent, pungent, and visually attractive characteristics. They also don't leave behind the same white residue on the skin as their counterparts with bigger particle sizes do, which is chalky in appearance. These ivy nanoparticles protect UV rays four times better than metallic oxide nanoparticles, according to studies. Sunforgettable powder by Colorescience, which contains titanium dioxide nanoparticles, is a nice illustration [31].

Broad-spectrum antibacterial action is present in silver nanoparticles, which is especially effective against bacteria. Silver nanoparticles are believed to be especially efficient for skin protection and as an antiseptic, in organic Korean soap and hand sanitizer. It is asserted that even Evolut is hypoallergenic and increases resistance to airborne diseases [31].

A unique set of multifunctional features, including a high surface-to-volume ratio, stability, catalytic performance, electromagnetic properties, and biological activities, are provided by effective nanoparticle deployment. The properties of nanoparticles described above, in particular, allow for boosting the comprehensive functionality of the product of interest [30]. To capitalize on the benefits of activities involving form and size, cosmetics are frequently made with nanoparticles of various morphologies and chemical contents [73,74], which can improve product performance. Due to their capacity to deflect and refract UV rays, many different forms of inorganic oxide-based nanoparticles, including TiO<sub>2</sub>, ZrO<sub>2</sub>, ZnO, and CeO<sub>2</sub>, are utilized as physical UV filters in sunscreen preparations as opposed to UV absorbers. Due to the UV radiation attenuation capabilities of these nanostructured materials, their resistance to UV light is increased [19,75].

Recent findings, Haddada et al. examined the safety of gold nanoparticles as a cosmetic additive by evaluating their antioxidant and dermoprotective effects [76]. Because they are inert, non-cytotoxic, biocompatible, and extremely stable, gold nanoparticles are remarkable for these qualities. Gold nanoparticles have grown in popularity because of their effective antibacterial and antifungal capabilities. Due to their effective antibacterial and antifungal qualities, gold nanoparticles have become more popular. These nanoparticles are found in a variety of cosmeceutical treatments, such as face packs, deodorants, creams, lotions, and anti-aging creams. The fact that lipid nanoparticles are made from disposable and physiological lipids makes them a "nanoscale" carrier technique with low toxicity/cytotoxicity and notable tolerance [46].

Lipid nanoparticles can also increase the chemical stability of materials that are sensitive to light, degradation, and hydrolysis. Through inclusion into the lipid nanoparticle drug delivery system, many cosmetic ingredients, including Coenzyme Q10, vitamin E, ascorbyl palmitate, and vitamin A, have increased their chemical stability [77]. Intrinsic viscosity is a crucial dendrimer characteristic that makes them valuable in cosmetic formulations. L'Oreal has combined film-forming polymers with terminal hydroxyl functionalized polyester dendrimers in cosmetic formulations for skin applications. The potency of many L'Oreal cosmetics products has grown due to the introduction of dendrimers [19,78].

TiO<sub>2</sub> and ZnO nanoparticles meet consumer needs better than micron-sized particles because they produce a translucent effect by reflecting only a small amount of the light particles that are incident [79,80]. ZnO and TiO<sub>2</sub> nanoparticles as small as 20 nm are also widely used in sunscreens as UV filters. They have superior dispersion and produce a more attractive cosmetic outcome [51]. The primary benefit of nanoparticles is that they release the active component in the outermost skin layers, guaranteeing that substantial concentrations of this chemical enter the epidermis [20,81].

For cellular distribution, inorganic nanoparticles are well suited due to their vast availability, rich functionality, strong biocompatibility, possibility for targeted administration, and regulated drug administration [58]. These are effective for the transdermal distribution of chemicals as well as for the dermatological treatment of disorders like vitiligo and skin cancer. They are also used in the cosmetics sector for therapies for both acne and aging, as well as for hydration and skin care products [38].

Due to their hydrophilic surface, which encourages longer circulation, and their low production cost, silica nanoparticles have caught the attention of the cosmetic industry [82]. The effectiveness, smoothness, and shelf life of cosmetic products are all improved by the use of nano-silica. It functions as an anti-caking agent and enhances absorbency [51].

Nanometer-sized solid lipid nanoparticles (SLNs) have a solid lipid matrix that maintains its form at body temperature [83], which preserves its structure at body temperature. SLNs feature an oily or lipid core and a single layer of shells. Since SLNs are tiny, they come into close contact with the stratum corneum, allowing for greater ingredient penetration into the skin [46]. They can aid in boosting the water content of the skin while also acting as potential UV blockers. Even though nanostructured lipid carriers (NLCs) can carry more active substances, SLNs can increase chemical stability. And they are easily scalable, and their production methods are well-established. Also, they improve the ability to penetrate the skin, to be biocompatible, and to be stable as a carrier delivery agent [22]. It is possible to produce SLNs and NLCs both in the lab and on a large scale, and they are highly tolerated carrier systems for dermal applications [46].

As a result of their tiny size and low-toxicity physiological and disposable lipid composition, they remain on the skin's surface and facilitate the dispersion of different compounds within the body, SLNs are widely used in cosmetics. SLNs also have occlusive properties that contribute to increased skin hydration [8,46].

The more recent nanoscale materials NLCs and SLNs distribute and stabilize more effectively than liposomes. Because of their high bioavailability and controlled occlusion when used in moisturizers, the skin is better hydrated. Nanogold is also said to have healing and anti-oxidant properties and is used in one moisturizer available in the UK. A moisturizer branded Hydra Flash

Bronzer Daily Face from the cosmetics company Lancôme claims to provide customers with a natural, glowing complexion because it contains nanocapsules of vitamin E [31].

The capacity to prevent encapsulated chemicals from degrading, controlled release, and improved penetration through the stratum corneum are only a few benefits of using these nanomaterials in cosmetic products (coenzyme Q10 and retinol) [83,84]. Because of their occlusive properties, they also increase skin hydration [29].

For dermal application, NLC and SLN both have many benefits. They are colloidal carriers that offer a variety of chemical-regulated release characteristics. Due to its diminutive size, which ensures direct contact with the stratum corneum and could boost the amount of medication absorbed by the skin. Skin hydration rises as a result of the occlusive features of lipid nanoparticles. Furthermore, materials that are susceptible to oxidation, UV, and hydrolysis can have their chemical stability increased by the addition of lipid nanoparticles [46].

Labile Active Pharmaceutical Ingredients can be protected from hydrolysis and oxidation by the solid matrix of SLNs. This is important for anti-aging and minor acne topical agents. Comparing SLN to an aqueous dispersion, tocopherol, retinol, and coenzyme Q10's chemical stability is increased by 57% [85] and tocopherol by 57%. [21].

SLNs have several advantageous properties, including: a) the existence of biodegradable, low-toxic, physiological lipids b) Obstructive characteristics that enhance skin moisture levels, and c) greater uptake of active substances due to small size-like properties. Because of these properties, they have become popular in cosmetics [46,86].

Skin thinning, loss of suppleness, dryness, wrinkles, the emergence of spots, and the loss of the skin's barrier function are all signs of aging skin. Accelerated aging has been associated with exposure to chemical contaminants, UV and infrared radiation, abrasion, and stress. Skin regeneration and replenishment, on the other hand, are dependent on the level of skin's collagen quality. Certain skin care products contain proteins made from progenitor cells that are wrapped in nanoparticles called liposomes that also contain anti-aging ingredients. This allows for effective protein delivery [67]. When creating anti-aging cosmetics, some people incorporate retinoids and botulinum toxins into nanoscale materials to promote skin renewal.

Encapsulation with liposomes (some manufacturers call them "nanosomes") preserves the medication against metabolic deterioration and allows for the controlled release of its bioactive constituents [87]. These are appropriate for delivering pharmacologically active substances with both hydrophobic and hydrophilic characteristics. Their sizes range between 20 nanometers and many micrometers, which determines how effective they are at targeting, and they may have a unilamellar or multilamellar structure [42]. Antioxidants like lycopene or carotenoids can be added to liposomes to increase their physical and chemical stability in water [19]. Cosmetics containing liposomes have a high substantivity, making them difficult to wash away. Liposomes, in particular, can increase the lipid content of the stratum corneum, increasing moisturization and decreasing skin dryness [20,81].

Liposomes are widely used in the cosmetic industry for a variety of reasons, including their ease of preparation, safety, structural similarity to the skin, biocompatibility, the capacity to enhance active component penetration through the skin, and the viability of directing the entrapped chemicals to particular skin layers while the skin moisturizing and restorative benefits of their inherent lipids and limiting negative effects caused by systemic absorption. Furthermore, liposomes may establish an active chemical reservoir in the skin and its appendages, providing a sustained release that may be effective in extending the effects of active compounds [55].

Several scientists hypothesized that making liposomes more elastic would enhance medication absorption through the skin. In addition, leakage-resistant flexible liposomes were developed to address the stiffness and stability issues that are common with traditional liposomes [32]. The cream Capture, introduced by Dior in 1986, was the first cosmetic product to use liposomes [3]. The utilization of liposomes is increasing due to their simplicity in manufacture and capacity to boost the skin's ability to absorb bioactive components, despite their instability and also the requirement for antioxidants, cryoprotectants, and other additions [29].

Liposomes are appropriate for skin care applications because of their ease of manufacture, improved absorption of active compounds via the skin, and protracted delivery of chemicals into cells [3]. The distribution of both hydrophobic and hydrophilic substances is possible with the help of liposomes, which are non-hazardous, biocompatible, and able to easily encapsulate active ingredients. Both hydrophilic and hydrophobic substance transport can be made more appropriate with the help of liposomes. And increased concentrations of drug products are possible with liposomes, by improving their absorption by the skin [6].

To improve penetration through the skin barrier, proteins are mixed with nanoliposomes and nanocapsule particles for usage in cosmetic applications [88]. Because of their water-containing structure, nanoliposome particles can moisturize skin; after liposomes penetrate the skin's stratum corneum layer, and the liposomes' inner water core serves as a source of hydration for the skin. [48].

Liposomes are relatively small spheres having an outer shell comprised of both hydrophilic and lipophilic materials. They mostly consist of water and active substances that are soluble in water, such as vitamins. They are minuscule (less than 1/10,000 mm) and have a cell-like exterior structure, which allows them to penetrate the skin [89].

Typically, liposomes have a size range of 20 nanometers to several hundred microns. These are essentially spherical vesicles that have a phospholipid bilayer trapping some of the solvents. They are appropriate for the administration of both hydrophilic and hydrophobic substances due to their capacity to shield the drug from the outside environment. Due to its softening and conditioning qualities, phosphatidylcholine, one of the liposome's essential components, has been found in a variety of skin care formulas and hair care products [60]. Due to the biocompatibility, biodegradability, and nontoxicity of liposomes, as well as the ease with which they encapsulate the active component, liposomes are employed in several cosmeceuticals [60,90].

Nanoemulsions have desirable attributes such as a broad excellent solubilization capacity, high kinetic stability, interfacial area, and low viscosity [91]. Smaller-sized particles of nanoemulsions promote applicability and stability for carrying active ingredients; they also boost the longevity of the product's shelf life [40,92]. These are widely used as a delivery medium for a variety of cosmetic products, including nail polish, lotions, shampoos, conditioners, sunscreens, deodorants, and hair serums [93].

Because of their interior lipophilic, nanoemulsions are better suited for transporting lipophilic compounds than liposomes. They, like liposomes, help active ingredients penetrate the skin and consequently boost their skin concentration. The high surface area of the little droplet, which enables efficient active transport to the skin, is another benefit [27].

The following characteristics explain why a nanoemulsion is superior to a macroemulsion broad surface area, enhanced inclusiveness, skin film generation, excellent stability, modified release and drug-delivery capacities, attractive visual character, and skin feel [94]. Liposomes are less stable than nanoemulsions, and occasionally a lamellar liquid-crystalline phase might develop surrounding the droplets [37,95].

Nanoemulsions in cosmeceutical products allow components to penetrate the skin quickly. As a result of the tiny droplet size, the potential benefits of using nanoemulsions in cosmetic products include (i) strong occlusive action of keeping skin hydrated, (ii) rapid skin penetration of active ingredients, (iii) visual aspects and skin with a gleaming sheen, (iv) excessive fluidity without gelation, and (v) enhanced diffusion into small gaps like hair scale spacings and pilosebaceous follicles [96].

Active chemicals can swiftly infiltrate the skin thanks to the nanoemulsion formulation's enormous surface area of the droplets. Nanoemulsions have even been found to be easily able to penetrate tough skin. Because of this nanoemulsion feature, it is no longer necessary to use a particular penetration enhancer, which is what causes formulation incompatibility [93].

In recent years, nanoemulsions have become more well-known as prospective delivery systems for cosmetics and as a means of improving the distribution of active ingredients in certain skin layers. Transporting lipophilic compounds is better suited with nanoemulsions than liposomes due to their



lipophilic interior. They increase the concentration of active chemicals in the skin by facilitating their absorption into the skin, similar to liposomes [27,93].

High fluidity, low viscosity, homogeneity, high solubilization capacity, low sedimentation, and thermal stability are characteristics of nanoemulsions [97]. Inserting chemicals that are physiologically active into them is relatively simple. This method is preferred due to the improvement in the efficacy of the components in nanoemulsions. They have been used in skin care products for aged skin due to their properties [98].

The enhanced methods for dermal creams and gels to penetrate the skin are being provided by nano-based compositions. It may be possible for dendrimers to successfully distribute dermal formulations via the skin [28,65].

The dendrimer structure has assisted in increasing resveratrol's systemic absorption and skin absorption (It is well-known for its antioxidant and anti-aging qualities.) [99], resulting in the subsequent scaling up and commercialization of this product with a dendrimer structure [51]. Dendrimers have the potential to improve bioavailability and drug solubility because of the possibility that molecules could be trapped by their hyper-branched structure and molecules that attach to their surface. The main factor driving dendrimers' strong demand in medication delivery systems and product development is due to their qualities [65].

Carbosiloxane dendrimer, according to Furukawa et al., can give the skin a healthy quantity of glossiness and sebum, as well as sensory perception, water repellency, and adhering characteristics [100]. Dendrimers' intrinsic viscosity is a crucial aspect that might accentuate them as a significant benefit for cosmetic innovators. And because of the nonlinear relationship between dendrimer molecular weight and inherent viscosity [65]. Dendrimers cover a significant portion of the cosmeceutical fields [8].

Although they are formed of artificial, non-ionic surfactants, niosomes are shaped similarly to liposomes [101]. Lancome introduced the first Niosome product to the market in 1987. Some of the benefits of using niosomes in cosmetics include their ability to improve the incorporated active ingredient's stability and raise the rate of skin absorption [29].

Niosomes can transport substances that are both hydrophilic and hydrophobic. Niosomes can be used as a novel medication administration system for poorly absorbed medicines [102]. Because they encapsulate the drug, niosomes can be used as a vehicle for poorly absorbable drugs [102]. It encapsulates the drug, extending its time in the systemic circulation and increasing entry into the target tissue. Niosomes eliminate the problems of liposomes, such as inconsistency, expensive demand, and vulnerability to oxidation [42,103].

Cubosomes have a substantial surface area, a low viscosity, and the ability to subsist with virtually any level of dilution. They are very thermostable and are capable of carrying both hydrophobic and hydrophilic compounds [3].

Because of its tiny pore size (5–10 nm), ability to hydrolyze hydrophilic, hydrophobic, and amphiphilic components, and biodegradability by simple enzyme activity, the cubic phase of cubosomes is appealing for controlled release. The cubic phase, which is exceptionally bioadhesive, is thought to be a skin penetration booster because of its exceptional tolerance to topical and mucosal accumulation and active ingredient administration [67].

Depending on whether or not their surfaces have a formal charge, nanocapsules are categorized as ionic or non-ionic. The inclusion of charge can boost the hydrolysis pressure at the surface of nanocapsules, encouraging repulsion among suspended particles and decreasing cluster formation [26,104].

The use of nanocapsules has the advantage of the targeted tissue or cells being delivered and releasing active substances under controlled conditions. As opposed to that, applying too many direct application of biologically active substances to the skin may impair the effectiveness of the medicine or cosmetic product. The active ingredient is shielded from potentially hazardous external influences like moisture or oxygen thanks to this nanoformulation, which is still another benefit [98,105].

Nanocrystals have higher kinetic saturation solubility due to their nano-dimension size, which, when combined with the large surface area, results in rapid dissolution. For rutin nanocrystals developed for oral administration, these effects have already been described [62,106].

Lipid particles provide an adhesion that covers the skin surface and prevents water from evaporating from the lipid nanodispersion that has been applied to it. As a result of decreased corneocyte packing and increased inter-corneocyte gaps, the stratum corneum's moisture may rise, enabling medication penetration into deeper skin layers [85,107].

The superficial connections of corneocyte clusters and the furrows between corneocyte islands can be closely contacted by small particles, facilitating sustained drug release over several hours [108]. While this is also true for liposomes, they differ in that they fall apart, which is thought to compromise percutaneous penetration [107]. Because of their strong adhesive properties, the application site's SLN and NLC should endure longer. Adhesion increases as particle size decreases. Furthermore, in the lipid matrix of the carrier, the medicine is dissolved or finely disseminated, or it sticks to the surface of the carrier, allowing contact with the outermost skin layers [21].

Chemical-specific receptors are also attached to nanocarriers, allowing them to reach any desired location in the body [101]. This increases the effectiveness of the active ingredients while decreasing the possibility of side effects [109]. Active ingredients like hyaluronic acid, antioxidants, vitamins, and different types of peptides are frequently transferred via nanocarriers in moisturizing lotions, nutrient preparations, and sunscreens [88,98].

NanoCarriers are particularly advantageous as cosmetic systems because they can improve cosmetic product delivery perceived or measured performance. Because NCs have numerous benefits over conventional topical formulations, such as improved active chemical stability and water solubility, greater bioavailability targeting specific skin layers, and so on, these carriers may help boost anti-oxidant topical efficiency. In particular, liposomes, niosomes, solid lipid nanoparticles, and so forth [55].

Natural inertness, extreme stability, biocompatibility, and noncytotoxicity characterize gold nanoparticles. After membrane staining, Nanogold is extremely stable in liquid or dried form and does not fade; it is also offered in conjugated and unconjugated forms [110]. Their small size, enormous surface area, shape, and crystallinity make them easy to move into the target cell and provide them with a high drug-loading capacity [111].

UV radiation can be reflected, absorbed, or dispersed by nanoparticles of compounds such as zinc oxide (ZnO) and titanium dioxide (TiO<sub>2</sub>). According to reports, nanoparticles can reach the tops of human hair follicles or the Horny layer, but they are incapable of passing through intact skin and reaching the critical epidermal layers [112,113]. Liposomes and SLNs, for example, have been used as penetration enhancers in various sunscreen formulations [114,115].

When compared to microparticles of the same chemical, nanomaterials may have different biological characteristics since a considerable portion of their atoms are on the surface of the particle. These distinct chemical properties may result in distinctive bioactivity [69]. Therefore, it is crucial to comprehend which chemical characteristics may be crucial for foretelling a biological response to a nanomaterial [1].

## 6. Conclusions

Given that nanotechnology has the potential to benefit cosmetics and personal care goods, cosmetic companies use nanoscale components to improve the performance of their products. A variety of skin care products now contain nanomaterials to benefit from the special characteristics of matter at the nanoscale. The application of nanotechnology to medicine, particularly more specifically to the administration of drugs, is expected to grow quickly. Pharmaceutical sciences have used nanoparticles to lessen the toxicity and adverse effects of medications for many years. To improve the transport of cosmetic components into the skin, researchers and manufacturers frequently cite this as a possible justification for the rising interest in and usage of nanomaterials in cosmetics. This review article places a strong emphasis on reason and the function of the features of nanomaterials on skincare as they are viewed.

**Author Contributions:** Nimasha Lakshini Rathnasinghe: Writing - original draft, review & editing, Kotuwegoda Guruge Kaushani: Writing - review & editing, B.P.S. Rajapakshe: Writing - review & editing, Awanthi De Silva: Supervision, R.A. Jayasinghe: Supervision, A.H.L.R. Nilmini: Supervision, Nadeeka .D. Tissera: Supervision, Ruchira N. Wijesena: Supervision, Gayan Priyadarshana: Supervision

**Funding:** This research received no external funding.

**Institutional Review Board Statement:** Not applicable.

**Informed Consent Statement:** Not applicable.

**Data Availability Statement:** The processed data required to reproduce these findings cannot be shared at this time due to legal or ethical reasons. The processed data required to reproduce these findings cannot be shared at this time due to technical or time limitations. The processed data required to reproduce these findings cannot be shared at this time as the data also forms part of an ongoing study.

**Acknowledgments:** This review is based on the study that was supported by the Faculty of Technology, Faculty of Graduate Studies, and University Research Grants [Grant No. ASP/01/RE/TEC/2022/62], University of Sri Jayewardenepura, Pitipana, Homagama, Sri Lanka.

**Conflicts of Interest:** The authors declare no conflict of interest.

## References

- Katz, L. M.; Dewan, K.; and Bronaugh, R. L. Nanotechnology in cosmetics. *Food Chem. Toxicol.* **2015**, doi: 10.1016/j.fct.2015.06.020.
- Yadwade, R.; Gharpure, S.; and Ankamwar, B. Nanotechnology in cosmetics pros and cons. *Nano Express* **2021**, vol. 2, no. 2, doi: 10.1088/2632-959X/abf46b.
- Raj, S.; Jose, S.; and Sabitha, M. Nanotechnology in cosmetics : Opportunities and challenges. **2012**, vol. 4, no. 3, doi: 10.4103/0975-7406.99016.
- Sivasankar, M.; and Kumar, B. P. Role of Nanoparticles in Drug Delivery System. **2010**, vol. 1, no. 2, pp. 41–66.
- Taylor, P.; Singh, P.; and Nanda, A. Toxicological & Environmental Chemistry Nanotechnology in cosmetics. **2012**, November 2014, pp. 37–41, doi: 10.1080/02772248.2012.723482.
- Hameed, A.; Fatima, G.R.; Malik, K.; Muqadas, A.; and Fazal-ur-Rehman, M. Scope of Nanotechnology in Cosmetics. *Dermatology and Skin Care Products* **2019**, no. September 2018, doi: 10.26655/jmchemsci.2019.6.2.
- Miyazaki, K.; and N. I. Å. Nanotechnology systems of innovation — An analysis of industry and academia research activities. **2007**, vol. 27, pp. 661–675, doi: 10.1016/j.technovation.2007.05.009.
- Gupta, L. R.; and Gupta, K. C. Role of Nanotechnology in Skin Remedies. **2018**, doi: 10.1007/978-981-10-5493-8.
- Robinson, P. R.; and Hsu, C. S. Introduction to petroleum technology. *Springer Handbooks* **2017**, vol. PartF1, pp. 1–83, doi: 10.1007/978-3-319-49347-3\_1.
- Baril, M. B.; Franco, G. F.; Viana, R. S.; and Zanin, S. M. W. Nanotechnology applied to cosmetics. **2012**, pp. 45–54,.
- Triunfo, M.; Tafi, E.; Guarnieri, A.; Salvia, R.; Falabella, P.; Scieuzo, C.; Hahn, T.; and Zibek, S. Insect chitin-based nanomaterials for innovative cosmetics and cosmeceuticals. *Cosmetics* **2021**, vol. 8, no. 2, pp. 1–20, doi: 10.3390/cosmetics8020040.
- Kolahalam, L. A.; Viswanath, I. V. K.; Diwakar, B. S.; Govindh, B.; Reddy, V.; and Murthy, Y. L. N. Materials Today : Proceedings Review on nanomaterials : Synthesis and applications. *Mater. Today Proc.*, **2019**, vol. 18, pp. 2182–2190, doi: 10.1016/j.matpr.2019.07.371.
- Meloa, A.; Amadeua, M.S.; Lancellottia, M.; de Hollandaa, L.M.; and Machado, D. The Role Of Nanomaterials In Cosmetics: National And International Legislative Aspects. **2015**, vol. 38, no. 4, pp. 599–603.
- Nasrollahzadeh, M.; Sajadi, S. M.; Sajjadi, M.; and Issaabadi, Z. An Introduction to Nanotechnology. *Elsevier Ltd.* **2019**, vol. 28.
- Gorai, S. Nanotechnology in Cosmetics. **2014**, vol. 1, no. 3, pp. 1–7,.
- Robertson, T. A.; Sanchez, W. Y.; and Roberts, M. S. Are Commercially Available Nanoparticles Safe When Applied to the Skin ?. **2010**, doi: 10.1166/jbn.2010.1145.
- Kim, J.; Park, S.; Lee, J.E.; Jin, S.M.; Lee, J.H.; Lee, I.S.; Yang, I.; Kim, J.; Kim, S.K.; Cho, M.; and Hyeon, T. Designed Fabrication of Multifunctional Magnetic Gold Nanoshells and Their Application to Magnetic Resonance Imaging and Photothermal Therapy. **2006**, pp. 7918–7922. doi: 10.1002/ange.200602471.
- Aziz,Z.A.; Mohd-Nasir,H.; Setapar,S.H.M.; Peng,W.L.; Chuo,S.C.; Khatoon,A.; Nasir, M.; Ibrahim,M.; Umar,K.; Ahmad,A.; cosmeceutical : Application in makeup and skin care i v o r l a n o i v o l. **2019**, doi: 10.3389/fchem.2019.00739.

19. Bilal, M. New Insights on Unique Features and Role of Nanostructured Materials in Cosmetics. **2020**, pp. 1–16.
20. Salvioni, L.; Morelli, L.; Ochoa, E.; Labra, M.; Fiandra, L.; Palugan, L.; Prosperi, D.; and Colombo, M. The emerging role of nanotechnology in skincare. *Adv. Colloid Interface Sci.* **2021**, vol. 293, p. 102437. doi: 10.1016/j.cis.2021.102437.
21. Schäfer-korting, M.; Mehnert, W.; and Korting, H. Lipid nanoparticles for improved topical application of drugs for skin diseases. **2007**, vol. 59, pp. 427–443. doi: 10.1016/j.addr.2007.04.006.
22. Santos, A.C.; Morais, F.; Simões, A.; Pereira, I.; Sequeira, J.A.D.; Pereira-Silva, M.; Veiga, F.; & Ribeiro, A. Cosmetic formulations Acceptus et. *Expert Opin. Drug Deliv.* **2019**, vol. 0, no. 0, p. 1. doi: 10.1080/17425247.2019.1585426.
23. Kulkamp, I. C. Artigo. **2009**, vol. 32, no. 8, pp. 2078–2084.
24. Morales, C.; Prado, A.; Matos, D.; De Paula, E.; Henrique, A.; and Fernandes, L. Benzocaine loaded biodegradable poly- ( d , l -lactide-co-glycolide ) nanocapsules : factorial design and characterization. **2009**, vol. 165, pp. 243–246. doi: 10.1016/j.mseb.2009.06.011.
25. Guterres, S. S.; Alves, M. P.; and Pohlmann, A. R. Polymeric Nanoparticles , Nanospheres and Nanocapsules , for Cutaneous Applications. **2007**, pp. 147–157. doi: 10.1177/117739280700200002.
26. Poletto, F. S.; Beck, R. C. R.; Guterres, S. S.; and Pohlmann, A. R. Polymeric Nanocapsules : Concepts and Applications. **2011**.
27. Sharma S. ;and Sarangdevot, K. Nanoemulsions For Cosmetics. **2012**, vol. 2, no. 3, pp. 408–415.
28. Ahmad, U. Strategies in Development and Delivery of Nanotechnology Based Cosmetic Products Authors Skin : A Barrier in Cosmetic Domain Understanding the Terms Cosmetics , Concept of Nanotechnology Factors Affecting Percutaneous Drug Absorption. **2018**.
29. Andonova, V.; Penkov, D.; and Katsarov, P. FOR AND AGAINST THE USE OF NANOSTRUCTURES IN COSMETIC. **2013**, no. March 2014.
30. Mihranyan, A.; Ferraz, N.; and Strømme, M. Progress in Materials Science Current status and future prospects of nanotechnology in cosmetics. *Prog. Mater. Sci.* **2012**, vol. 57, no. 5, pp. 875–910. doi: 10.1016/j.pmatsci.2011.10.001.
31. Ekpa, D. ; Ekpa, D.; and Otobong, T. Nanotechnology in Cosmetics : Basics , Current Trends and Safety Concerns — A Review. **2020**, pp. 1–28. doi: 10.4236/anp.2020.91001.
32. Abila, M. J. ; Singh, N. D.; and Banga, A. K. Role of Nanotechnology in Skin Delivery of Drugs. **2016**, doi: 10.1007/978-3-662-47862-2.
33. Mu L.; and Sprando, R. L. Application of nanotechnology in cosmetics. *Pharm. Res.* **2010**, vol. 27, no. 8, pp. 1746–1749. doi: 10.1007/s11095-010-0139-1.
34. Solans, C.; Izquierdo, P.; Nolla, J.; and Azemar, N. Nano-emulsions. **2005** , vol. 10, pp. 102–110. doi: 10.1016/j.cocis.2005.06.004.
35. Cohen, P. R.; and Nasir, A. Nanotechnology and dermatology : Part II — risks of nanotechnology. *Clin. Dermatol.* **2010**, vol. 28, no. 5, pp. 581–588. doi: 10.1016/j.clindermatol.2009.06.006.
36. "WO2006087156A1.pdf." .
37. Yukuyama, M. N.; Ghisleni, D. D. M.; and Pinto, T. J. A. Nanoemulsion : process selection and application in cosmetics – a review. **2016** pp. 13–24. doi: 10.1111/ics.12260.
38. Gupta, S.; Bansal, R.; Gupta, S.; Jindal, N.; and Jindal, A. Nanocarriers and nanoparticles for skin care and dermatological treatments. *Indian Dermatol. Online J.* **2013**, vol. 4, no. 4, p. 267. doi: 10.4103/2229-5178.120635.
39. Mason, T. G.; Wilking, J. N.; Meleson, K.; Chang, C. B.; and Graves, S. M. Nanoemulsions: Formation, structure, and physical properties. *J. Phys. Condens. Matter.* **2006**, vol. 18, no. 41. doi: 10.1088/0953-8984/18/41/R01.
40. Simonnet, J.; and Allore, F. L. Nanoemulsions : a new vehicle for skincare products. **2004**, vol. 109, no. 03, pp. 145–149. doi: 10.1016/S0001-8686(03)00146-5.
41. Otosan, F. Nanoemulsions in Cosmetics. **2014**, no. June.
42. Kaul, S.; Gulati, N.; Verma, D.; Mukherjee, S.; and Nagaich, U. Role of Nanotechnology in Cosmeceuticals: A Review of Recent Advances. *J. Pharm.* **2018**, vol. 2018, pp. 1–19. doi: 10.1155/2018/3420204.
43. Nohynek, G. J. Safety of Nanotechnology in Sunscreens and Personal Care Products. **2011**, vol. 25, pp. 17–25.
44. Abdelwahab, S. Tamoxifen drug loading solid lipid nanoparticles prepared by hot high- pressure homogenization techniques Tamoxifen Drug Loading Solid Lipid Nanoparticles Prepared by Hot High Pressure Homogenization Techniques. **2008**. doi: 10.3844/ajptsp.2008.219.224.
45. "WO1999032076A1.pdf." .
46. Pardeike, J. ; Hommoss, A.; and Müller, R. H. Lipid nanoparticles (SLN , NLC) in cosmetic and pharmaceutical dermal products. **2009**, vol. 366, pp. 170–184. doi: 10.1016/j.ijpharm.2008.10.003.
47. Villalobos, R. Sun protection enhancement of titanium dioxide crystals by the use of carnauba wax nanoparticles : The synergistic interaction between organic and inorganic sunscreens at nanoscale. **2006**, vol. 322, pp. 161–170. doi: 10.1016/j.ijpharm.2006.05.037.



48. Abdullaeva, Z. Nanomaterials in daily life: Compounds, synthesis, processing and commercialization. *Nanomater. Dly. Life Compd. Synth. Process. Commer.* **2017**, pp. 1–149. doi: 10.1007/978-3-319-57216-1.
49. Teerasumran, P.; Velliou, E.; Bai, S.; and Cai, Q. Deodorants and antiperspirants: New trends in their active agents and testing methods. *Int. J. Cosmet. Sci.* **2023**, vol. 45, no. 4, pp. 426–443. doi: 10.1111/ics.12852.
50. Ku, I. C.; and Jose, A. Influence of nanoencapsulation on the sensory properties of cosmetic formulations containing lipoic acid. **2013**, pp. 105–111. doi: 10.1111/ics.12013.
51. Fytianos, G.; Rahdar, A.; and Kyzas, G. Z. Nanomaterials in cosmetics: Recent updates. *Nanomaterials.* **2020**, vol. 10, no. 5, pp. 1–16. doi: 10.3390/nano10050979.
52. Vettor, M.; Bourgeois, S.; Fessi, H.; Pelletier, J.; Perugini, P.; Pavanetto, F. and Bolzinger, M. A. "Skin absorption studies of octyl-methoxycinnamate loaded poly (D, L-lactide) nanoparticles : Estimation of the UV filter distribution and release behaviour in skin layers," **2010**, vol. 27, no. 3, pp. 253–262. doi: 10.3109/10717540903097770.
53. Shin, J.; Shin, K.; Lee, H.; Nam, J.; Jung, J.; Ryu, J.; Han, J.; Suh, K.; Kim, Y. J.; Shim, J.; Kim, J.; Han, S.; Char, K.; Kim, Y. K.; Chung, J. H.; Lee, M. J.; Kang, B. C. and Kim, J. Non-invasive Transdermal Delivery Route Using Electrostatically Interactive Biocompatible Nanocapsules. **2010**, pp. 739–743 doi: 10.1002/adma.200902079.
54. Barre, G. Biodegradable polymer nanocapsules containing a sunscreen agent: preparation and photoprotection. **2011**, vol. 52, pp. 191–195.
55. Montenegro, L. Nanocarriers for skin delivery of cosmetic antioxidants. **2014**.
56. Zhou, Z. Liposome Formulation of Fullerene-Based Molecular Diagnostic and Therapeutic Agents. **2013**, pp. 525–541. doi: 10.3390/pharmaceutics5040525.
57. Lens, M. Use of Fullerenes in Cosmetics. **2009**, pp. 118–123.
58. Ping, Z.; Hua, Q.; Qing, G.; and Bing, A. Inorganic nanoparticles as carriers for efficient cellular delivery. **2006**, vol. 61, pp. 1027–1040. doi: 10.1016/j.ces.2005.06.019.
59. Fumelli, C.; Marconi, A.; Salvioli, S.; Straface, E.; Malorni,.; Ofdani, A. M.; Pellicciari, R.; Schettini, G.; Giannetti, A.; Monti, D.; Franceschi, C.; and Pincelli, C. Carboxyfullerenes Protect Human Keratinocytes from Ultraviolet-B-Induced Apoptosis. **2000**, pp. 835–841.
60. Arif, T. Nanomedicine & Biotherapeutic Discovery Therapeutic and Diagnostic Applications of Nanotechnology in Dermatology and Cosmetics. **2015**, no. August, doi: 10.4172/2155-983X.1000134.
61. Petersen, R. NANOCRYSTALS FOR USE IN TOPICAL COSMETIC FORMULATIONS AND METHOD OF PRODUCTION THEREOF. **2015**, vol. 2, no. 12.
62. Pyo, S. M.; Meinke, M.; and Keck, C. M. Rutin — Increased Antioxidant Activity and Skin Penetration by Nanocrystal Technology. **2015**. doi: 10.3390/cosmetics3010009.
63. Johnston, J. H.; Burridge, K. A.; Kelly, F. M.; and Small, A. C. Nanogold and Nanosilver Wool : New Products for High Value Fashion Apparel and Functional Textiles Nanogold and Nanosilver Wool : New Products for High Value Fashion Apparel and Functional Textiles. **2015**, no. March.
64. Demming, A.; Brongersma, M.; Kim, D. S.; Demming, A.; and Demming, A. Nanotechnology under the skin. **2011**, pp. 9–11. doi: 10.1088/0957-4484/22/26/260201.
65. Chauhan, A.; Patil, C.; Jain, P.; and Kulhari, H. 14 - Dendrimer-based marketed formulations and miscellaneous applications in cosmetics, veterinary, and agriculture. *Elsevier Inc.* **2020**.
66. Visscher, M. O.; and Spicer, P. Bicontinuous cubic liquid crystalline phase and cubosome personal care delivery systems. **2003**.
67. Garg, G.; Araf, S. S.; and Araf, S. S. Cubosomes : An Overview. **2007**, vol. 30, no. 2, pp. 350–353.
68. Ulbrich, W.; and Lamprecht, A. Targeted drug-delivery approaches by nanoparticulate carriers in the therapy of inflammatory diseases. **2010**, no. November 2009.
69. Castranova, V. Overview of Current Toxicological Knowledge of Engineered Nanoparticles CHARACTERISTICS AND BIOACTIVITY. **2011**, vol. 53, no. 6, pp. 14–17. doi: 10.1097/JOM.0b013e31821b1e5a.
70. Hilton, L. Cosmetic Dermatology, Aesthetic Technology. **2021**.
71. Gajbhiye, S.; and Sakharwade, S. Silver Nanoparticles in Cosmetics 2 . Mechanism of Action of Silver Nanoparticles. Surface Area of Nanoparticles. **2016**, pp. 1–18. doi: 10.4236/jcdsa.2016.61007
72. Mukherji, S.; Ruparelia, J.; and Agnihotri, S. Antimicrobial Activity of Silver and Copper Nanoparticles : Variation in Sensitivity Across Various Strains of Bacteria and Fungi. **2012**, pp. 225–251. doi: 10.1007/978-3-642-24428-5.
73. Albanese, A.; Tang, P. S.; and Chan, W. C. W. The Effect of Nanoparticle Size , Shape , and Surface Chemistry on Biological Systems. **2012**, doi: 10.1146/annurev-bioeng-071811-150124.
74. Burda, C.; Chen, X.; Narayanan, R.; and El-sayed, M. A. Chemistry and Properties of Nanocrystals of Different Shapes. **2005**.
75. Dransfield, G. P. Inorganic sunscreens. **2000**, vol. 91, pp. 271–273.
76. Haddadaa, M. B.; Geromettaa, E.; Chawecha, R.; Sorresa, J.; Bialeckic, A.; Pesnela, S.; Spadavecchiab, J.; and Morel, A. Assessment of antioxidant and dermoprotective activities of gold nanoparticles as safe cosmetic

- ingredient. *Colloids Surfaces B Biointerfaces*. **2020**, vol. 189, no. July 2019, p. 110855. doi: 10.1016/j.colsurfb.2020.110855.
77. Radtke, M.; and Wissing, S. A. Solid lipid nanoparticles (SLN ) and nanostructured lipid carriers ( NLC ) in cosmetic and dermatological preparations. **2002**, vol. 1, pp. 131–155.
  78. Lohani, A.; Verma, A.; Joshi, H.; Yadav, N.; and Karki, N. Nanotechnology-Based Cosmeceuticals. **2018**, vol. 2014.
  79. Schneider, S. L.; and Lim, H. W. A review of inorganic UV filters zinc oxide and titanium dioxide. **2018**, no. June 2018, pp. 442–446. doi: 10.1111/phpp.12439.
  80. Salvioni, L.; Galbiati, E.; Collico, V.; Alessio, G.; Avvakumova, S.; Corsi, F.; Tortor, P.; Prosperi, D.; Colombo, M. Negatively charged silver nanoparticles with potent antibacterial activity and reduced toxicity for pharmaceutical preparations. **2017**, pp. 2517–2530.
  81. Betz, G.; Aeppli, A.; Menshutina, N.; and Leuenberger, H. In vivo comparison of various liposome formulations for cosmetic application. **2005**, vol. 296, pp. 44–54. doi: 10.1016/j.ijpharm.2005.02.032.
  82. Humbert, P. Agache ' s Measuring the Skin. **2017**.
  83. Gohla, S. H.; Jennings, V.; Gysler, A.; and Scha, A. Vitamin A loaded solid lipid nanoparticles for topical use : occlusive properties and drug targeting to the upper skin. **2000**, vol. 49.
  84. Wissing, S. A.; and Müller, R. H. Cosmetic applications for solid lipid nanoparticles (SLN ). **2003**, vol. 254, pp. 65–68. doi: 10.1016/S0378-5173(02)00684-1.
  85. Wissing, S. A.; R. H. Mu, R. H. ; Manthei, L.; and Mayer, C. Structural Characterization of Q10-Loaded Solid Lipid Nanoparticles by NMR spectroscopy. **2004**, vol. 21, no. 3, pp. 400–405.
  86. Müller, R. H.; Maeder, K.; Gohla, S.; Solid lipid nanoparticles (SLN) for controlled drug delivery - a review of the state of the art. *Elsevier*. **2000**, vol. 50, no. 2314, pp. 1–63.
  87. Hope, C. N.; and Kitson, M. J. Liposomes: A perspective for dermatologists. **1993**.
  88. Desai, P.; Patlolla, R. R. ; and Singh, M. Interaction of nanoparticles and cell-penetrating peptides with skin for transdermal drug delivery. *Mol. Membr. Biol.* **2010**, vol. 27, no. 7, pp. 247–259. doi: 10.3109/09687688.2010.522203.
  89. B. Huber and J. Burfeindt, "Nanotechnology in Cosmetics," pp. 17–25, 2019.
  90. I. Kaur and R. Agrawal, "Nanotechnology: A New Paradigm in Cosmeceuticals," *Recent Pat. Drug Deliv. Formul.*, vol. 1, no. 2, pp. 171–182, 2008, doi: 10.2174/187221107780831888.
  91. Patel, J. R.; R. P.; Joshi, AN OVERVIEW ON NANOEMULSION: A NOVEL APPROACH. **2012**, vol. 3, no. 12, pp. 4640–4650.
  92. Fred, Z.; Esther, B.; Daniel, S.; Christina, L.; and Franz, S. Preparation and Properties of Coenzyme Q10 Nanoemulsions. *Cosmetic Science Technology*. **2006**, p. 304.
  93. Özgün, S. Nanoemulsions in Cosmetics. **2013**, no. June, 2013.
  94. Izquierdo, P.; Esquena, J.; Tadros, T. F.; Dederen, C.; Garcia, M. J. ; Azemar, N.; and Solans, C. "Formation and Stability of Nano-Emulsions Prepared Using the Phase Inversion Temperature Method. **2002**, no. 7, pp. 26–30.
  95. Bouchemal, K.; Briançon, S.; Perrier, E.; and Fessi, H. Nano-emulsion formulation using spontaneous emulsification: solvent , oil and surfactant optimisation. **2004**, vol. 280, pp. 241–251. doi: 10.1016/j.ijpharm.2004.05.016.
  96. Chevalier, Y.; and Bolzinger, M. Micelles and Nanoemulsions. **2019**, pp. 47–72.
  97. Gupta, A.; Burak Eral, H.; Hatton, T. A.; and Doyle, P. S. Multi-phase semicrystalline microstructures drive exciton dissociation in neat plastic semiconductors. *J. Mater. Chem. C*. **2016**, vol. 3, pp. 10715–10722, 2016, doi: 10.1039/b000000x.
  98. Niska, K.; Zielinska, E.; Radomski, M. W.; and Inkielewicz-stepniak, I. Metal nanoparticles in dermatology and cosmetology: Interactions with human skin cells. *Chem. Biol. Interact.* **2017**. doi: 10.1016/j.cbi.2017.06.018.
  99. Pentek, T.; Newenhouse, E.; O'Brien, B.; and Chauhan, A. S. Development of a Topical Resveratrol Formulation for Commercial Applications Using Dendrimer Nanotechnology. **2017**, doi: 10.3390/molecules22010137.
  100. Iimura, T.; and Furukawa, H. ( 12 ) Patent Application Publication ( 10 ) Pub . No . : US 2012 / 026-3662 A1. **2012**, vol. 1, no. 19.
  101. Arzani, G.; Haeri, A.; Daeihamed, M.; Bakhtiari-Kaboutaraki, H.; and Dadashzadeh, S. Niosomal carriers enhance oral bioavailability of carvedilol: Effects of bile salt-enriched vesicles and carrier surface charge. *Int. J. Nanomedicine*. **2015**, vol. 10, pp. 4797–4813. doi: 10.2147/IJN.S84703.
  102. Chandu, V. P.; Arunachalam, A.; Jeganath, S.; Yamini, K.; Tharangini, K.; and Chaitanya, G. Niosomes : a Novel Drug Delivery System. **2012**, vol. 3618, p. 15.
  103. Kumar, G. P.; and Rajeshwarrao, P.; Nonionic surfactant vesicular systems for effective drug delivery —an overview. *Acta Pharm. Sin. B*. **2011**, vol. 1, no. 4, pp. 208–219. doi: 10.1016/j.apsb.2011.09.002.

104. Santander-Ortega, M. J.; Lozano-López, M. V.; Bastos-González, D.; Peula-García, J. M.; and Ortega-Vinuesa, J. L. Novel core-shell lipid-chitosan and lipid-poloxamer nanocapsules: Stability by hydration forces. *Colloid Polym. Sci.* **2010**, vol. 288, no. 2, pp. 159–172. doi: 10.1007/s00396-009-2132-y.
105. Karakoti, A.; Singh, S.; Dowding, J. M. ; Seal, S.; and Self, W. T. Redox-active radical scavenging nanomaterials. *Chem. Soc. Rev.* **2010**, vol. 39, no. 11, pp. 4422–4432. doi: 10.1039/b919677n.
106. Al Shaal, L.; Müller, R. H.; and Shegokar, R. SmartCrystal combination technology - Scale up from lab to pilot scale and long term stability. *Pharmazie.* **2010**, vol. 65, no. 12, pp. 877–884. doi: 10.1691/ph.2010.0181.
107. Cevc, G. Lipid vesicles and other colloids as drug carriers on the skin. *Adv. Drug Deliv. Rev.* **2004**, vol. 56, no. 5, pp. 675–711. doi: 10.1016/j.addr.2003.10.028.
108. Kalia, Y. N.; Guy, R. H. and Fessi, H. Enhancement of Topical Delivery from Biodegradable Nanoparticles. **2004**, vol. 21, no. 10, pp. 1818–1825.
109. Vincent, N.; Ramya Devi, D.; and Vedha Hari, B. N.; Progress in psoriasis therapy via novel drug delivery systems. *Dermatology Reports.* **2014**, vol. 6, no. 1, pp. 15–19. doi: 10.4081/dr.2014.5451.
110. Verma, H. N.; Singh, P.; and Chavan, R. M. Gold nanoparticle: Synthesis and characterization. *Vet. World.* **2014**, vol. 7, no. 2, pp. 72–77. doi: 10.14202/vetworld.2014.72-77.
111. Yeh, Y. C.; Creran, B.; and Rotello, V. M. Gold nanoparticles: Preparation, properties, and applications in bionanotechnology. *Nanoscale.* **2012**, vol. 4, no. 6, pp. 1871–1880. doi: 10.1039/c1nr11188d.
112. Cross, S. E.; Innes, B.; Roberts, M. S.; Tsuzuki, T.; Robertson, T. A.; and McCormick, P. Human skin penetration of sunscreen nanoparticles: In-vitro assessment of a novel micronized zinc oxide formulation. *Skin Pharmacol. Physiol.* **2007**, vol. 20, no. 3, pp. 148–154. doi: 10.1159/000098701.
113. Newman, M. D.; Stotland, M.; and Ellis, J. I. The safety of nanosized particles in titanium dioxide- and zinc oxide-based sunscreens. *J. Am. Acad. Dermatol.* **2009**, vol. 61, no. 4, pp. 685–692 doi: 10.1016/j.jaad.2009.02.051.
114. Durand, L.; Habran, N.; Henschel, V.; and Amighi, K. Encapsulation of ethylhexyl methoxycinnamate, a light-sensitive UV filter, in lipid nanoparticles. *J. Microencapsul.* **2010**, vol. 27, no. 8, pp. 714–725. doi: 10.3109/02652048.2010.513455.
115. Padamwar, M. N.; and Pokharkar, V. B. Development of vitamin loaded topical liposomal formulation using factorial design approach: Drug deposition and stability. *Int. J. Pharm.* **2006**, vol. 320, no. 1–2, pp. 37–44. doi: 10.1016/j.ijpharm.2006.04.001.

**Disclaimer/Publisher's Note:** The statements, opinions and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of MDPI and/or the editor(s). MDPI and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions or products referred to in the content.