

Article

Not peer-reviewed version

---

# Characterization of *Lithraea molleoides* Gum Films

---

[Federico Becerra](#) <sup>\*</sup>, [Maria Filomena Garro](#) <sup>\*</sup>, Gisella Melo, [Martin Alberto Masuelli](#) <sup>\*</sup>

Posted Date: 2 October 2024

doi: 10.20944/preprints202410.0074.v1

Keywords: *Lithraea molleoides* fruit gum; hydrolysis; films



Preprints.org is a free multidiscipline platform providing preprint service that is dedicated to making early versions of research outputs permanently available and citable. Preprints posted at Preprints.org appear in Web of Science, Crossref, Google Scholar, Scilit, Europe PMC.

Copyright: This is an open access article distributed under the Creative Commons Attribution License which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Disclaimer/Publisher's Note: The statements, opinions, and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of MDPI and/or the editor(s). MDPI and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions, or products referred to in the content.

## Article

# Characterization of *Lithraea molleoides* Gum Films

Federico Becerra <sup>1,\*</sup>, Maria F. Garro <sup>2,\*</sup>, Gisella Melo <sup>3</sup> and Martin Masuelli <sup>1,\*</sup>

<sup>1</sup> Instituto de Física Aplicada (INFAP-CONICET-UNSL)-Departamento de Química, Facultad de Química, Bioquímica y Farmacia, Universidad Nacional de San Luis. Ejército de los Andes 950-San Luis, Argentina.

<sup>2</sup> Departamento de Farmacia, Facultad de Química, Bioquímica y Farmacia, Universidad Nacional de San Luis, Ejército de los Andes 950-San Luis, Argentina.

<sup>3</sup> Facultad de Química, Bioquímica y Farmacia, IMIBIO-CONICET, Universidad Nacional de San Luis, Chacabuco 917, San Luis ZC: 5700, Argentina

\* Correspondence: federicobecerra456@gmail.com (F.B.), mfgarro@gmail.com (M.F.G.), masuelli@unsl.edu.ar (M.M.)

**Abstract:** *Lithraea molleoides* fruit gum (LMFG) is a valuable product obtained from the total hydrolysis of the fruit. The hydrolysis process involves three methods: thermal (LMFGT), basic (LMFGB), and acid (LMFGA). Through these methods, the aim is to break bonds and de-esterify polysaccharides, resulting in increased solubility and decreased molecular weight. The resulting hydrolysates are then combined with pectins in a 1:2 ratios to form films. In this study, the focus is on utilizing the hydrolysates of *Lithraea molleoides* gums for film applications, with an evaluation of their structural and physicochemical characteristics. The films produced exhibit excellent mechanical properties and low water vapor permeability, as well as exceptional thermal stability. These properties make them highly suitable for industrial films in pharmaceutical and food applications. This research highlights the potential of LMFG-based films as a viable solution for various industrial needs due to their outstanding performance across multiple parameters.

**Keywords:** *Lithraea molleoides* fruit gum; hydrolysis; films

## 1. Introduction

The packaging in the food industry uses synthetic plastics. The thermoplastic as polystyrene, polyethylene, poly(ethylene terephthalate), and polypropylene use for packaging and are disposable, generating waste, entering the environment and undergoing degradation processes [1]. The disposal of nondegradable packaging waste of synthetic polymers is a global issue, the scientific community seeks to develop biodegradable packaging from renewable sources to reduce environmental impact [2]. Water-soluble gums are valuable in many fields, including adhesives, agriculture, biotechnology, ceramics, cosmetics, explosives, food, paper, textiles and texturization, among many others [3-5]. The edible films and coatings, which are still used today, help prevent oxidative rancidity, preserve sensory qualities, maintain pigments, delay ripening, and extend the shelf life of various food products [6]. The proteins, polysaccharides, and their blends are used to make edibles films/coatings containing antimicrobials, which demonstrated to be a useful tool as a stress factor to protect foodstuff against spoilage flora and to decrease the risk of pathogen growth [7].

Carrageenan, cornstarch, and Gelatin are analyzed for their chemical, physical, and mechanical properties how biodegradable alternatives from renewable sources to produce films [8]. Starch formulations with a protein that show synergy because protein has characteristics that can form a flexible film and do not tear easily and rectify the physical characteristics of the polysaccharide film [9]. Edible films and coatings enhance the quality of food products, protecting them from physical, chemical, and biological deterioration [10].

The edible films and coatings with polysaccharides, proteins and lipids. – their sources, properties and possible application - substantially improve its all properties [11]. In addition, need improvements in structural and barrier limitations for better performance [12-14]. The coatings and films from polysaccharides, proteins and lipids with the addition of surfactants and plasticizers are

used barrier and mechanical properties which in turn depend its formation process and film composition. For the edible coatings, the method of application on the product, and the capacity of the coating to adhere to the surface are the most important parameters [15-18]. The advancements in edible films or coatings composed from natural plant compounds, highlighting their mechanical and physicochemical characteristics and promotes sustainable practices in the packaging industry [19]. The importance of assessing the preformed matrix of edible films quantifies various parameters such as antimicrobial properties, mechanical and optical since this envelope creates a modified atmosphere for straightening the gases transfer ( $\text{CO}_2$ ,  $\text{O}_2$ ) and aromatic compounds barrier [20].

The native or modified chitosans and chitooligosaccharides are associated with bioadhesive applications, adsorption, antimicrobial activities, and chelation in the wine industry [21]. The potential of coatings based on xylan derivatives and chitosan to provide barrier properties and antimicrobial protection for packaging food [22]. The study show developing functional properties of taro starch-reinforced polysaccharide-based films for active packaging, fabricating films containing chitosan, pullulan, and taro starch extracted from *Colocasia esculenta* tubers using the wet-milling process [23]. Papers covered with poly-vinyl alcohol and biodegradable cellulose nanocrystals were also used for the purpose of biopackaging aqueous foods [24]. Algal polysaccharides like galactans, alginates, and ulvan, detailing structure, properties, and applications in foods packaging [25]. Biodegradable packaging films incorporating purple cauliflower-extracted anthocyanins into fucoidan and alginate/carboxymethyl chitosan matrices with  $\text{Ca}^{2+}$  and  $\text{Zn}^{2+}$  crosslinker [26-27]. *Gracilaria chouae* polysaccharide food packaging applied with carboxymethyl cellulose and lysozyme [28].

Films derived from cellulose and its derivatives, pectin, starch, alginate, chitosan, pullulan reducing water vapor permeability [29]. Agroindustrial waste as a cost-effective starting material for bioprocessing, to enhance efficiency and reduce fermentation costs [30]. Advances in green solvents for production of polysaccharide-based packaging films: Insights of ionic liquids and deep eutectic solvents [31-32].  $\kappa$ -carrageenan/starch with zinc oxide nanoparticles films [33]. Films of Aloe vera in  $\beta$ -hydroxy- $\beta$ -methylbutyrate calcium and nanocellulose films for blueberry freshness preservation [34]. Policaju and Tween 80 edible coatings/films for Golden apples protection [35]. Kraft paper with cellulase impregnating with essential clove oil and cold-pressed grape seed oil films [36]. Propolis with cellulose, starch, chitosan, and alginate used for composite biodegradable active packaging [37]. Bionanocomposite films with plasticized whey protein isolate-jujube polysaccharide/starch nanocrystal blends for packaging fresh-cut carrots [38]. Characterization of *Zizania latifolia* polysaccharide-corn starch composite films and their application in the postharvest preservation of strawberries [39]. The study developed a polysaccharide-based composite film with antimicrobial properties to extend the shelf life of fresh-cut watermelon. Packaging tests demonstrated its potential for prolonging shelf life and showed excellent barrier and heat-sealing properties [40]. Xanthan gum/pullulan with grape seed extract (GSE) composite films extended the shelf life of fresh-cut apples [41]. Soluble soybean polysaccharide and *Malva sylvestris* extract to extend food shelf life and detect shrimp spoilage [42]. Extracts of *Pinus brutia* bark were added in chitosan-polyvinyl alcohol films [43]. *Auricularia auricula* polysaccharide-based films and application in meat preservation [44]. Starch, chitosan, sodium alginate, and cellulose, focusing on improving hydrophilic barrier, and mechanical properties [45]. Silver nanoparticles (PCP-AgNPs) using *Poria cocos* polysaccharide films exhibited excellent antibacterial activity and extended the shelf life of strawberries [46]. Carboxymethyl cellulose films enhanced with mulberry leaf polysaccharides [47]. Soluble soybean polysaccharide, grape skin anthocyanin extract, and graphene oxide to monitor food freshness (pH sensitivity and a color change indicating spoilage) for smart packaging [48]. Biodegradable, antimicrobial, and antioxidant packaging from chitosan, hyaluronic acid, and chondroitin sulfate [49]. Citric acid to crosslink glycerol-plasticized soybean polysaccharide films, enhancing their water resistance, mechanical, UV-barrier, water vapor barrier, antioxidant, thermal, and antibacterial properties [50]. Renewable and biodegradable fiber-based packaging materials are being developed to replace nonbiodegradable plastics. We created waterborne barrier coatings from natural polysaccharides, achieving a highly crosslinked polymer network that forms uniform, effective

barrier layers on paperboard and molded pulp. These coatings offer excellent oil and grease resistance, reduced water sensitivity, and maintain recyclability [51-53].

*Lithraea molleoides* (Vell.) Engl. (Anacardiaceae) is a polygamous dioecious tree with persistent and dense foliage, also known as "molle de beber." It is distributed in northern and central Argentina, Bolivia, Brazil, and Uruguay. It is a tree that grows 3-8m tall, with a globose crown, shiny leaves, and dark branches. The leaves are evergreen, alternate, shiny green, compound, with 3-5 lanceolate leaflets that come to a sharp point. The prominent secondary veins run parallel to each other. The small yellowish flowers are clustered in compound axillary racemes. The fruit is a globose drupe, with a greenish or white epicarp. It appears juicy when ripe, but is dry and breaks to release the seeds. The fruit is a globose drupe, 6-8 mm in diameter, whitish-green and shiny. It blooms from October to November and bears fruit from January onwards. These are edible; the indigenous Tehuelche people favored the fruits and also made chicha from the crushed seeds [54].

In this study *Lithraea Molleoides* fruit Gum (LMFG) is obtained from hydrolysis of the fruit. The hydrolysis used are three: thermal (LMFGT), basic (LMFGB) and acid (LMFGA). The LMFG are analyzed by Proximate Analysis of Biomass, Antioxidant Activity Assays (Reducing Power, Hydroxyl Radical Scavenging, DPPH Scavenging Activity, Total Polyphenol Content), Fourier Transform Infrared Spectroscopy, X-ray Diffraction (XRD), Differential Scanning Calorimetric Analysis (DSC), Thermogravimetric Analysis—Differential Thermogravimetric Analysis. The aim of hydrolysis is bond breaking and de-esterification of polysaccharide, with the consequent increase in solubility and decrease in molecular weight. Blend films with pectins are prepared from these gums LMFGTf (Thermal), basic LMFGBf and acid LMFGAf. These films were characterized by Scanning Electron Microscopy—Electron Dispersive X-ray Spectroscopy (SEM-EDX), Mechanical Tests, Water Vapor Permeability and Biodegradability.

## 2. Materials and Methods

### 2.1. Raw Material

The *Lithraea molleoides* fruit, LMF, (voucher number: UNSL # 533 [54]) was collected in the countryside located in San Francisco del Monte de Oro (32°36'00" S, 66°07'30" W) in San Luis, Argentina, in January 2022. The fruit was selected and washed with distilled water, placed in a polypropylene container and dried at 60°C for 24 hours. All fruit (husk and seed) was ground and separate to 50 mesh obtaining flour from LMF. All hydrolysis was performed at 80°C for 6h, at a concentration of 0.1M NaOH (Anhendra, Argentina) or HCl (Ciccarelli, Argentina). The soluble fraction was precipitated with ethanol/distilled water 70/30 and separated by filtration, the filtrate was concentrated at 60°C for 8h, and dried at 60°C for 24h. The synthesis of films was carried out by adding 2g of pectin (MAC, Argentina) as a polymer matrix, 1 gram of the different hydrolysates and 1mL of glycerin used as a plasticizer. The nomenclature for the different films that contain hydrolysates were as follows: LMFGTf for thermal hydrolysis, LMFGBf for basic hydrolysis and LMFGAf for acid hydrolysis [55]. The pectin film (Pec2.5) was made by the casting method from 2.5 g of pectin (MAC, Argentina), then follows the same procedure as the rest of the films.

### 2.2. *Lithraea MOLLEOIDES* FRUIT GUM FLOur (LMFG)

#### 2.2.1. Proximate ANALYsis of BIOMass

In accordance with standard methods, the sample was macerated to a powder and subjected to proximate analysis (AOAC, 2012). The nitrogen content was determined using the Kjeldahl-Arnold-Gunning method, and total proteins were calculated using a factor of 6.25 (AOAC. 920.12). Protein productivity was also calculated and expressed as milligrams of protein produced per liter of culture per hour. Total fats were determined using the Soxhlet gravimetric method with petroleum ether (Sigma Aldrich) (AOAC 945.39), while crude fiber was determined using the digesting sample method with H<sub>2</sub>SO<sub>4</sub> and NaOH (Sigma Aldrich) (AOAC 962.09). Ashes were determined using the

weight difference method after calcining the sample (AOAC 945.46), and moisture content was determined through heating under reduced pressure (AOAC 945.46). Carbohydrates were indirectly calculated as, Total carbohydrates = 100 – (Proteins + Total Fat + Moisture + Ash). Following these established methods ensures accuracy and consistency in our analysis, providing valuable information for further research or application within various industries [56].

#### 2.2.4. Antioxidant Activity Assays

Reactive oxygen species (ROS) are known to cause liver-damaging oxidation and loss of bodily functions. Among these ROS, superoxide anion radicals ( $O_2^{\cdot-}$ ), hydroxyl radicals ( $\cdot OH$ ), and DPPH radicals are particularly detrimental to the body. Therefore, the determination of these ROS is crucial in the study of novel polysaccharides. Understanding the impact of ROS on the body's functions is essential for developing effective treatments for liver damage and oxidative stress-related conditions. By studying how novel polysaccharides interact with and potentially neutralize these harmful free radicals, researchers can advance our understanding of their potential therapeutic benefits. Investigating the effect of novel polysaccharides on reactive oxygen species could lead to breakthroughs in medical treatment and preventive care. The determination of ROS is a key step in this research process, laying the groundwork for potential advancements in healthcare and wellness [57]. The role that reactive oxygen species play in liver damage underscores the importance of studying novel polysaccharides as potential countermeasures. The determination of these harmful free radicals serves as a critical starting point for further advancements in medical research and treatment options.

#### 2.2.5. Reducing Power

The reducing power assay, as described by reference [57], involved several steps to determine the reducing power of polysaccharide solutions. This method required precise measurements and careful incubation to ensure accurate results. The addition of reagents such as phosphate buffer (2M, pH 6.6), potassium ferricyanide (1% *w/v*), trichloroacetic acid (2.5ml 10% *w/v*), and ferric chloride (0.2mL) were crucial in stopping the reaction and measuring the absorbance at 700 nm. The procedure was conducted in triplicate to ensure reliability, with ascorbic acid serving as a positive control for comparison. This meticulous approach allowed for a thorough assessment of the reducing power of polysaccharide solutions, demonstrating the importance of precision in scientific methodologies.

#### 2.2.6. Hydroxyl Radical Scavenging

The hydroxyl radical assay was conducted following the salicylic method outlined by reference [58], with some adjustments. In a test tube, 2 mL polysaccharide solution (0.1–1 mg/mL) was combined with 2 mL  $FeSO_4$  (4 mM), 2 mL salicylic acid hydroalcoholic solution (4 mM), and 2 mL  $H_2O_2$  (4 mM) in a test tube. The mixture was then agitated and incubated at 37 °C for 30 minutes before being centrifuged at 300 g for 5 minutes, and the absorbance of the supernatant was measured at a wavelength of 510 nm. The hydroxyl scavenging rate (r%) was determined using the formula:

$$r(\%) = \frac{(A_{c0} - (A_{m0} - A_{b0}))}{A_{c0}} \times 100 \quad (5)$$

where  $A_{c0}$  is the absorbance of the control, prepared with  $H_2O$  replacing the sample;  $A_m$  is the sample absorbance, and  $A_{b0}$  is the blank absorbance, prepared for each sample with  $H_2O$  replacing  $H_2O_2$ . The procedure was carried out in duplicate, and ascorbic acid served as a positive control. Results were expressed in mg/L equivalents of ascorbic acid. This modified method provides an accurate means of measuring hydroxyl radical scavenging activity in various solutions, allowing researchers to effectively assess antioxidant capabilities within their samples.

#### 2.2.7. DPPH Scavenging Activity

DPPH radical scavenging activity was assessed using a method described by reference [57] with some adjustments. The process involved adding 0.5 mL of polysaccharide solution (0.1-1mL) to a 90% ethanolic solution of DPPH (0.15M) and incubating it in darkness for 30 minutes before measuring absorbance at 517 nm. The total antioxidant content was calculated as a percentage of antioxidant activity (% AA) using the formula:

$$AA(\%) = \frac{(A_c - (A_m - A_b))}{A_c} * 100 \quad (6)$$

where  $A_c$  is the absorbance of the control,  $A_m$  is the sample absorbance, and  $A_b$  is the blank absorbance. The procedure was conducted in triplicate, and ascorbic acid was used as a positive control. A calibration curve for ascorbic acid was also prepared and measured to express the results in mg/L equivalents of ascorbic acid. These meticulous measurements and calculations provide valuable insights into the antioxidant properties of polysaccharides, contributing to our understanding of their potential health benefits.

#### 2.2.8. Total Polyphenol Content

The determination of total phenolic compounds was conducted in accordance with the Folin-Ciocalteu method [59-60], with some modifications to ensure accuracy and precision. A 5 mL aliquot of the sample was carefully measured and combined with 1.5 mL of Folin-Ciocalteu reagent (2 N) and 15 mL of  $Na_2CO_3$  solution (15%) in a volumetric flask, resulting in a final volume of 25 mL that was completed with distilled water. The resulting mixture was allowed to stand in a location shielded from light, at room temperature for a duration of 2 hours to facilitate the reaction. Following completion of the reaction, the absorbance was measured at 760 nm using appropriate instrumentation. The quantity of total phenolic compounds present in the sample was then expressed as gallic acid equivalents for standardization purposes. In order to establish calibration curves and ensure accuracy, six concentrations ranging from 1-6 mg/L were prepared using gallic acid as a reference standard. To validate results, this entire procedure was meticulously performed twice in order to confirm reproducibility and reliability.

#### 2.2.9. Fourier Transform Infrared Spectroscopy

In the field of analytical chemistry, Fourier-transform infrared (FTIR) spectroscopy is a widely used technique for identifying and analyzing chemical compounds. In this study, FTIR spectra were obtained using two different modes - diffuse reflectance (DRIFTS) and transmission - with the use of a Nicolet PROTEGE 460 Spectrometer. The operational range for the spectra collection was set from 700 to 400  $cm^{-1}$ , allowing for comprehensive analysis of the samples. Furthermore, each sample was scanned 64 times to ensure accuracy and reliability in the results. The choice of using both DRIFTS and transmission modes provides valuable insight into the chemical composition and structure of the samples under investigation. This comprehensive approach allows for a thorough understanding of the molecular vibrations present in the samples across a wide range of wavelengths. Overall, this study showcases meticulous attention to detail in experimental design and execution, aiming to provide high-quality data for further analysis and interpretation. The use of advanced instrumentation coupled with precise scanning parameters ensures that the FTIR spectra obtained are robust and reliable, laying a solid foundation for meaningful insights into the chemical nature of the samples [61].

#### 2.2.10. X-ray Diffraction (XRD)

X-ray diffraction (XRD) studies were conducted utilizing state-of-the-art Rigaku equipment, specifically the model ULTIMA IV type II, manufactured in Tokyo, Japan. This equipment was equipped with a  $Cu K\alpha$  lamp with a wavelength ( $\lambda_B$ ) of 1.54 Å and a nickel filter to ensure accurate and precise measurements. The operational range for the  $2\theta$  angle was set from  $3^\circ$  to  $60^\circ$ , with the instrument being operated at 30 kV and 20 mA. A sweep rate of  $3^\circ$  per minute with a reading step of

.02° was utilized in continuous mode to ensure comprehensive data collection. The  $d_{spacing}$ , or average intercatenary distance, was determined by applying Bragg's equation:

$$d_{spacing} = \frac{n \lambda_B}{2 \sin \theta_B} \quad (3)$$

where  $d_{spacing}$  represents the intercatenary distance,  $n$  is an integer value determined through analysis,  $\lambda_B$  denotes the X-ray wavelength used, and  $\theta_B$  refers to Bragg's angle [61].

$$IC_r = 100 \frac{I_{max} - I_{ad}}{I_{max}} \quad (4)$$

Moreover, the crystalline index ( $IC_r$ ) was calculated from the normalized diffractogram using peak intensities at lattice plane reflection indices such as 110 lattices ( $I_{max}$ ), which is observed at an angle of approximately 21° corresponding to maximum intensity. Additionally, amorphous diffraction data  $I_{ad}$  at an angle of approximately 15° was utilized in determining  $IC_r$  following methods outlined in previous literature [62-64].

#### 2.2.11. Differential Scanning Calorimetric Analysis (DSC)

Differential scanning calorimetry (DSC) was conducted using the STA 449F3-Jupiter equipment manufactured by Selb, Germany. To begin the analysis, approximately 5 mg of the biopolymer sample was carefully placed in an alumina crucible. The sample was then subjected to a controlled heating process, starting from an initial temperature of 25 °C and steadily increasing to a maximum temperature of 400 °C. This heating process was carried out at a constant rate of 5 °C per minute under a dynamic nitrogen atmosphere with a flow rate set at 25 mL per minute [65]. These specific parameters were chosen in order to accurately measure and analyze the thermal behavior and properties of the biopolymer sample, allowing for precise determination of its characteristic transitions and thermal stability under these controlled conditions.

#### 2.2.12. Thermogravimetric Analysis—Differential Thermogravimetric Analysis

The thermal stability of the polysaccharides films was assessed through a comprehensive thermogravimetric analysis (TGA). Utilizing a TG 295 analyzer from TA Instruments, Inc., located in New Castle, DE, USA, the TGA determinations were carried out. The analytical conditions included a heating rate of 10 °C/min in a N<sub>2</sub> (99.99%) atmosphere with a flow rate of 50 mL/min, which had been pre-filtered. Moreover, the temperature axes for thermogravimetric analysis were calibrated using indium (99.99%, with a melting point of 156.60 °C) and the Curie point of Ni (353 °C). Empty aluminum pans (40 mL) were utilized as reference materials and polysaccharide samples weighing approximately 8 mg were employed [65].

### 2.3. *Lithraea Molleoides* Fruit Gum Films (LMFGf)

#### 2.3.1. Scanning Electron Microscopy–Electron Dispersive X-ray Spectroscopy (SEM-EDX)

The film's morphology was meticulously analyzed using a state-of-the-art scanning electron microscope, the LEO 145VP, located in Los Altos, CA, USA. Additionally, the energy dispersion X-ray analysis was conducted using the highly advanced EDS Genesis 200 by EDAX, also based in Los Altos, CA, USA. Prior to the surface analysis with SEM, the samples underwent a preparation process involving immersion in liquid nitrogen and subsequent coating with gold. The observations of biopolymer samples were carried out under high vacuum conditions, and the resulting EDAX spectrums were obtained with an acceleration voltage of 120 kV [65], ensuring precise and accurate data collection for thorough investigation.

### 2.3.2. Mechanical Tests

The mechanical properties of the materials were assessed using a Brookfield CT3 instrument from the USA, in accordance with the ASTM D882 requirements, at a consistent traction speed of .1 mm/min. The experimental procedure for determining these properties was conducted at a temperature of 25 °C and relative humidity of 40%, with each test performed in triplicate. Test samples measuring 40 mm in length by 10 mm wide were utilized, with thickness measurements taken for each film using a micrometer. Data on force (F) and deformation ( $\Delta l$ ) were collected until the breaking point was reached. Tensile strength ( $\sigma$ ) was calculated by dividing the maximum load by the specimen's initial cross-sectional area (A). Percentage elongation at break ( $\% \epsilon$ ) was determined as a percentage change from the specimen's initial length ( $l = 40$  mm) at failure. Lastly, elastic modulus, or Young's modulus (E), was derived from the slope of stress ( $\sigma$ ) vs strain ( $\epsilon$ ) curve in the elastic region, which represents the linear part of the curve [65-66].

$$E = \frac{\sigma}{\epsilon} \quad (7)$$

$$\sigma = \frac{F}{A} \quad (8)$$

$$\epsilon = \frac{\Delta l}{l_0} \quad (9)$$

### 2.3.4. Water Vapor Permeability

The equipment used for determining water vapor permeability was Electrotech Systems, Chicago, IL, USA, which operates as a closed system controlled by sensors for temperature and humidity measurements. The weight change was obtained by a RADWAG balance (Radom, Poland), with a precision of 0.1 mg, and a Kölfe thickness micrometer (München, Germany), with an accuracy of 0.1 m. The film samples of 25 mm in diameter were cut, their thicknesses were measured, and they were placed in the perforated caps of the bottles with 20 g of silica gel inside each one. Each bottle with silica gel was weighed and the cap was put on before starting the experiment. Then, they were placed in the equipment which must be at 30 °C and 85% humidity; during the first hour they were weighed every five minutes. After this initial hour, the weight of each bottle was measured every fifteen minutes until the third hour when it was then measured at one-hour intervals until reaching twenty-four hours (ASTM E96). The mechanism can be described for a homogeneous polymer film of thickness permeant pressure  $p$  (with  $p_1 > p_2$ ) and permeant concentrations  $c$  throughout the film (with  $c_1 > c_2$ ):

$$\tau = \frac{Q}{t A} \quad (1)$$

$$P = \frac{\lambda}{\Delta P} \tau \quad (1)$$

where  $\tau$  is transmission speed (ng/m<sup>2</sup>s),  $Q$  is permeating mass (ng),  $\lambda$  is thickness of film(m),  $A$  is area of cell (m<sup>2</sup>),  $t$  is measurement time(s), and  $\Delta P$  pure water vapor pressure (4238 .605 Pa) [65-67].

### 2.3.5. Biodegradability

The process of biodegradation is a complex and crucial aspect of the life cycle of biopolymers. It involves the breakdown and transformation of these materials through the enzymatic action of microorganisms such as bacteria, yeasts, and fungi. This process can result in total or partial degradation, with partial degradation leading to changes in chemical composition and loss of specific

properties. The complete degradation of a material occurs when it is entirely consumed by microorganisms, resulting in the production of methane or CO<sub>2</sub> depending on the conditions. In a recent study, a covered container was filled with moistened soil samples at 85% relative humidity, and samples were monitored over a 120-day period under mesophilic conditions at 30°C to assess biodegradation rates [66-68]. The findings from this study shed light on the intricate mechanisms involved in biodegradation processes and their potential implications for sustainable waste management practices.

### 3. Results

#### 3.1. *Lithraea Molleoides* Fruit Gum Flour (LMFG flour)

##### 3.1.1. Proximate Analysis of Biomass and Antioxidant Capacity

The percentage yield of the gum obtained was calculated from 10 g of dried fruit, where R<sub>e</sub>% is the ratio between what was obtained and the sample. The yield is determined after filtration of the solution and the soluble filtrate is precipitated with ethanol/water in a 70/30 ratio. There is no information about the type and structure of the polysaccharide obtained, which will be studied in future publications. This means that thermal hydrolysis is more efficient in extracting polysaccharide, while thermal hydrolysis is less efficient. The yield for the LMFGB flour is 33.88%, for the LMFGA 15.43% and for the LMFGT 11.11%. This means that basic hydrolysis is more efficient in extracting polysaccharide, while thermal hydrolysis is less efficient. Taking into account the fiber analysis, a similar but numerically greater trend can be seen, this is because the technique performs a total hydrolysis, with the amount of sample being much higher than the yield. The amount of protein is tiny and less than 0.1%. Ashes give mixed results, but the interesting fact is that untreated flour (HLM) is similar to thermal flour, repeating the pattern in total fats. As for total fats, these are partially eliminated during basic or acid hydrolysis in a similar way. Moisture is similar to all flours. For proximate analysis of biomass see Table1.

**Table 1.** Proximate analysis of biomass.

	Moisture (%wt.)	Ash (%wt.)	Total Grass (g/100g)	Proteins (%wt.)	Fibers (%wt.)
HLM	10.60±0.25	1.84±0.02	9.92±0.33	0.0454	15.22±0.53
LMFGT	2.40±0.74	1.45±0.03	7.30±0.31	0.0851	28.49±1.24
LMFGA	3.12±0.18	0.82±0.01	3.40±0.14	0.0189	27.78±1.55
LMFGB	3.25±0.17	0.84±0.01	2.84±0.13	0.0330	42.20±1.89


However, not all polysaccharides exhibit high antioxidant activity, as is the case with LMFGT, LMFGA, and LMFGB. Some studies have shown that certain types of polysaccharides have limited antioxidant activity, meaning that their ability to protect cells from oxidative stress is lower compared to other compounds, see Table 2. This limited antioxidant activity may be due to several factors. First, the chemical structure of the polysaccharide can influence its ability to act as an antioxidant agent. For example, some polysaccharides may have side chains or functional groups that make it difficult for them to interact with free radicals. Furthermore, the degree of branching and the chain length of the polysaccharide can also affect its antioxidant activity. Longer polymers tend to have a greater ability to trap and neutralize free radicals due to their greater molecular surface available to interact with them. On the other hand, external factors such as hydrolysis processing can also decrease the antioxidant activity of polysaccharides. During these processes, adverse conditions such as high temperatures or exposure to oxygen can cause modifications in the chemical structure of the compound, reducing its effectiveness as a protective agent against oxidative stress. In summary, although polysaccharides are known for their various biological and nutritional benefits, not all of them have high antioxidant activity. It is important to take these aspects into account when choosing natural or supplemental sources of polysaccharides for therapeutic purposes.

**Table 2.** Antioxidant activity of the different gums obtained.

	Reducing Power (μeq gal/mL)	Antioxidant Activity (μeq AA/ml)	Total Polyphenols (μeq gal/mL)
HLM	4.04±0.22	14.78±0.55	13.13±0.39
LMFGT	1.91±0.17	3.48±0.22	28.58±0.62
LMFGA	3.49±0.33	2.71±0.37	11.96±0.48
LMFGB	9.91±0.42	9.46±0.45	41.82±1.06

### 3.1.3. DRX

Amorphous polysaccharides are an essential component of many natural and synthetic materials. Understanding their structural properties is crucial for various fields, including pharmaceuticals, food science, and material engineering. One method of analyzing these polysaccharides is through X-ray diffraction (DRX) data. The DRX data of amorphous polysaccharides provides valuable insights into their molecular arrangement. In this particular case, the  $2\theta$  values for LMFGT, LMFGA, and LMFGB are 20.18, 20.62, and 20.34, respectively. Additionally, the  $d_{spacing}$  values for LMFGT, LMFGA, and LMFGB are recorded as 4.39 nm, 4.30 nm, and 4.36 nm respectively (see Table 3). These numerical values serve as a foundation for further analysis of the amorphous polysaccharides' structure and characteristics and comparing the different peaks in the X-ray diffraction pattern with standard references or known structures of similar compounds or polymers can provide valuable information about the arrangement at atomic level.

**Figure 1.** DRX of gums.**Table 3.** DRX data of gums.


Flour	$2\theta$	$d_{spacing}$ (nm)	$I_{Cr}$ %
LMFGT	20.18±0.81	4.39±1.03	47.75±1.23
LMFGA	20.62±0.79	4.30±0.98	48.10±1.01
LMFGB	20.34±0.84	4.36±0.95	48.83±0.98

This data can be used to deduce important information about these amorphous polysaccharides such as intermolecular distances between chains or structural modifications due to environmental changes like moisture content or temperature fluctuations. Furthermore, these findings could help in developing new materials with enhanced functionalities by modulating their structure at molecular level hence improving applications on packaging industry to achieve better barriers properties against gases like oxygen which will improve shelf life on food products in contact with it. The  $I_{Cr}$

data are lower compared to those obtained by chitosan and its performance in an active film with quercetin and *Phaseolus polyanthus* starch [69]. While similar results are observed in chitosan with  $\text{I}_{\text{cr}}$  of 20.07 corresponding to the crystallographic planes (110) with  $\text{I}_{\text{cr}}$  of 40-42% [70]. In reference [71], the objective was to determine the physicochemical characteristics of Sac-Beh corn starch obtained and *Delonix regia* galactomannan and use them to produce films with vanillin had potential use as edible film material for coating on climacteric fruits preservation, obtaining crystallographic data similar to this paper. Similar case is for properties of galactomannan bioplastics from *Prosopis juliflora* with citric acid [72].

### 3.1.4. FTIR


The infrared spectrum of the compound shows several prominent absorption bands. The  $-\text{OH}$  stretching is observed at  $339 \text{ cm}^{-1}$ , indicating the presence of hydroxyl groups. The  $\text{C}-\text{H}$  band is located at  $2927 \text{ cm}^{-1}$ , and the carbonyl band is seen at  $1743 \text{ cm}^{-1}$ . Furthermore, the carboxylate group displays a distinct carbonyl band at  $1621 \text{ cm}^{-1}$  ( $\text{C}=\text{O}$  from  $-\text{COO}^-$ ). The  $\text{C}-\text{H}$  side-chain bending  $-\text{CH}_2\text{OH}$  exhibits multiple bands at  $1413 \text{ cm}^{-1}$ ,  $1375$  and  $1327 \text{ cm}^{-1}$ . Additionally, a strong absorption peak is observed at  $1242 \text{ cm}^{-1}$  corresponding to  $\text{C}-\text{O}-\text{C}$  stretching. Furthermore, the absorption peaks in the range of  $1074 \text{ cm}^{-1}$  to  $1047 \text{ cm}^{-1}$  are assigned to  $\text{C}-\text{O}$  glucopyranosidic bending. Lastly, signals out-of-plane bending  $\text{C}-\text{O}$  are noted at frequencies of  $781$ – $777$  and  $704 \text{ cm}^{-1}$  [69–73]. This comprehensive analysis provides valuable insight into the molecular structure and composition of the compound under investigation.



**Figure 2.** FTIR of gums.

### 3.1.5. DSC

The glass transition temperature ( $T_g$ ) is a critical property of polymeric materials, as it marks the onset of significant molecular motion and can have a profound effect on the material's mechanical and thermal properties. In the case of three particular films, it has been found that the  $T_g$  falls within a range of 40 to 50°C. This broad range highlights the difficulty in pinpointing an exact  $T_g$  for these films, as it is not a sharply defined transition. On the other hand, the melting temperatures ( $T_m$ ) are more readily observable and have been determined to be 134°C for LMFGT, 143°C for LMFGA, and 132°C for LMFGB. The relatively close proximity of  $T_m$  values for LMFGT and LMFGB indicates similarities in their molecular structures and bonding interactions. However, the higher  $T_m$  value for LMFGA suggests that its molecular structure possesses stronger intracatenary hydrogen bonding. This difference in melting temperatures can be attributed to variations in molecular packing arrangements within the films.




**Figure 3.** DSC of gums.

The stronger intermolecular interactions present in LMFGA result in a higher energy barrier required to disrupt these bonds and initiate melting. Understanding these thermal properties is crucial for predicting how these films will behave under different processing conditions or when subjected to varying environmental factors such as temperature changes. By elucidating how molecular structure influences thermal behavior, researchers can better tailor these materials for specific applications. The glass transition temperature may prove elusive due to its diffuse nature, melting temperatures offer insight into the differences in molecular packing and strength, for example, the case is carrageenan 2%/PVA8% films with  $T_g$  of 217.57 °C [73]. According to reference [74], the  $T_g$  of pectin is 70.8°C and the  $T_m$  is 119.5°C. This explains that the 1:2 ratio of pectin and LMFG at different hydrolysis is predominant over pectin, mainly due to the presence of LMFG.

In studying the intrinsic viscosity and molecular weight data, see reference [55], it becomes evident that basic hydrolysis is the most energetically favorable process. This conclusion is drawn from the decrease in these parameters compared to thermal and acid hydrolysis. The nature of the biopolymer, a polysaccharide rich in hydroxyl and carboxyl groups, plays a significant role in this phenomenon. The incorporation of  $\text{Na}^+$  by the carboxyl group increases solubility and promotes greater bond breaking during basic hydrolysis. Conversely, acid hydrolysis leads to greater unwinding of the polysaccharide, resulting in increased solubilization of groups and subsequent higher values for hydrodynamic radius and hydration value. These findings shed light on the intricate behavior of biopolymers under different hydrolytic conditions.

### 3.1.6. TGA

The thermal stability of LMFGT, LMFGA, and LMFGB has been determined to be 184.7°C, 200°C, and 186.4°C, respectively [73]. This data confirms the effect of intrachain hydrogen bonds on the thermal stability of these films, with LMFGA exhibiting the highest stability due to the presence of these bonds. These findings are significant in understanding the properties and potential applications of these materials in various industries. The identification of specific factors contributing to thermal stability will aid in further research and development efforts aimed at enhancing the performance of these films for practical use. The thermal stability of pectins is up to 215°C [74], although this is greater than those with LMFG, this may be due to the fact that they have fewer functional groups that can be oxidized.





**Figure 4.** TGA of gums.

### 3.2. *Lithraea Molleoides* Fruit Gum Films (LMFG films)

#### 3.2.1. SEM-EDX

The surface images show a slight undulation type of low mountains and shallow valleys. There are also certain isolated particles that are cellulosic remains that do not affect permeability. The surface image in LMFGTf is smooth while the undulations are more marked in the LMFGBf surface image. Regarding the presence of sodium on the surface of the films, it is LMFGBf > LMFGTf > LMFGAf. The presence of sodium accounts for an increase in the rigidity of the film due to the presence of -COONa, a phenomenon evidenced in the mechanical tests, discussed later [70]. The pectin films appear homogeneous on the surface except for some particles and imperfections in minor quantities and a morphology similar to craters, valleys, and peaks (not acute) [74].





**Figure 5.** SEM surface images of a) LMFGTf, b) LMFGAf and c) LMFGBf. Each with its corresponding elemental analysis by EDX.

### 3.2.2. Mechanical Test, WVP-Water Vapor Sorption (WVS)

Water vapor transport from the atmosphere through the packaging to the product is assessed by the WVP. High or low water vapor permeability of packaging is prescribed for fresh or dehydrated vegetable products, as this case from 0.97-2.06 ng.m/ m<sup>2</sup> s Pa. However, highly water permeable materials may limit their use as food packaging, as Pec2.5 with 0.55 ng.m/ m<sup>2</sup> s Pa, because undesirable reactions promoted by water and the contained carbohydrates, lipids and proteins of the food may occur, decreasing its shelf life [34, 67-68].

WVP in films with glycerol at 25°C of pectins (without glycerol) of 1.6-4.7, chitosan 2% with 4.8-7.3, starch/chitosan 0.15-3.3, sago starch/alginate at 20.7-34.6, cassava starch 5% at 54-139, gellan 0.5% at 18-23, alginate 1.5% at 7-14 [7]. Where the units of WVP are similar to that of this paper according to reference [7]. In the case of  $\kappa$ -carrageenan/starch/ZnONPs based films [34], these have a lower WVP compared to those made in this paper, this is because these films have a greater affinity for water due to the greater amount of hydrogen bonds. The same can be observed in films of Pectin/chitosan with noni fruit extract where values range from 1.1 to 2.3 ng m/m<sup>2</sup> Pa s [75].

**Table 4.** Mechanical properties and water vapor permeation of gums (e, is thickness).

Films	e (μm)	ε <sub>max</sub> %	σ <sub>max</sub> (MPa)	E (MPa)	WVP P (ng.m/ m <sup>2</sup> s Pa)
Pec2.5	207.8±9.2	20.08±0.90	23.79±0.97	32.85±1.1	0.55
LMFGTf	224.4±8.1	24.47±0.78	8.44±0.34	19.65±0.91	0.97
LMFGAf	264.6±6.5	25.58±0.06	21.87±0.87	47.23±0.82	1.52
LMFGBf	221.9±5.8	19.40±0.88	13.37±0.56	26.05±0.89	2.06

Mechanical tests account for the physical integrity of the material under study, including its stability when applied to a force. The films have a dissimilar response to the applied force, for example, LMFGTf and LMFGBf have a low maximum stress at break and a similar maximum elongation at break between 19-25%, with a Young's modulus of 19-26MPa; The LMFGAf film has similar maximum elongation at break at 25.58%, σ<sub>max</sub> of 21.87MPa with an E of 47.23MPa, that is to say, the film is more rigid, perhaps its high molecular weight of 589000 g/mol causes this response in the film. For thermal and basic hydrolysis, the fruit of *Lithraea molleoides* responds in a similar way, which causes the pectin polymer matrix to have a similar response and does not show synergism. However, acid hydrolysis compromises the polymer matrix, improving the rigidity of the material, this is due to a greater interaction between the pectin polymer matrix and LMFGAf through an improvement in hydrogen bond interactions. Another factor to take into account is the thickness of the film, which shows different mechanical properties due to the greater force to be applied. Where the mechanical tests are practically similar to those observed below. As for the mechanical test data of Pec2.5, ε<sub>max</sub> is 20.08%, σ<sub>max</sub> is 23.8MPa and E is 32.85MPa. These data of pure pectin are similar to those of LMFAf where the interactions are not very marked, which means they are structurally and chemically similar. As for the mechanical tests for reference [7], the ε<sub>max</sub> for pectins (without glycerol) was 0.8-1.2, chitosan 2% with 18-106, starch/chitosan with 61-152, sago starch/alginate with 3.7-13.2, cassava starch 5% with 39-164, alginate 1.5% between 5-20. While σ<sub>max</sub> (MPa) for pectins (without glycerol) was 13-25, chitosan 2% with 5.5-21.3, starch/chitosan with 61-152, sago starch/alginate with 13-16, cassava starch 5% with 1-4.7 and alginate 1.5% with 23-160 [7].

### 3.2.3. Biodegradability

The biodegradability of the films under study indicates a rapid decomposition process, with almost total breakdown occurring within ten days and Pec2.5 in 8 days. This phenomenon is attributed to the consumption of these polysaccharide materials by microorganisms at a temperature of 30°C and with a relative humidity of 85%. These findings suggest that the films proceed in a similar and efficient manner, with significant degradation taking place over a short timeframe [65].

The use of algal polysaccharides for film forming are biodegradable, such as galactans, alginates, and ulvan, have shown tremendous potential in the development of novel packaging materials with improved barrier, mechanical, antioxidant, and antimicrobial properties [10, 18, 25]. In a recent study [40], metalloanthocyanin-inspired biodegradable packaging films were developed by incorporating purple cauliflower extracted anthocyanins into alginate/carboxymethyl chitosan hybrid polymer matrices. The addition of fucoidan further enhanced the mechanical and antibacterial activity of the films. These complexation processes also resulted in improved storage stability and antioxidant capability while reducing the release rate of anthocyanins. The development of edible films and coatings has seen substantial growth in recent years and is expected to significantly impact the quality of food products in the future. Additionally, research into polysaccharide-based films with ionic inclusion liquids (ILs) and deep eutectic solvents (DESs) as potential replacements for conventional solvents/plasticizers has shown promising results [10, 18, 32]. The great potential for active films based on commercial polysaccharides incorporating ZnONPs given they provide improved functionality compared with conventional packing materials but more research needs be conducted especially concerning safety issues before widespread adoption in commercial applications occurs [34]. Blended films consisting of sodium carboxymethylcellulose (CMC), chitosan (CS), sodium alginate (SA), glycerol, CaCl<sub>2</sub> as plasticizer/crosslinker enriched with monobasic ammonium

phosphate have also demonstrated increased water resistance and thermal stability while enhancing biodegradability [76].

#### 4. Discussion

*Lithraea molleoides* fruit gum (LMFG) is a valuable product obtained from the total hydrolysis of the fruit. The hydrolysis process involves three methods: thermal (LMFGT), basic (LMFGB), and acid (LMFGA). The yield for the LMFGB flour is 33.88%, for the LMFGA 15.43% and for the LMFGT 11.11%. This means that basic hydrolysis is more efficient in extracting polysaccharide, while thermal hydrolysis is less efficient. In reference [55] where molecular weight for LMFGB is 85000 g/mol, followed in ascending order by LMFGT with a value of 195000 g/mol and ending with LMFGA with 589000 g/mol. These molecular weight values largely justify the behavior of the resulting films. The resulting hydrolysates are then combined with pectins in a 1:2 ratio to form films. In this study, the focus is on utilizing the hydrolysates of *Lithraea molleoides* gums for films applications, with an evaluation of their structural and physicochemical characteristics. The films produced exhibit excellent mechanical properties y comparables al film de pectin (Pec2.5) and low water vapor permeability, as well as good thermal stability less than 200°C. The films blends are biodegradability in ten days, but pectin film are seven days, this may be due to the presence of antioxidants providing protection against soil microorganisms [77].

#### 5. Conclusions

The films obtained by the different hydrolysis give good yields and contributions in polysaccharides that can be mixed with pectins and form films with good mechanical characteristics and water vapor permeability and at the same time resistant to microorganisms. Thermal stability is up to 200°C with  $T_g$  between 40 and 50°C and  $T_m$  from 132 to 143°C, which indicates an excellent material that can be extruded and is also thermally resistant. The packaging capacity is strengthened since it has a certain protection due to its antioxidant capacity.

**Author Contributions:** Conceptualization, F.B. and M.M.; methodology, F.B.; validation, M.G., G.M.; formal analysis, F.B. and G.M.; investigation, M.G.; resources, M.M.; writing—original draft preparation, F.B. and M.M.; writing—review and editing, F.B., M.G. and M.M. All authors have read and agreed to the published version of the manuscript.

**Funding:** PICT-2020-SERIEA-00895 (RAICES). Title: "Obtención de Polisacáridos a partir de Vegetales y Microorganismos de la Región del Semiárido de San Luis. Aplicaciones: Alimentarias, Geles y Bioempaque", 2. PROICO 2-3423, UNSL: "Bioprospección de Recursos Autóctonos Vegetales y Microbianos de la Provincia de San Luis con Potencial Uso Biotecnológico" and 3. PIP 2021/2023, IF-2021-85081432-APN-DCP#CONICET, "Valorización biotecnológica de efluentes de destilería para la obtención de productos microbianos".

**Acknowledgments:** The authors thank the following institutions in Argentina. Instituto de Física Aplicada (INFAP-UNSL-CONICET) and Laboratorio de Investigación y Servicios de Química Física (LISeQF-UNSL). The authors also thank Javier Rigau from the Instituto de Investigación en Tecnología Química (INTEQUI-UNSL-CONICET) for their determinations of the FTIR, TGA, and DSC; and Ariel Ochoa from the Laboratorio de Membranas y Biomateriales del INFAP-CONICET-UNSL for their contributions to the mechanical test and water vapor permeability results.

**Conflicts of Interest:** The authors declare no conflicts of interest.

## References

1. Kadac-Czapska, K., Knez, E., Gierszewska, M., Olewnik-Kruszkowska, E., & Grembecka, M. (2023). Microplastics derived from food packaging waste—their origin and health risks. *Materials*, 16(2), 674.
2. Ferreira, M. S., Linhares, R., & Martelli, M. (2016). Films and coatings from agro-industrial residues. Chapter 11, In *Edible films and coatings* (pp. 211-232). CRC Press, London, UK.
3. Nussinovitch, A. (2009). Biopolymer films and composite coatings. In *Modern biopolymer science* (pp. 295-326). Academic Press, London, UK.
4. da Silva, M. A., & Bierhalz, A. C. K. (2023). *Biopolymer Films and Composite Coatings: Applications*. In *Handbook of Biopolymers* (pp. 1229-1261). Springer Nature, Singapore.
5. Lopez, O. V., Garcia, M. A., & Zaritzky, N. E. (2010). Novel sources of edible films and coatings. *Stewart Postharvest Review*, 3, 2, 1-8.
6. Beyza, H., Fatma, K., & Hecer, C. (2018). Edible films and coatings: A good idea from past to future technology. *J. Food Technol*, 5, 28-33.
7. Campos, C. A., Gerschenson, L. N., & Flores, S. K. (2011). Development of edible films and coatings with antimicrobial activity. *Food and bioprocess technology*, 4, 849-875.
8. Dyshlyuk, L., Babich, O., Belova, D., & Prosekov, A. (2017). Comparative analysis of physical and chemical properties of biodegradable edible films of various compositions. *Journal of food process engineering*, 40(1), e12331.
9. Subroto, E., Indiarto, R., Pangawikan, A. D., & Prakoso, F. (2021). Production and Characteristics of Composite Edible Films Based on Polysaccharides and Proteins. *International Journal of Emerging Trends in Engineering Research*, 9(2) 42-48.
10. Han, J. H. (2014). Edible films and coatings: a review. Chapter 9. in *Innovations in food packaging*, pp 213-255, Academic Press, San Diego, CA, USA.
11. Šuput, D. Z., Lazić, V. L., Popović, S. Z., & Hromiš, N. M. (2015). Edible films and coatings: Sources, properties and application. *Food and Feed Research*, 42 (1), 11-22.
12. Liyanapathiranage, A., Dassanayake, R. S., Gamage, A., Karri, R. R., Manamperi, A., Evon, P., ... & Merah, O. (2023). Recent developments in edible films and coatings for fruits and vegetables. *Coatings*, 13(7), 1177.
13. Drevet, R., & Benhayoune, H. (2022). Advanced Biomaterials and Coatings. *Coatings*, 12(7), 965.
14. Marangoni Júnior, L., Coltro, L., Dantas, F. B. H., & Vieira, R. P. (2022). Research on food packaging and storage. *Coatings*, 12(11), 1714.
15. Dhanapal A., Sasikala. P, Rajamani L., Kavitha.V, Yazhini G., Banu S. (2012). Edible films from polysaccharides. *Food science and quality management*, 3, 9-17.
16. Kocira, A., Kozłowicz, K., Panasiewicz, K., Staniak, M., Szpunar-Krok, E., & Horthyńska, P. (2021). Polysaccharides as edible films and coatings: Characteristics and influence on fruit and vegetable quality—A review. *Agronomy*, 11(5), 813.
17. Nieto, M. B. (2009). Structure and function of polysaccharide gum-based edible films and coatings. Chapter 2. In *Edible films and coatings for food applications*, pp 57-112, Springer-Nature, Berlin, Germany.
18. Galus, S., Arik Kibar, E. A., Gniewosz, M., & Kraśniewska, K. (2020). Novel materials in the preparation of edible films and coatings—A review. *Coatings*, 10(7), 674.
19. Avramescu, S. M., Butean, C., Popa, C. V., Ortan, A., Moraru, I., & Temocico, G. (2020). Edible and functionalized films/coatings—performances and perspectives. *Coatings* 10: 687.
20. Falguera, V., Quintero, J. P., Jiménez, A., Muñoz, J. A., & Ibarz, A. (2011). Edible films and coatings: Structures, active functions and trends in their use. *Trends in Food Science & Technology*, 22(6), 292-303.
21. Brasselet, C., Pierre, G., Dubessay, P., Dols-Lafargue, M., Coulon, J., Maupeu, J., ... & Delattre, C. (2019). Modification of chitosan for the generation of functional derivatives. *Applied Sciences*, 9(7), 1321.
22. Roman, M., Nechita, P., Vasile, M. A., & Cantaragiu Ceoromila, A. M. (2023). Barrier and Antimicrobial Properties of Coatings Based on Xylan Derivatives and Chitosan for Food Packaging Papers. *Coatings*, 13(10), 1761.
23. Pinto, J. P., D'souza, O. J., Hiremani, V. D., Dalbanjan, N. P., Kumar, S. P., Narasagoudr, S. S., ... & Chougale, R. B. (2023). Functional properties of taro starch reinforced polysaccharide based films for active packaging. *Food Bioscience*, 56, 103340.
24. Tarnowiecka-Kuca, A., Peeters, R., Bamps, B., Stobińska, M., Kamola, P., Wierzchowski, A., ... & Mizielińska, M. (2023). Paper Coatings Based on Polyvinyl Alcohol and Cellulose Nanocrystals Using Various Coating Techniques and Determination of Their Barrier Properties. *Coatings*, 13(11), 1975.
25. Thiviya, P., Gamage, A., Liyanapathiranage, A., Makehelwala, M., Dassanayake, R. S., Manamperi, A., ... & Madhujith, T. (2023). Algal polysaccharides: Structure, preparation and applications in food packaging. *Food Chemistry*, 405, 134903.
26. Huang, H. L., Tsai, I. L., Lin, C., Hang, Y. H., Ho, Y. C., Tsai, M. L., & Mi, F. L. (2023). Intelligent films of marine polysaccharides and purple cauliflower extract for food packaging and spoilage monitoring. *Carbohydrate Polymers*, 299, 120133.

27. Kokkuvayil Ramadas, B., Rhim, J. W., & Roy, S. (2024). Recent Progress of Carrageenan-Based Composite Films in Active and Intelligent Food Packaging Applications. *Polymers*, 16(7), 1001.
28. Chang, S., Zou, X., Zhu, B., You, L., Zhao, Z., & Hileuskaya, K. (2023). The characteristics of polysaccharide from Gracilaria chouae and its application in food packaging with carboxymethyl cellulose and lysozyme. *Food Hydrocolloids*, 135, 108109.
29. Long, J., Zhang, W., Zhao, M., & Ruan, C. Q. (2023). The reduce of water vapor permeability of polysaccharide-based films in food packaging: A comprehensive review. *Carbohydrate Polymers*, 121267.
30. Ferreira, D. C. M., Dos Santos, P. N., Santos, F. H., Molina, G., & Pelissari, F. M. (2023). Sustainability approaches for agrowaste solution: Biodegradable packaging and microbial polysaccharides bio-production. *Science of The Total Environment*, 886, 163922.
31. Yu, J., Liu, X., Xu, S., Shao, P., Li, J., Chen, Z., ... & Renard, C. M. (2023). Advances in green solvents for production of polysaccharide-based packaging films: Insights of ionic liquids and deep eutectic solvents. *Comprehensive Reviews in Food Science and Food Safety*, 22(2), 1030-1057.
32. Wang, H., Cao, Z., Yao, L., Feng, T., Song, S., & Sun, M. (2023). Insights into the Edible and Biodegradable Ulvan-Based Films and Coatings for Food Packaging. *Foods*, 12(8), 1622.
33. da Silva Bruni, A. R., Friedrichsen, J. D. S. A., de Jesus, G. A. M., da Silva Alves, E., da Costa, J. C. M., Souza, P. R., ... & Bonafe, E. G. (2023). Characterization and application of active films based on commercial polysaccharides incorporating ZnONPs. *International Journal of Biological Macromolecules*, 224, 1322-1336.
34. Tang, H., Han, Z., Zhao, C., Jiang, Q., Tang, Y., Li, Y., & Cheng, Z. (2023). Preparation and characterization of Aloe vera polysaccharide-based packaging film and its application in blueberry preservation. *Progress in Organic Coatings*, 177, 107445.
35. Carneiro-da-Cunha, M. G., Cerqueira, M. A., Souza, B. W., Souza, M. P., Teixeira, J. A., & Vicente, A. A. (2009). Physical properties of edible coatings and films made with a polysaccharide from *Anacardium occidentale* L. *Journal of Food Engineering*, 95(3), 379-385.
36. Irimia, A., & Popescu, C. M. (2023). Bioactive Paper Packaging for Extended Food Shelf Life. *Coatings*, 13(9), 1658.
37. Salama, A., & El-Sakhawy, M. (2024). Polysaccharides/propolis composite as promising materials with biomedical and packaging applications: A review. *Biomass Conversion and Biorefinery*, 14(4), 4555-4565.
38. Gharibzahedi, S. M. T., Ahmadigol, A., Khubber, S., & Altintas, Z. (2023). Bionanocomposite films with plasticized WPI-jujube polysaccharide/starch nanocrystal blends for packaging fresh-cut carrots. *Food Packaging and Shelf Life*, 36, 101042.
39. Huang, J., Wu, W., Niu, B., Fang, X., Chen, H., Wang, Y., & Gao, H. (2023). Characterization of *Zizania latifolia* polysaccharide-corn starch composite films and their application in the postharvest preservation of strawberries. *LWT*, 173, 114332.
40. Song, X., Wang, X., Zhang, H., Zhang, D., Li, Z., & Yu, J. (2023). Characterization of polysaccharide-based antibacterial films properties of loaded with Nisin and preservation of fresh-cut watermelon. *Food Science and Technology*, 43, e127522.
41. Zheng, M., Zhu, Y., Zhuang, Y., Tan, K. B., & Chen, J. (2023). Effects of grape seed extract on the properties of pullulan polysaccharide/xanthan gum active films for apple preservation. *International Journal of Biological Macromolecules*, 241, 124617.
42. Jafarian, M., Taghinia, P., & Sedaghati, S. (2023). Development and characterization of a new active and intelligent packaging system based on soluble soybean polysaccharide-*Malva sylvestris* extract. *Journal of Food Science and Technology*, 60(7), 1944-1951.
43. Şahin, S., Eyüboğlu, S., Karkar, B., & Ata, G. D. (2024). Development of bioactive films loaded with extract and polysaccharide of *Pinus brutia* bark. *Journal of Food Science*.
44. Yu, T., Wu, D., Liang, B., Wang, J., Shang, X., & Wu, Q. (2023). Preparation, characterization of *Auricularia auricula* polysaccharide-based films and application in meat preservation. *International Journal of Biological Macromolecules*, 244, 125242.
45. Janik, W., Jakubski, Ł., Kudła, S., & Dudek, G. (2023). Modified polysaccharides for food packaging applications: A review. *International Journal of Biological Macromolecules*, 128916.
46. Yang, X., Niu, Y., Fan, Y., Zheng, T., & Fan, J. (2024). Green synthesis of *Poria cocos* polysaccharides-silver nanoparticles and their applications in food packaging. *International Journal of Biological Macromolecules*, 269, 131928.
47. Akhtar, H. M. S., Ahmed, S., Olewnik-Kruszkowska, E., Gierszewska, M., Brzezinska, M. S., Dembińska, K., & Kalwasinska, A. (2023). Carboxymethyl cellulose based films enriched with polysaccharides from mulberry leaves (*Morus alba* L.) as new biodegradable packaging material. *International Journal of Biological Macromolecules*, 253, 127633.
48. Kafashan, A., Joze-Majidi, H., Kazemi-Pasarvi, S., Babaei, A., & Jafari, S. M. (2023). Nanocomposites of soluble soybean polysaccharides with grape skin anthocyanins and graphene oxide as an efficient halochromic smart packaging. *Sustainable Materials and Technologies*, 38, e00755.

49. Sarkar, S., Manna, S., Das, S., De, S., Paul, P., Dua, T. K., ... & Nandi, G. (2023). Current Status of Marine Animal Derived Polysaccharides in Sustainable Food Packaging. *ACS Food Science & Technology*, 3(11), 1877-1889.

50. Liu, J., Dong, Y., Zheng, X., Pei, Y., & Tang, K. (2024). Citric acid crosslinked soluble soybean polysaccharide films for active food packaging applications. *Food Chemistry*, 438, 138009.

51. Chi, K., He, J., Lin, W. S., Bokhari, S. M., & Catchmark, J. M. (2023). Electrostatically complexed natural polysaccharides as aqueous barrier coatings for sustainable and recyclable fiber-based packaging. *ACS Applied Materials & Interfaces*, 15(9), 12248-12260.

52. Kaya, E. C., & Yucel, U. (2023). Advances in cellulose-based packaging films for food products. In *Cellulose-Fundamentals and Conversion into Biofuel and Useful Chemicals*. pp 1-21 Intech Open, London, UK.

53. Dong, Y., Li, Y., Ma, Z., Rao, Z., Zheng, X., Tang, K., & Liu, J. (2023). Effect of polyol plasticizers on properties and microstructure of soluble soybean polysaccharide edible films. *Food Packaging and Shelf Life*, 35, 101023.

54. Garro, M. F., Salinas Ibáñez, A. G., Vega, A. E., Arismendi Sosa, A. C., Pelzer, L., Saad, J. R. & Maria, A. O. (2015). Gastroprotective effects and antimicrobial activity of *Lithraea molleoides* and isolated compounds against *Helicobacter pylori*. *Journal of Ethnopharmacology*, 176, 469-474.

55. Becerra, F., Garro M.F., Masuelli, M. (2023). Influence of the Type of Hydrolysis on the Intrinsic Viscosity of *Lithraea Molleoides* Fruit Gum. *J. Mate. Poly. Sci.*, 3(2): 1-6.

56. Rulli, M. M., Villegas, L. B., Barcia, C. S., & Colin, V. L. (2021). Bioconversion of sugarcane vinasse into fungal biomass protein and its potential use in fish farming. *Journal of Environmental Chemical Engineering*, 9(5), 106136.

57. Deng, C.; Hu, Z.; Fu, H.; Hu, M.; Xu, X.; Chen, J. Chen, Chemical analysis and antioxidant activity in vitro of  $\beta$ -D-glucan isolated from *Dictyophora indusiate*. *Int. J. Biol. Macromol.* 2012, 51, 70-75.

58. Du, X.; Mu, H.; Zhou, S.; Zhang, Y.; Zhu, X. Chemical analysis and antioxidant activity of polysaccharides extracted from *Inonotus obliquus* sclerotia. *Int. J. Biol. Macromol.* 2013, 62, 691-696.

59. Kaur, R.; Arora, S.; Singh, B. Antioxidant activity of the phenol rich fractions of leaves of *Chukrasia tabularis* A. Juss. *Bioresour. Technol.* 2008, 99, 7692-7698.

60. Ainsworth, E.A.; Gillespie, K.M.J.N.P. Estimation of total phenolic content and other oxidation substrates in plant tissues using Folin-Ciocalteu reagent. *Nat. Protoc.* 2007, 2, 875-877.

61. Zanon, M.; Masuelli, M. Purification and characterization of alcayota gum. *Biopolym. Res.* 2018, 2, 105.

62. Beppu, M.M.; Vieira, R.S.; Aimoli, C.G.; Santana, C.C. Crosslinking of chitosan membranes using glutaraldehyde: Effect on ion permeability and water absorption. *J. Membr. Sci.* 2007, 301, 126-130.

63. Al Sagheer, F.A.; Al-Sughayer, M.A.; Muslim, S.; Elsabee, M.Z. Extraction and characterization of chitin and chitosan from marine sources in Arabian Gulf. *Carbohydr. Polym.* 2009, 77, 410-419.

64. Barbosa, H.F.; Francisco, D.S.; Ferreira, A.P.; Cavalheiro, É.T. A new look towards the thermal decomposition of chitins and chitosans with different degrees of deacetylation by coupled TG-FTIR. *Carbohydr. Polym.* 2019, 225, 115232.

65. Zanon, M.; Masuelli, M.A. Alcayota gum films: Experimental reviews. *J. Mater. Sci. Chem. Eng.* 2018, 6, 11-58.

66. Lazo, L., Melo, G. M., Auad, M. L., Filippa, M., & Masuelli, M. A. (2022). Synthesis and characterization of Chañar gum films. *Colloids and Interfaces*, 6(1), 10.

67. Illanes, C. O., Takara, E. A., Masuelli, M. A., & Ochoa, N. A. (2024). pH-responsive gum tragacanth hydrogels for high methylene blue adsorption. *Journal of Chemical Technology & Biotechnology*, 99(1), 31-39.

68. Masuelli, M. A., Lazo, L., Becerra, F., Torres, F., Illanes, C. O., Takara, A., ... & Bercea, M. (2024). Physical and Chemical Properties of *Pachycymbiola brasiliiana* Eggshells—From Application to Separative Processes. *Processes*, 12(4), 814.

69. Zapata-Luna, R. L., Davidov-Pardo, G., Pacheco, N., Ayora-Talavera, T., Espinosa-Andrews, H., García-Márquez, E., & Cuevas-Bernardino, J. C. (2023). Structural and physicochemical properties of bio-chemical chitosan and its performing in an active film with quercetin and *Phaseolus polyanthus* starch. *Revista Mexicana de Ingeniería Química*, 22(2), 1-11.

70. Acosta-Ferreira, S., Castillo, O.S., Madera-Santana, J.T., Mendoza-García, D.A., Núñez-Colín, C.A., Grijalva-Verdugo, C., Villa-Lerma, A.G., Morales-Vargas, A. T., and Rodríguez-Núñez, J.R. (2020). Production and physicochemical characterization of chitosan for the harvesting of wild microalgae consortia. *Biotechnology Reports* 28, e00554.

71. Chel-Guerrero, L., Betancur-Ancona, D., Aguilar-Vega, M., & Rodríguez-Canto, W. (2024). Films properties of QPM corn starch with *Delonix regia* seed galactomannan as an edible coating material. *International Journal of Biological Macromolecules*, 255, 128408.

72. Leite, K., Nascimento, J., Neto, J. H. L., & Gomes, K. (2024). Influence of citric acid on the properties of galactomannan bioplastics from *Prosopis juliflora* (Sw.) DC.: Influência do ácido cítrico nas propriedades dos bioplásticos de galactomanana de *Prosopis juliflora* (sw.) DC. *Concilium*, 24.

73. Meng, F., Zhang, Y., Xiong, Z., Wang, G., Li, F., & Zhang, L. (2018). Mechanical, hydrophobic and thermal properties of an organic-inorganic hybrid carrageenan-polyvinyl alcohol composite film. Composites Part B: Engineering, 143, 1-8.
74. Ruano, P.; Lazo Delgado, L.; Picco, S.; Villegas, L.; Tonelli, F.; Aguilera Merlo, M. E.; Rigau, J.; Diaz, D.; Masuelli, M. (2020). Extraction and Characterization of Pectins from Peels of Criolla Oranges (*Citrus sinensis*). Experimental Reviews. Chapter 1. In Pectins - Extraction, Purification, Characterization and Applications. Ed. Martin Masuelli. INTECH Publishers, London, UK.
75. Lin, X., Chen, S., Wang, R., Li, C., & Wang, L. (2023). Fabrication, characterization and biological properties of pectin and/or chitosan-based films incorporated with noni (*Morinda citrifolia*) fruit extract. Food Hydrocolloids, 134, 108025.
76. Ciaramitaro, V., Piacenza, E., Paliaga, S., Cavallaro, G., Badalucco, L., Laudicina, V. A., & Chillura Martino, D. F. (2024). Exploring the Feasibility of Polysaccharide-Based Mulch Films with Controlled Ammonium and Phosphate Ions Release for Sustainable Agriculture. Polymers, 16(16), 2298.
77. Li, H., Li, Z., Wang, P., Liu, Z., An, L., Zhang, X., ... & Gao, W. (2024). Evaluation of citrus pectin extraction methods: Synergistic enhancement of pectin's antioxidant capacity and gel properties through combined use of organic acids, ultrasonication, and microwaves. International Journal of Biological Macromolecules, 266, 131164.

**Disclaimer/Publisher's Note:** The statements, opinions and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of MDPI and/or the editor(s). MDPI and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions or products referred to in the content.